

Final Project Report:

Grant DE-FG02-04ER15604

Project Title: Surface Termination of M1 Phase and Rational Design of Propane Ammoxidation Catalysts

Report Period: 8/15/10 – 8/14/14

Applicant/Institution: University of Cincinnati

Street Address/City/State/Zip: P.O. Box 210222, Cincinnati, OH 45221-0222

Principal Investigator: Professor Vadim V. Guliyants

Address: Department of Biomedical, Chemical, and Environmental Engineering
University of Cincinnati, OH 45221-0012

Telephone: (513) 556-0203

E-Mail: vadim.guliyants@uc.edu

DOE/Office of Science Program Office: Chemical Sciences, Geosciences and Biosciences Division, Office of Basic Energy Sciences

DOE/Office of Science Program Office Technical Contact: Dr. Raul Miranda

Research Area: Catalysis Science

Summary

The overall objective of this research was to develop fundamental understanding of selective oxidation processes (oxidation, ammoxidation, and oxidative dehydrogenation) of lower alkanes (C₂-C₄) over complex Mo-V-M-O mixed metal oxides (M= Nb, Ta, Te, Sb, and their combinations, etc.) containing so-called “M1” and “M2” phases via the integration of theory and modeling; catalyst synthesis and characterization of its bulk and surface; microreactor studies; and catalyst optimization. Many exciting and important fundamental advances were made to date while pursuing the following specific objectives:

- *Establish roles of Mo-V-M-O M1 and M2 phases in propane ammoxidation*
- *Investigate Nb and Ta location in the M1 structure*
- *Elucidate surface *ab* plane termination in Mo-V-Te-Nb-O M1 catalysts*
- *Probe mechanism of propane ammoxidation over surface *ab* plane of Mo-V-Te-Nb-O M1 phase*

We demonstrated a synergy between the Mo-V-Te-Nb-O M1 and M2 phases at low propane conversion because this Nb-free M2 phase was much more active than the Nb-containing M1 phase in the ammoxidation of the propylene intermediate formed over the M1 phase (Korovchenko and Guliyants 2007; Korovchenko et al. 2007; Guliyants, 2008; Korovchenko et al. 2008). We also showed that at high propane conversion the Mo-V-Te-Nb-O M1 is the only phase required for propane ammoxidation to acrylonitrile (ACN) and oxidation to acrylic acid (Korovchenko et al. 2008) and that its surface *ab* planes are responsible for its activity and selectivity in propane (amm)oxidation (Guliyants et al. 2005a; Guliyants et al. 2005b; Guliyants et al. 2006a; Guliyants et al. 2006b; Trunschke et al. 2006). Redox VO_x sites present in the surface *ab* planes of the M1 phase activate C-H bonds in propane and propylene, whereas other surface MO_x species (Mo and Te) are responsible for the selectivity of the NH insertion into the allyl intermediate. Our XANES study confirmed that only VO_x species undergo reversible oxidation

state changes when the M1 catalyst is cycled between reducing (H_2/He) and oxidizing (O_2/He) environments (Shiju et al. 2007a; Shiju et al. 2008a).

Parallel structural studies of Mo-V-O, Mo-V-Te-O, Mo-V-Te-Nb-O and Mo-V-Te-Ta-O M1 phases revealed that the nature of substituting element (Nb, Ta, Mo or even V) at the pentagonal Site 9 (S9) has a significant impact on the vanadium occupancy in the proposed surface active center and its catalytic behavior in propane ammoxidation (Shiju et al. 2008b). ^{13}C -labeled propane ammoxidation to ACN over the Mo-V-Te-Nb-O M1 phase demonstrated that this reaction occurs directly via C_3 intermediates without their dimerization or skeletal rearrangement as was suggested previously for propane oxidation over other classes of mixed metal oxides (Shiju et al. 2007b). The Mo-V-Te-Nb-O M1 catalysts modified by atomic layer deposition (ALD) of alumina and silica and selectively exposing surface *ab* planes displayed much greater catalytic activity and selectivity in propane ammoxidation than the original Mo-V-Te-Nb-O M1 catalysts indicating that the surface *ab* planes contain the active and selective catalytic sites for this reaction (Shiju et al. 2008c).

Our experimental studies during the last renewal period have focused on the synthesis and characterization of Ta- and Sb-substituted M1 and M2 phases. Pure reference Mo-V-Te-Ta-O M1 phases with different Ta content were successfully made for the first time by hydrothermal synthesis. The Ta-substituted M1 phases were used a model for the structurally and chemically similar Nb-M1 because Nb and Mo in the latter M1 phase could not distinguished by structural methods due to similar scattering factors of these 2 elements. The Ta-M1 phases were employed in a STEM study to directly image the Ta sites in the M1 structure and determine their partial occupancies from the analysis of the Ta atomic column contrast across many unit cells from the surface region to the crystal bulk (Yu et al. 2012). The same analysis was also applied to determine the Mo/V partial occupancies in 10 other metal lattice sites in the M1 phase. This analysis revealed that Ta was present only in so-called pentagonal bipyramidal Site 9 where its occupancy varied from 12 to 39%, the rest being Mo. Contrary to findings of an earlier study employing a Ta-M1 phase made by rapid slurry evaporation (Pyrz et al. 2009), the Ta content was constant from the surface region to the crystal bulk confirming that hydrothermal synthesis results in better-defined catalytic materials. A density functional theory (DFT) study of the model clusters of the Ta- and Nb-M1 phase further confirmed that Site 9 was by far the most preferred location for both Ta and Nb, thereby providing first concrete support for earlier hypothetical models of Nb location in the M1 phase (Yu et al. 2012).

The Ta-M1 phase with the highest Ta content (39% Site 9 occupancy) displayed slightly higher selectivity to ACN (87 vs. 84 mol. %) at optimal propane conversion (28%) as compared to the Nb-M1 phase with assumed 100% Nb occupancy at Site 9. A linear correlation was established between the selectivity to ACN and the Ta partial occupancy in Site 9 suggesting a beneficial active site isolation effect due to the presence of Ta at Site 9. Moreover, a volcano-shaped curve was suggested when the selectivity to ACN at optimal propane conversion (28%) was plotted against the probability of finding a single V^{5+} cation in the proposed active center (Woo et al. 2014). This is primarily explained by poor site isolation effect observed at very high concentration of active centers in a Mo-V-Te-O M1 catalyst. The maximum selectivity to ACN corresponded to ca. 49% probability of finding just one V^{5+} cation in the active center, which is the proposed active and selective site for propane activation to ACN over the *ab* planes of the M1 phase. This volcano plot is in good agreement with another volcano plot reported in our earlier study of the Mo-V-Te-O M1 phases where the ACN selectivity was plotted against the V

concentration in the topmost surface of these M1 phases found in a LEIS study (Gulianti et al. 2005a). Furthermore, a direct correlation was indicated between the selectivity to combustion products (CO_x) and the probability of finding only Mo in the active center. This correlation suggested that Mo^{6+} might be responsible for combustion reactions.

These very important findings provide support for the new concept of active site isolation that manifests itself on two length scales. On a shorter length scale, the isolated (single) V^{5+} cations present at the active centers are associated with high activity and selectivity of the M1 phase in propane ammoxidation to ACN. On a longer length scale, these active centers are further isolated from one another due to the presence of either Ta or Nb at Site 9 that are unable to activate propane and other C_3 intermediates. The active site isolation on a longer length scale further boosts the selectivity of the M1 phase catalysts towards acrylonitrile. These novel insights into the composition of the active centers and roles of constituent metal oxide species guided our theoretical studies of propane ammoxidation on the surface *ab* planes of the Mo-V-Te-Nb-O M1 phase.

Our theoretical studies of propane ammoxidation on the surface *ab* planes of the Mo-V-Te-Nb-O M1 phase (Govindasamy et al. 2010; Muthukumar et al. 2011; Yu et al. 2014a; Yu et al. 2014b) have yielded significant new insights into the elementary reaction steps that suggest different pathways from those advanced in current hypothetical models. Contrary to the hypothetical models, propane is activated over a surface $\text{V}=\text{O}$ species resulting in isopropyl radical and H atoms adsorbed on $\text{V}=\text{O}$ and $\text{Te}=\text{O}$, respectively, with a 1.15 eV barrier consistent with the experimental observations. Moreover, the second and third H abstraction steps were also found to occur over the surface $\text{V}=\text{O}$ and $\text{Te}=\text{O}$ sites. Contrary to the hypothetical model, ammonia is activated on an oxo-depleted Mo site, which is different from the sites for dioxygen and propane activation. Activation of NH_x ($x=1-3$) species over this Mo site is energetically downhill all the way to recombination of N atoms into gas-phase dinitrogen, making the surface imido ($\text{Mo}=\text{NH}$) the most stable H-containing N species. NH insertion from $\text{Mo}=\text{NH}$ into the allyl radical was found to be energetically favorable proceeding essentially without an energy barrier (0.09 eV). This observation suggests that the selectivity of this step would depend on relative abundance of surface $\text{Mo}=\text{NH}$ and various oxygen-containing metal oxide species.

The findings gained in these experimental and theoretical studies are particularly significant due to unique ability of the M1 phase among mixed metal oxides to selectively catalyze several alkane transformation reactions, e.g., propane ammoxidation to ACN (Gulianti *et al.* 2006a), propane oxidation to acrylic acid (Gulianti et al. 2004; Gulianti et al. 2005a; Gulianti et al. 2005b; Trunschke et al. 2006; Gulianti et al. 2006b), selective oxidation of *n*-butane to butadiene and maleic anhydride and *i*-butane to methacrolein, and oxidative dehydrogenation (ODH) of ethane (Botella et al. 2004). Therefore, fundamental advances made in understanding the surface molecular structure – reactivity relationships for this unique system offer a possibility of not only rational design of propane ammoxidation catalysts, but also expanding the scope of selective alkane oxidation beyond the limited number of feedstocks that have met with technological and commercial success.

Researchers Supported During the Current Grant Period

J. Woo, Ph.D. student, Chemical Engineering, University of Cincinnati (2007-2015)

J. Yu, Ph.D. student, Chemical Engineering, University of Cincinnati (2009-2015)

Publications (2010-2015) resulting from DE-FG02-04ER15604

J. Yu, Y. Xu and V. V. Guliants, "Propane Ammoxidation over Mo-V-Te-Nb-O M1 Phase: Density Functional Theory Study of Propane Oxidative Dehydrogenation Steps", *Catalysis Today* 238 (2014) 28-34.

J. Yu, Y. Xu and V. V. Guliants, "Propane Ammoxidation over Mo-V-Te-Nb-O M1 Phase Investigated by DFT: Elementary Steps of Ammonia Adsorption, Activation and NH Insertion into π -Allyl Intermediate", *Topics in Catalysis* 57 (2014) 1145-1151.

J. Yu, J. Woo, A. Borisevich, Y. Xu and V. V. Guliants, "A Combined HAADF STEM and Density Functional Theory Study of Tantalum and Niobium Locations in the Mo-V-Te-Ta(Nb)-O M1 Phases", *Catal. Commun.* 29 (2012) 68-72.

K. Muthukumar, J. Yu, Y. Xu, and V. V. Guliants, "Propane Ammoxidation Over the Mo-V-Nb-Te-O M1 Phase: Reactivity of Surface Cations in Hydrogen Abstraction Steps", *Topics Catal.* 54 (2011) 605-613.

P. Biswas, J. Woo, V. V. Guliants, "Ruthenium and gold-doped M1 phase MoVNbTeO catalysts for propane ammoxidation to acrylonitrile", *Catal. Commun.* 12 (2010) 58-63.

A. Govindasamy, K. Muthukumar, J. Yu, Y. Xu, V. V. Guliants, "Adsorption of Propane, Isopropyl, and Hydrogen on Cluster Models of the M1 Phase of Mo-V-Te-Nb-O Mixed Metal Oxide Catalyst", *Journal of Physical Chemistry C* 114 (2010) 4544-4549.

submitted:

J. Woo, A. Borisevich, Q. He, V.V. Guliants, "Propane Ammoxidation Over Mo-V-Te-Ta-O M1 Phases: HAADF-STEM Study of Mo/V Distributions and Their Correlations with Catalytic Behavior", *Appl. Catal. A*.

Q. He, A. Borisevich, J. Woo, and V. V. Guliants, "HAADF STEM Observation of M1/M2 Phase Intergrowths: Implications for M1/M2 Synergy in Selective Ammoxidation of Propane", *ACS Nano*.

in preparation:

J. Yu, Y. Xu and V. V. Guliants, "Selective and Unselective Transformation Pathways During Propylene Ammoxidation: N Insertion vs. Oxidation Steps".

J. Yu, Y. Xu and V. V. Guliants, "Quantum Chemistry Based Microkinetic Modeling of Complex Catalytic Processes: Propane Ammoxidation over Mo-V-Te-Nb-O M1 Phase".

J. Woo, A. Borisevich, Q. He, V.V. Guliants, "Quantitative Analysis of Partial Occupancies of Metal Sites in the MoVTaTeO M1 Phase Determined on the Basis of HAADF STEM Imaging".

J. Woo and V.V. Guliants, "Probability Models of Propane Ammoxidation Behavior of MoVTaTeO M1 Phases Based on Quantitative Analysis of Partial Occupancies of Metal Sites from HAADF STEM Imaging".

J. Woo and V.V. Guliants, "New Insights into the Origins of M1/M2 Phase Synergy for Mo-V-(Nb, Ta)-(Te, Sb)-O Compositions".

Bibliography and References Cited

A. Govindasamy, K. Muthukumar, J. Yu, Y. Xu, V. V. Guliants, "Adsorption of Propane, Isopropyl, and Hydrogen on Cluster Models of the M1 Phase of Mo-V-Te-Nb-O Mixed Metal Oxide Catalyst", *Journal of Physical Chemistry C* 114 (2010) 4544-4549.

V.V. Guliants, R. Bhandari, J.N. Al-Saeedi, V. Vasudevan, R.S. Soman, O. Guerrero-Perez, M.A. Banares, "Bulk Mixed Mo-V-Te-O Catalysts for Propane Oxidation to Acrylic Acid", *Applied Catalysis A*, 274(1-2), 123-132, 2004.

(a) V.V. Guliants, R. Bhandari, H.H. Brongersma, A. Knoester, A.M. Gaffney, S. Han, "A Study of the Surface Region of the Mo-V-Te-O Catalysts for Propane Oxidation to Acrylic Acid", *Journal of Physical Chemistry B*, 109(20), 10234-10242, 2005.

(b) V.V. Guliants, R. Bhandari, B. Swaminathan, V.K. Vasudevan, H.H. Brongersma, A. Knoester, A.M. Gaffney, S. Han, "Roles of Surface Te, Nb, and Sb Oxides in Propane Oxidation to Acrylic Acid over Bulk Orthorhombic Mo-V-O Phase", *Journal of Physical Chemistry B*, 109(50), 24046-24055, 2005.

(a) V.V. Guliants, R. Bhandari, A.R. Hughett, S. Bhatt, B.D. Schuler, H.H. Brongersma, A. Knoester, A.M. Gaffney, S. Han, "Probe Molecule Chemisorption-Low Energy Ion Scattering Study of Surface Active Sites Present in the Orthorhombic Mo-V-(Te-Nb)-O Catalysts for Propane (Amm)oxidation", *Journal of Physical Chemistry B*, 110(12), 6129-6140, 2006.

(b) V.V. Guliants, H.H. Brongersma, A. Knoester, A.M. Gaffney, S. Han, "Surface Active Sites Present in the Orthorhombic M1 Phases: Low Energy Ion Scattering Study of Methanol and Allyl Alcohol Chemisorption over Mo-V-Te-Nb-O and Mo-V-O Catalysts", *Topics in Catalysis*, 38(1-3), 41-50, 2006.

V. V. Guliants, "M1/M2 phases for propane ammoxidation to acrylonitrile: recent insights into bulk microstructure, the nature of the active surface and reaction pathways", Preprints - American Chemical Society, Division of Petroleum Chemistry (2008), 53(1), 123-124.

(a) P. Korovchenko, V. V. Guliants, M. O. Guerrero-Perez, "Thermal transformation of the Mo-V-Te-O M1 to M2 phases: Synthesis, structural characteristics and catalytic performance in propane ammoxidation", Abstracts of Papers, 233rd ACS National Meeting, Chicago, IL, United States, March 25-29, 2007 (2007), PETR-049.

(b) P. Korovchenko, V. V. Guliants, "On cooperation of the Mo-V-Te-Nb-O M1 and M2 phases in propane ammoxidation to acrylonitrile", Abstracts of Papers, 233rd ACS National Meeting, Chicago, IL, United States, March 25-29, 2007 (2007), PETR-050.

P. Korovchenko, N. R. Shiju, A. K. Dozier, U. M. Graham, M. O. Guerrero-Perez, V. V. Guliants, "M1 to M2 Phase Transformation and Phase Cooperation in Bulk Mixed Metal Mo-V-M-O (M=Te, Nb) Catalysts for Selective Ammoxidation of Propane", *Topics in Catalysis* 50 (2008) 43-51.

K. Muthukumar, J. Yu, Y. Xu, and V. V. Guliants, "Propane Ammoxidation Over the Mo-V-Nb-Te-O M1 Phase: Reactivity of Surface Cations in Hydrogen Abstraction Steps", *Topics Catal.* 54 (2011) 605-613.

W. D. Pyrz, D. A. Blom, N. R. Shiju, V. V. Guliants, "Using Aberration-Corrected STEM

Imaging to Explore Chemical and Structural Variations in the M1 Phase of the MoVNbTeO Oxidation Catalyst”, *Journal of Physical Chemistry C*, 112(27), 10043-10049, 2008.

(a) N. R. Shiju, D. R. Mullins, S. H. Overbury, V. V. Guliants, “Selective ammoxidation of propane over Mo-V-O based mixed oxide catalysts”, Preprints - American Chemical Society, Division of Petroleum Chemistry (2007), 52(2), 64-66.

(b) N. R. Shiju, R. R. Kale, S. S. Iyer, V. V. Guliants, “¹³C isotope labeling study of propane ammoxidation over M1 phase Mo-V-Te-Nb-O mixed oxide catalyst”, *Journal of Physical Chemistry C*, 111(49), 18001-18003, 2007.

(a) N. R. Shiju, A. J. Rondinone, D. R. Mullins, V. Schwartz, S. H. Overbury, and V. V. Guliants, “XANES Study of Hydrothermal Mo-V-Based Mixed Oxide M1-Phase Catalysts for the (Amm)oxidation of Propane”, *Chemistry of Materials* 20 (2008) 6611-6616.

(b) N. R. Shiju, V. V. Guliants, S. H. Overbury, A. J. Rondinone, “Toward environmentally benign oxidations: bulk mixed Mo-V-(Te-Nb)-O M1 phase catalysts for the selective ammoxidation of propane”, *ChemSusChem* 1 (2008) 519-523.

(c) N. R. Shiju, X. Liang, A. W. Weimer, C. Liang, S. Dai, V. V. Guliants, “The role of surface basal planes of layered mixed metal oxides in selective transformation of lower alkanes: Propane ammoxidation over surface *ab* planes of Mo-V-Te-Nb-O M1 phase”, *Journal of the American Chemical Society*, 130 (18), 5850-5851, 2008.

A. Trunschke, R. Schloegl, V.V. Guliants, A. Knoester, H.H. Brongersma, “Surface Analysis of the *ab*-Plane of MoVTeNbO_x Catalysts for Propane (Amm)oxidation by Low Energy Ion Scattering (LEIS)”, Abstracts of Papers, 232nd ACS National Meeting, San Francisco, CA, United States, Sept. 10-14, 2006.

J. Woo, A. Borisevich, V. V. Guliants, „Ta-Substituted M1 Phases: Partial Occupancies of Ta in Pentagonal Bipyramidal Site and Their Catalytic Behavior in Selective Propane Ammoxidation“, in preparation.

J. Yu, J. Woo, A. Borisevich, Y. Xu and V. V. Guliants, “A Combined HAADF STEM and Density Functional Theory Study of Tantalum and Niobium Locations in the Mo-V-Te-Ta(Nb)-O M1 Phases”, *Catal. Commun.* 29 (2012) 68-72.

(a) J. Yu, Y. Xu and V. V. Guliants, “Propane Ammoxidation over Mo-V-Te-Nb-O M1 Phase: Density Functional Theory Study of Propane Oxidative Dehydrogenation Steps”, *Catalysis Today* 238 (2014) 28-34.

(b) J. Yu, Y. Xu and V. V. Guliants, “Propane Ammoxidation over Mo-V-Te-Nb-O M1 Phase Investigated by DFT: Elementary Steps of Ammonia Adsorption, Activation and NH Insertion into π -Allyl Intermediate”, *Topics in Catalysis* 57 (2014) 1145-1151.