

“USES OF LOW COPPER AMALGAM ALLOYS IN DENTISTRY”

Gaurav Solanki

Jodhpur National University, Jhanwar Road, Narnadi, Jodhpur-324003, (Rajasthan) India.

Corresponding author: dr_gauravsolanki@yahoo.com

This article is available online at www.ss-journals.com

ABSTRACT

A filling is the repair of a damaged or decayed tooth, restoring it back to its normal shape, appearance and function. Amalgam Restoration is an example of the material giving its name to the process. Amalgam fillings are made up of mercury, powdered silver and tin. They are mixed and packed into cavities in teeth where it hardens slowly and replaces the missing tooth substance. This article throws light on low copper alloys of dental amalgam, its advantages, disadvantages and contraindications. A review of some patents on amalgam is also provided that summarizes the recent technical advancements taken place in this area.

KEY WORDS: Amalgam, low copper, uses, advantages, patents

1. INTRODUCTION

A dental restoration is also called a filling. It is the repair of a damaged or decayed tooth, restoring it back to its normal shape, appearance and function. The name of the material that is used to repair a tooth is often the name given to the repair process. "Amalgam Restoration" is an example of the material giving its name to the process. Low copper amalgams are also known as "traditional" or "conventional" and have been used for many decades (even at present) and contain less than 6 % copper^{1,2}.

Dental amalgam is a combination of mercury with other metals and has been used for over 150 years for the treatment of tooth cavities because it is very strong and durable. It is also soft to adapt to the size and shape of the tooth cavity, yet hardens sufficiently fast to make it practical. It is still considered a material of choice for some fillings in the back teeth, the use of amalgams has been decreasing in recent years, because it is not tooth-colored and does not adhere to the surface of the tooth. Alternative tooth-colored filling materials have become increasingly popular. Not only do these materials look better, but they require the dentist to remove less tooth material and they do not contain mercury also. Amalgam fillings (silver fillings) are made up of mercury, powdered silver and tin. They are mixed and packed into cavities in teeth. It hardens slowly, and replaces the missing tooth

substance. Amalgam fillings are held in place by the shape of the prepared cavity³.

The cavity has to have an undercut to prevent the filling from falling out. The amalgam is then slotted into the cavity. It is still commonly used, despite an ongoing debate about mercury toxicity^{4,5}.

2. CLASSIFICATION OF AMALGAM ALLOYS

2.1 According to content^{6,7}

- **Silver Amalgam:** Silver more than 65%.
- **Copper Amalgam:** 70% Hg and 30% Cu.
- **Preamalgamated alloys:** Contain less than 3% of Hg.
- **Noble metal amalgam alloys:** Contain Au and/or Pd.

2.2 According to presence or absence of Zinc^{8,9}

- **Zinc-containing alloys:** More than 0.01% Zn.
- **Zinc-free alloys:** Less than 0.01% Zn.

1.3. According to Copper content¹⁰

- Low Copper alloys (2-4% Cu)
- High copper alloys (13-30% Cu)
 - Admixed alloy (1/3rd Low Cu + 2/3rd Ag-Cu eutectic)
 - Unicompositional or Single compositional alloy

2.4 According to number of metals in the alloy¹¹

- **Binary alloy:** Ag; Sn
- **Ternary alloy:** Ag; Sn; Cu
- **Quaternary alloys:** Ag; Sn; Cu; In.

2.5 According to the shape of alloy particles¹²

- **Spherical** (Smooth shaped spheres)
- **Spheroidal** (Irregular shaped spheres)
- **Lathe-cut** (Irregular shavings or filings). It is of three types: Micro-cut, Fine-cut and Coarse cut.

2.6 According to development of Amalgam alloys¹³

- **1st generation amalgam alloys:** G.V.Black's formulation of 3parts Ag and 1 part Sn
- **2nd generation amalgam alloys:** Addition of 4% Cu and upto 1% Zn
- **3rd generation amalgam alloys:** Admixed alloys.
- **4th generation amalgam alloys:** Ternary alloys - Addition of Cu to Ag and Sn to form Ag₂CuSn.
- **5th generation amalgam alloys:** Quaternary alloys - Ag, Sn, Cu, and Indium.
- **6th generation amalgam alloys:** Ag-Cu-Pd eutectic alloy (62%, 28%, and 10% respectively) is added in a ratio of 1:2 to low Cu alloy.

3.PHASES OF DENTAL AMALGAM^{14, 15, 16}

- Gamma: AgSn
- Gamma 1: AgHg
- Gamma 2: SnHg
- Epsilon: CuSn
- Eta: CuSn
- Beta: AgSn
- Beta 1: AgHg
- Beta (Galloy): GaCu + Sn

4.COMPONENTS

4.1 Silver: Increases strength, expansion and reactivity. Decreases creep¹⁷.

Corrosion products are AgCl and AgS.

4.2 Tin: Increases reactivity and corrosion. Decreases strength and hardness.

Corrosion products are SnO, SnCl, and SnS¹⁸.

4.3 Copper: Increases strength, expansion and hardness. Decreases creep.

Corrosion products are CuO and CuS¹⁹.

4.4 Zinc: Increases plasticity, strength and the Hg: alloy ratio.

Decreases creep. Causes secondary expansion. Corrosion products are ZnCl and ZnO²⁰.

4.5. Mercury: Wets the alloy particles. Decreases strength if in excess amounts.


Implicated in toxic and allergic reactions²¹.

5.COMPOSITION OF LOW COPPER ALLOYS²²

- Silver: 65% min.
- Tin: 29% max.
- Copper: 6% max.
- Mercury: 3% max.
- Zinc: 2% max.

6.SETTING REACTION OF LOW COPPER ALLOYS²³

This is a process by which liquid Hg reacts with dental amalgam alloy particles to produce a matrix of intermetallic compounds of Hg with metals of the alloy.



7.ADVANTAGES OF DENTAL AMALGAM^{24, 25}

- Durable
- Least technique sensitive of all restorative materials
- Applicable to a broad range of clinical situations
- Newer formulations have greater long-term resistance to surface corrosion
- Good long-term clinical performance
- Ease of manipulation by dentist
- Minimal placement time compared to other materials
- Initially, corrosion products seal the tooth-restoration interface and prevent bacterial leakage.
- One appointment placement (direct material)
- Long lasting if placed under ideal conditions
- Often can be repaired
- Economical
- Relatively inexpensive.
- Easy to manipulate.
- Restoration is completed within one sitting without requiring much chair time.
- Well-condensed and triturated amalgams have good compressive strengths.
- Sealing ability improves with age by formation of corrosion products at tooth-amalgam interface.
- Relatively not technique sensitive.

8. DISADVANTAGES OF DENTAL AMALGAM^{26, 27}

- Some destruction of sound tooth tissue

- Poor esthetic qualities
- Long-term corrosion at tooth-restoration interface may result in "ditching" leading to replacement.
- Galvanic response potential exists
- Local allergic potential
- Concern about possible mercury toxicity
- Marginal breakdown
- Marginal breakdown and fracture.
- Tarnish and corrosion.
- Unnatural appearance (not aesthetic).
- Metallic taste and Galvanic shock.
- Marginal leakage.
- Discoloration of the tooth structure.
- Lack of chemical or mechanical adhesion to the tooth structure.
- Mercury toxicity.
- High rate of secondary caries.
- Thermal conductivity.
- Promotes plaque adhesion.
- Delayed expansion.

9. CAN BE USED IN^{28, 29, 30}

- In patients of all ages
- Stress bearing areas
- In small to moderate size cavities
- In patients with poor oral hygiene
- When moisture control is a problem
- In low economic status patients
- As a foundation to metal ceramic, cast metal restorations
- As a filling material for Class I and Class II cavities.
- Can be used for Class V cavities of posterior teeth.
- Sometimes can be used for cuspal restorations (with pins usually).
- As a core build-up material prior to cast restoration.
- As a retrograde filling material.
- In combination with Composite resin for cavities in posterior teeth. Resin veneer over amalgam.

10. HOW TO AVOID FAILURES OF RESTORATION^{31, 32, 33}

- complete removal of dental caries
- complete and proper base application
- proper isolation while placement of the restoration
- avoid bulk placement of material
- avoid contact with fingers or gloved hands
- keep cavity as small as possible

- avoid sharp internal line angles
- use small increments
- Restoration at bevelled areas should be polished properly

11. CONTRAINDICATIONS OF DENTAL AMALGAM^{34, 35, 36}

- A large filling is needed and the cost of other restorative materials is not a major factor in the treatment decision.
- Where esthetics are important, such as in the anterior teeth and in lingual endodontic-access (root canal) restorations of the anterior teeth,
- A large restoration is needed and the cost of other restorative materials is not a significant factor in the treatment decision.
- Patients having a history of allergy to mercury or other amalgam components.

12. MERCURY TOXICITY^{37, 38, 39, 40}

Dental amalgam fillings occasionally cause local effects in the mouth, such as allergic reactions of the gums and of the skin inside the mouth, but this happens only rarely and is normally easy to manage. Mercury toxicity may cause signs like Tremor Headache, Ataxia Irritability, Personality change Slowed nerve conduction, Loss of memory, Weight loss, Insomnia Appetite loss, Fatigue Gingivitis, Depression Psychological distress, etc. Dental workers are more exposed to mercury toxicity than the general population. People are mainly exposed to elemental mercury by breathing in its vapour, since contact with the skin or ingestion leads to very little absorption into the body. Mercury vapour is absorbed in the lungs, spreads to the entire body and is then slowly excreted. Breathing in extremely high concentrations of mercury may produce bronchitis and pneumonia and affect the central system, for instance leading to muscle tremors. Long-term exposure to high levels may affect the kidneys and the inside of the mouth and gums. However, the amount released by dental amalgams is much lower than the limits allowed for exposure at work.

13. SOME PATENTS ON AMALGAM RESTORATIONS

13.1 Amalgamatable dental alloy powder having an effect of reducing initial mercury vapor release rate: It provides an

amalgamatable dental alloy powder for making an amalgam having a low initial mercury vapor release rate having a composition comprising 50-80 wt % Ag; 10-30 wt % Cu, and 10-35 wt % Sn, and optionally less than 7 wt % of Pd, which is prepared by subjecting a single-alloy powder having a particle size ranging from 1 to 55 microns with a majority thereof having a particle size less than 20 microns to a heat treatment, or separately subjecting a Ag--Cu--Sn powder having a particle size ranging from 1 to 70 microns with a majority thereof having a particle size less than 30 microns and a Ag--Cu--Pd powder having a particle size ranging from 1 to 100 microns with a majority thereof having a particle size less than 45 microns to heat treatments, and subjecting the heat treated powders to a pickling treatment⁴¹.

13.2 Anti-tarnish silver alloy: An anti-tarnish silver alloy is provided including at least about 85% silver, with the balance including zinc, copper, indium, and tin. Also provided are articles made from the alloy and methods of making the articles⁴².

○ **Dental amalgam alloy:** The present invention relates to low in silver particulate dental amalgam alloys comprising by weight from about 46 to 48% silver, about 23 to 33% tin, about 20 to 28% copper and about 0.5 to 5% indium. The dental amalgam alloys of the present invention have been found to be particularly efficacious when incorporated in blends with high silver particulate dental amalgam alloys, said high silver alloys being used in amounts between about 30% and 70% of the total alloy blend⁴³.

○ **Method For Bonding Amalgam To Dental Surfaces:** A method for adhering amalgam to a dental surface comprising the steps of a) etching the dental surface with acid, b) applying a treatment composition comprising an aromatic sulfinic salt to the etched dental surface, c) applying a priming solution containing a film-former to the treated dental surface, d) applying a chemically curable dental adhesive to the primed dental surface, and e) applying amalgam to the adhesive-coated dental surface. The chemically curable adhesive comprises an oxidizing agent and a reducing agent. The oxidizing agent is present in an amount sufficient to interact with said aromatic sulfinic salt to achieve higher adhesion to the dental surface than a like

method not comprising an aromatic sulfinic salt in the treatment composition⁴⁴.

13.5. Silver-tin-copper-palladium alloy and amalgam thereof : In this, the inventors Asgar k and steven H tells us about a silver-tin-copper-palladium alloy which contains from 30 to 70% silver, 15 to 37% tin, at least 13% copper and from 0.05 to 0.95% palladium; and an amalgam thereof. These all increases the working capacity of the amalgam and also increases its strength⁴⁵.

CONCLUSION

Dental amalgam not only corrects the damaged tooth but also restores the esthetics, phonetics and function of the tooth. Proper treatment should be done to avoid any complications and to make tooth appear more natural. Every treatment should be done according to the particular patient's condition and work should be done in such a way that most portion of natural tooth is protected from damage. Hope this review will be helpful in providing some useful information related to dental amalgam to dental students.

REFERENCES

1. <http://www.medicalscience.com/>
2. J.R. Davis, ed., Handbook of Materials for Medical Devices. ASM International, 2003; p 195-7.
3. Ring ME. Dentistry, an illustrated history. New York: Abrams, 1985.
4. Anderson MH, McCoy RB. Dental amalgam: The state of the art and science. 3rd Ed. Philadelphia: Saunders, 1993.
5. <http://www.amalgam.com/>
6. Greener EH. Amalgam--yesterday, today, and tomorrow. *Oper Dent* 1979; 4 (1): 24-35.
7. Ferracane, Jack L. Materials in Dentistry: Principles and Applications. Lippincott Williams & Wilkins, 2001; pp. 3.
8. Hardy J. Mercury Free Amalgam. Gabriel Rose Press, Inc; 1996.
9. Westcott A. Report to the Onondongia Medical Society on metal paste (amalgam). *Am J Dent Sci* IV, 1st Ser, 1844: 175-201.
10. Harris, Chapin Aaron The Principles and Practice of Dental Surgery. Lindsay & Blakiston, 1845; pp. 270-1.
11. Molin C Amalgam--fact and fiction. *J Dent Res*, Feb 1992; 100 (1): 66-73.

12. American Society of Dental Surgeons. *American Journal of Dental Science*. Harvard University. p. 170.
13. Maynard H.K. Review of dentistry: Questions and Answers, 1979.
14. Bremner M. The Story of Dentistry from the Dawn of Civilization to the Present Dental Items of Interest Pub. Co, 1939; p 86-87
15. Berry TG, Summit JD, Chung AKH, Osborne JW. Amalgam and the new millennium. 1998; 129: 1547-1556.
16. Eames, WB. Preparation and condensation of amalgam with low mercury alloy ratio. 1959; 58 (4): 78-83.
17. <http://www.lowcopperalloys.com>.
18. Innes DBK, Youdelis WV. Dispersion strengthened amalgam. *J Can Dent Assoc*, 1963; 29: 587-93.
19. Leinfelder KF. Do restorations made of amalgam outlast those made of resin-based composites. 2000; 131:1186-87.
20. Asgar K. Behavior of copper dispersion allows. *J Dent Res*, 1971; 50: 56.
21. Christensen GJ. Longevity of posterior tooth dental restorations. 2005; 136: 201-203.
22. Soncini JA, Maserejian NN. The longevity of amalgam versus compomer/composites restorations in posterior primary and permanent teeth. 2007; 138: 763-72.
23. Bernardo M, Martin MD, Lerouz BG. Survival and reasons for failure of amalgam versus resin-based composites posterior restorations placed in a randomized clinical trial. 2007; 138: 775-83.
24. Christensen, GJ. Longevity of posterior tooth dental restorations. 2005; 136: 201-203.
25. Estefan D, Agosta C. Eliminating microleakage from the composite resin system. *Gen Dent*, 2003; 516: 506-09.
26. Burgess JO, Walker R, Davidson JM. Posterior resin-based composite: review of the literature. *Pediatr Dent*, 2002; 24 (5): 465-79.
27. Forss H, Widstrom E. The post-amalgam era: a selection of materials and their longevity in the primary and young permanent dentition. Others express concern regarding the Children's Amalgam Trial's elevated serum and urine mercury content in the children with the amalgams. *Int J Paediatr Dent*, 2003; 13(3): 158-164.
28. http://www.ptc.state.id.us/Forms_Publications/Health/Curriculum/DentalPolishingAmalgamRestorations.pdf.
29. Qvist V, Thylstrup A. Restorative treatment patterns and longevity of amalgam restorations in Denmark. *Acta Odontol Scand* 1986; 44(6): 343-349.
30. http://www.thenhf.com/articles/articles_701/articles_701.htm.
31. Life Sciences Research Office. Review and analysis of the health effects of dental amalgam Toxicological Reviews, 2005.
32. Fuks AB. The use of amalgam in pediatric patients. *Pediatr Dent* 2002; 24 (5): 448-55.
33. Newman SM. Amalgam alternatives: what can compete? 1991; 122 (8): 67-71.
34. <http://jama.ama-assn.org/cgi/content/full/295/15/1784>.
35. <http://jama.ama-assn.org/cgi/content/full/295/15/1775>
36. http://www.dentaleconomics.com/articles/article_display.html?id=284909.
37. ADA Council on Scientific Affairs. Direct and indirect restorative materials. 2003; 134 (4): 463-472.
38. Clifton JC. Mercury exposure and public health. *Pediatr Clin North*, 2007; 54 (2): 237-69.
39. <http://www.dentalamalgam.com>.
40. <http://jama.ama-assn.org/cgi/content/full/295/15/1835>
41. Lin, Chern J in-ventors. Amalgamatable dental alloy powder having an effect of reducing initial mercury vapor release rate. US patent 6,458,180; 2002 Oct 1.
42. Croce, Scott M in-ventors. Anti-tarnish silver alloy. US patent 6,841,012; 2005 Jan 11.
43. in-ventor. Dental amalgam alloy. US patent 4,427,628; 1984 Jan 24.
44. Ario P, Aasen S in-ventors. Method for bonding amalgam to dental surfaces. Minnesota Mining and Manufacturing Company. US patent 5,595,487; 1997..
45. Asgar k, steven H in-ventors. Silver-tin-copper-palladium alloy and amalgam thereof. Special Metals Corporation. US patent 4,374,085; 1983 Feb 15.