

Original Article

The color masking ability of a zirconia ceramic on the substrates with different values

Farhad Tabatabaian^{1*} • Mahdiye Javadi Sharif² • Farhood Massoumi³ • Mahshid Namdari⁴

¹Assistant Professor, Department of Prosthodontics, School of Dentistry, Shahid Beheshti University of Medical Sciences, Tehran, Iran

²Postgraduate Student, School of Dentistry, Shahid Beheshti University of Medical Sciences, Tehran, Iran

³Assistant Professor, Department of Prosthodontics, School of Dentistry, Shahid Beheshti University of Medical Sciences, Tehran, Iran

⁴Assistant Professor of Biostatistics, Department of Community Oral Health, School of Dentistry, Shahid Beheshti University of Medical Sciences, Tehran, Iran

*Corresponding Author; E-mail: f_tabatabaian@yahoo.com

Received: 31 March 2016; Accepted: 1 March 2017

J Dent Res Dent Clin Dent Prospect 2017; 11(1): 7-13 | doi: 10.15171/joddd.2017.002

This article is available from: <http://dentistry.tbzmed.ac.ir/joddd>

© 2017 Tabatabaian et al. This is an Open Access article published and distributed by Tabriz University of Medical Sciences under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Abstract

Background. The color masking ability of a restoration plays a significant role in covering a discolored substructure; however, this optical property of zirconia ceramics has not been clearly determined yet. The aim of this in vitro study was to evaluate the color masking ability of a zirconia ceramic on substrates with different values.

Methods. Ten zirconia disk specimens, 0.5 mm in thickness and 10 mm in diameter, were fabricated by a CAD/CAM system. Four substrates with different values were prepared, including: white (control), light grey, dark grey, and black. The disk specimens were placed over the substrates for spectrophotometric measurements. A spectrophotometer measured the L^* , a^* , and b^* color attributes of the specimens. Additionally, ΔE values were calculated to determine the color differences between each group and the control, and were then compared with the perceptual threshold of $\Delta E=2.6$. Repeated-measures ANOVA, Bonferroni, and one-sample t-test were used to analyze data. All the tests were carried out at 0.05 level of significance.

Results. The means and standard deviations of ΔE values for the three groups of light grey, dark grey and black were 9.94 ± 2.11 , 10.40 ± 2.09 , and 13.34 ± 1.77 units, respectively. Significant differences were detected between the groups in the ΔE values ($P<0.0001$). The ΔE values in all the groups were more than the predetermined perceptual threshold ($\Delta E>2.6$) ($P<0.0001$).

Conclusion. Within the limitations of this study, it was concluded that the tested zirconia ceramic did not exhibit sufficient color masking ability to hide the grey and black substrates.

Key words: Color, spectrophotometry, visual perception, Y-TZP ceramic.

Introduction

Metal ceramic restorations have shown long-term success due to good mechanical proper-

ties.^{1,2} However, achieving a natural appearance is more challenging with a metal-ceramic restoration than an all-ceramic restoration due to the fact that metal copings prevent light transmission.^{3,4} This has

led to an increase in the use of non-metallic restorations such as zirconia-based restorations.⁵ Zirconia-crowns combine the benefits of metal restorations, such as minimally invasive tooth preparation and simple cementation, with those of all-ceramic crowns, such as low thermal conductivity and adequate translucency.^{6,7} However, the high translucency of a ceramic is not necessarily a benefit, especially in cases with discolored teeth, metallic core materials, colored dental substrates,⁸ and even titanium abutments.⁹ In these cases a ceramic with color masking ability of its background should be reasonably applied to obtain acceptable esthetic outcomes. The masking ability has been defined as the ability to hide a colored background.⁵

A method to evaluate the masking ability of restorative materials is to measure a ΔE color difference in CIELab color system. In this color system the color attributes of L^* , a^* , and b^* define lightness, red/green value, and yellow/blue value, respectively, which can be measured via spectrophotometry. The ΔE is calculated to determine color differences using this formula:

$$\Delta E_{ab}^* = \left[(L_2^* - L_1^*)^2 + (a_2^* - a_1^*)^2 + (b_2^* - b_1^*)^2 \right]^{1/2}$$

which is the most commonly used formula for ΔE .⁵ This formula can detect even a small amount of color difference between natural dentition and restorations.¹⁰ An opaque material with ideal masking ability has a ΔE color difference close to zero when being placed over a black and white substrate.⁸ In this case the color of the material is not affected by the substrate's color. As spectrophotometers and colorimeters can recognize even a small amount of color change which cannot be detected by human eyes, limits have been defined for the perceptual threshold and the acceptable clinical threshold based on the ΔE value.⁵ It has been considered that the acceptable clinical threshold is more than the perceptual threshold.¹¹ If the ΔE color change is more than the threshold, a color match will be rejected. The perceptual threshold range is 1–5.5 of ΔE in the literature.¹²⁻¹⁴

Several studies have evaluated the optical properties of different ceramic materials.¹⁵⁻¹⁸ Some investigations have assessed various factors affecting the final color of zirconia restorations, including substrates,¹⁹⁻²² cements,^{21,23} ceramic veneers and their thicknesses,²⁴⁻²⁶ glazing process,²⁴ and laboratory techniques.²⁷

Suputtamongkol et al¹⁹ concluded that the color of a substructure affected the color of posterior zirconia-based restorations on a metal post and core or a

prefabricated post and a composite resin core, ranging from 1.2 to 3.1 of ΔE . Choi & Razzoog²⁰ evaluated the masking ability of zirconia ceramics with and without porcelain veneer and concluded that the unveneered zirconia ceramic was rather capable of masking the different tested substrates. Oh & Kim²² concluded that abutment shade, ceramic thickness and coping type affected the color resulting from zirconia restorations. Pecho et al²⁸ concluded that clinicians should pay attention to the optical property differences between zirconia ceramics and human dentin to achieve optimal esthetics in restorative dentistry. Kurtulmus-Yilmaz and Ulusoy²⁹ showed that zirconia ceramics were less translucent than lithium disilicate glass ceramic, and had partial translucency with some translucency differences among the zirconia systems. Tuncel et al³⁰ reported that the translucency of zirconia was influenced by the coloring procedure and the grain size. The masking ability of a zirconia ceramic is related to its color coverage over underlying structures, including cement and dental substrates. Masking a dental substrate with cements may not be feasible because different shades do not exist for all the cements; in addition, availability of different cement shades allows minor esthetic corrections.²¹ Therefore the color masking ability of a zirconia ceramic on different substrates may be essential to achieve proper clinical results. The L^* attribute, which is related to the value or lightness of a ceramic or a substrate, is the most effective factor in the resultant color.²⁰ Therefore, the aim of this in vitro study was to evaluate the color masking ability of a zirconia ceramic on the substrates with different values. The null hypothesis was that the examined zirconia ceramic would show sufficient color masking ability to hide the tested substrates.

Methods

A sample of maximum 10 is needed in a repeated-measure design with 3 replicates and the effect size of 0.81 (variance within groups=4 and variance explained by the effect=2.6), with $\alpha=0.05$ and $\beta=0.1$. A G power of 3.1.3 was implemented for sample size calculation.

Therefore, 10 zirconia disk specimens were fabricated. The disk specimens were placed onto four substrates with different values, including: white (W), light grey (LG), dark grey (DG) and black (B). Spectrophotometric measurements were performed on the specimens.

A CAD/CAM system (CORITEC 250i, imes-icore GmbH, Eiterfeld, Germany) milled zirconia blocks (Luminesse High Strength 98mm Discs #5113, Tal-

ladium, Valencia, CA, USA) to prepare zirconia disks. The disks were 0.5 mm in thickness and 10 mm in diameter.²² All the zirconia disks were sintered at 1500°C for a 12-hour process in a sintering furnace (iSINT HT, Imes-Core GmbH, Eiterfeld, Germany). A micrometer (293 MDC-MX Lite, Mitutoyo Corporation, Tokyo, Japan) with an accuracy of 0.002 mm was employed to measure the thicknesses of the disks. The disks were adjusted to a thickness of 0.5 ± 0.01 mm. An adjustment and polishing kit (BruxZir, Glidewell Direct, Irvine, CA, USA) was used to reduce the thicknesses according to the above-mentioned acceptable range. In case of lack of the acceptable thickness, the disk was excluded from the study. The zirconia disks were polished, cleaned in an ultrasonic bath (Elmasonic S-30, Dentec, North Shore, Australia) containing 98% ethanol for 15 minutes and finally dried.

Four cylindrical substrates with different values, including white (W), light grey (LG), dark grey (DG) and black (B), were prepared. The substrates were 10 mm in diameter and 10 mm in height.²² White and black Teflon materials (PTFE, Omnia Plastica SPA, Busto Arsizio, Italy) were milled to fabricate the white and black substrates according to the above-mentioned dimensions. In order to fabricate grey substrates, a putty silicone impression (Speedex, Coltene, Altstätten, Switzerland) was taken from the black substrate to prepare a mold. Half a gram and one gram of carbon graphite were separately added to the liquid of an auto-polymerized acrylic resin (Alike, GC Corporation, Tokyo, Japan), to make the light and dark grey substrates, respectively.²⁰ The liquid and powder of the acrylic resin were mixed and applied to the mold. After 5 minutes the polymerization of the acrylic resin was completed. The grey acrylic substrates were polished with 800-grit silicon carbide abrasive papers for 10 minutes. All the substrates were cleaned in the same ultrasonic bath containing 98% ethanol for 15 minutes (Figure 1). The CIELab values of the substrates were measured (W: $L^* = 92.1$, $a^* = -1.7$, $b^* = 0.7$; LG: $L^* = 57.6$, $a^* = -0.6$, $b^* = 4.3$; DG: $L^* = 39.8$, $a^* = -0.5$, $b^* = 2.5$; B: $L^* = 9.4$, $a^* = -0.9$, $b^* = -1.1$)




Figure 1. The tested substrates.

A spectrophotometer (Spectro Shade Micro, MHT, Verona, Italy) was employed for spectrometric measurements.³¹ A putty silicone material (Speedex, Coltene, Altstätten, Switzerland) was adapted to the mouthpiece of the spectrophotometer to match the conditions of spectrophotometry for all the specimens and to prevent external light. The specimens were located at the center of this putty mold. Before each measurement the spectrophotometer was calibrated by the white and green calibration plates, respectively. The disks were placed on the substrates with a water drop in between to prevent refraction of light.⁵ Each disk specimen was placed on each of the four substrates and the color measurements were carried out. All the color measurements were conducted at the center of the specimens marked by a pen on the monitor screen of spectrophotometer, and the color attributes of L^* , a^* , and b^* were recorded for each specimen. ΔE was calculated to determine the color differences of a disc on different substrates. To compare the three substrates of LG, DG and B with the substrate W, the ΔE values were measured in three situations, including W-LG, W-DG and W-B. The aforementioned formula was employed to calculate ΔE . The $\Delta E = 2.6$ for perceptual threshold was hypothesized in this study.^{13,14}

A normal distribution of data was confirmed in all the groups by Kolmogorov-Smirnov test ($P > 0.05$). SPSS 21 (SPSS Inc., Chicago, IL, USA) was used for the analysis of data. In order to compare the color attributes of L^* , a^* , b^* and ΔE in the four groups of W, LG, DG and B, repeated-measures ANOVA was employed. Pairwise comparisons of the groups were performed by Bonferroni test. STATA (StataCorp LP, Lake way, TX, USA) was used to compare the ΔE values with the threshold of 2.6 using one-sample t-test. All the tests were carried out at 0.05 level of significance.

Results

The means and standard deviations of the L^* values for the four groups of W, LG, DG, and B were 88.35 ± 1.46 , 78.46 ± 1.71 , 78.06 ± 1.66 , and 75.38 ± 1.35 units, respectively (Table 1) (Figure 2). Repeated-measures ANOVA detected significant differences between the groups ($P < 0.0001$). Pairwise comparisons of the four groups revealed significant differences between all the groups ($P < 0.0001$), except between LG and DG ($P = 0.652$).

The means and standard deviations of a^* values for the four groups of W, LG, DG and B were 0.40 ± 0.42 , -0.32 ± 0.48 , -0.28 ± 0.52 , and 0.36 ± 0.45 units, respectively (Table 1) (Figure 3).

Table 1. Measures of the color attributes of specimens in the four groups

Substrate	Color attributes	Mean	Standard deviation	Minimum	Maximum	%95 Confidence Interval
White (W)	L*	88.35	1.46	85.40	90.50	(87.30,89.39)
	a*	-0.40	0.42	-1.10	0.30	(-0.69,-0.10)
	b*	3.38	0.36	2.90	4.10	(3.11,3.64)
Black (B)	L*	75.38	1.35	73.20	77.10	(74.41,76.34)
	a*	-0.36	0.45	-0.80	0.80	(-0.68,-0.03)
	b*	0.40	0.49	-0.30	1.40	(0.05,0.75)
Light Grey (LG)	ΔE	13.34	1.77	9.64	15.94	(12.06,14.60)
	L*	78.46	1.71	76.00	80.20	(77.24,79.68)
	a*	-0.32	0.48	-0.80	0.90	(-0.66,0.027)
Dark Grey (DG)	b*	2.61	0.41	2.20	3.40	(2.31,2.90)
	ΔE	9.94	2.11	5.88	12.80	(8.43,11.45)
	L*	78.06	1.66	75.20	79.60	(76.87,79.24)
Dark Grey (DG)	a*	-0.28	0.52	-0.80	1.00	(-0.65,0.09)
	b*	2.06	0.44	1.50	2.70	(1.74,2.37)
	ΔE	10.40	2.09	5.98	13.86	(8.89,11.89)




Figure 2. The means and standard deviations of the L* values in the four groups.

Repeated-measures ANOVA detected no significant differences between the groups (P=1).

The means and standard deviations of b* values for the four groups of W, LG, DG and B were 3.38±0.36, 2.61±0.41, 2.06±0.44, and 0.40±0.49 units, respectively (Table 1) (Figure 4). Repeated-measures ANOVA detected significant differences between the groups (P<0.0001). Pair wise comparisons of the four groups showed significant differences




Figure 3. The means and standard deviations of the a* values in the four groups.

es between all the groups (P<0.0001), except between LG and W (P=0.09).

The means and standard deviations of the ΔE_{W-LG}, ΔE_{W-DG}, and ΔE_{W-B} values were 9.94±2.11, 10.40±2.09, and 13.34±1.77units, respectively (Table 1) (Figure 5). Repeated-measures ANOVA showed significant differences between the groups (P<0.0001). Pair wise comparisons of the groups revealed significant differences between all the groups (P<0.0001), except between LG and DG (P=0.469). In order to compare the means of the ΔE_{W-LG}, ΔE_{W-DG}, and ΔE_{W-B} values with the threshold of ΔE=2.6, one-sample t-test (one-sided) was employed. The null hypothesis of $\mu \geq 2.6$ was rejected for ΔE_{W-LG}, ΔE_{W-DG} and ΔE_{W-B} (P<0.0001).

Discussion

Based on the results of this study, the tested zirconia ceramic upon the tested substrates demonstrated perceptible color differences and did not show sufficient color masking ability to hide the grey and black substrates. Hence, the null hypothesis of the study was refuted.

The L* values decreased in all the groups com-




Figure 4. The means and standard deviations of the b* values in the four groups.




Figure 5. The means and standard deviations of the ΔE values.

pared with the W. This decrease was the highest in the B, while there was no significant difference between the LG and the DG in this respect. As the L^* value expresses the lightness of an object, a black substrate reasonably causes the highest decrease in this color attribute. This is due to optical properties of zirconia ceramic which allows for light transmission.

The a^* values increased in all the groups compared with the W, though this increase was not statistically significant. This shows that grey and black substrates do not affect the a^* color attribute. As the a^* color attribute defines red/green value, the result seems rational.

The b^* values decreased in all the groups compared with the W. The decrease of the b^* value was the highest in the B. This may be due to the natural b^* value of a black substrate and its effect on the zirconia ceramic.

All the ΔE values (ΔE_{W-LG} , ΔE_{W-DG} and ΔE_{W-B}) were more than the threshold of $\Delta E=2.6$. This demonstrated that the color changes induced by the substrates were beyond the perceptual threshold. Tracing the L^* , a^* , b^* and ΔE values (Table 1) indicated that the highest amount of difference was related to the L^* attribute. Accordingly the substrate types had the highest impact on the L^* attribute. Therefore the ΔE changes had mainly been derived from this attribute (Table 1).

Suputtamongkol et al¹⁹ reported that the color of a background substructure could affect the color of zirconia-based restorations on a metal post and core or a prefabricated post and composite resin core. Moreover minor color changes of zirconia crowns were disclosed by measuring ΔE .¹⁹ Despite some differences between the above-mentioned study and the present investigation like ceramic brand, ceramic thickness, layered zirconia versus zirconia coping, thresholds and substrate types, both investigations

revealed that the zirconia ceramic was rather capable of masking its substrate.

Oh & Kim²² assessed the effects of abutment shade, ceramic thickness, and coping type on the color of zirconia-based restorations. The abutments were prepared with gold alloy, nickel-chromium alloy, and composite resins with different shades. The mean ΔE value of Lava zirconia between the A2 composite resin and gold alloy abutments was higher than those between the A2 composite resin and other abutments ($\Delta E=5.5$). It was concluded that the color of the tested zirconia ceramic was affected by its substrate. A comparable consequence was gained from the present study, though the substrates and zirconia ceramics used were not similar.

Choi & Razzoog²⁰ assessed the masking ability of a zirconia ceramic with and without porcelain veneer. The color differences induced by zirconia ceramic and porcelain veneer were compared with the substrates alone, and it was concluded that the unveneered zirconia ceramic was rather capable to mask the different tested substrates. However, in the present study the color differences induced by the substrates were compared with a white substrate and the results revealed that the tested zirconia ceramic could not hide the substrates. In other words, Choi & Razzoog²⁰ calculated the ΔE between the substrate (as a control) and the zirconia ceramic with the substrate, while we calculated the ΔE between the zirconia ceramic with the white substrate (as a control) and the zirconia ceramic with the other substrates. The difference in the results might be attributed to the mentioned methodological approaches. It should be considered that incomplete masking ability of a ceramic on discolored background substructures might lead to unpleasant esthetic results. On the other hand, the highest color changes, reported by Choi & Razzoog,²⁰ occurred in the L^* and b^* values. Similarly the highest amount of color differences were caused by the L^* attribute in the current investigation.

Although Kurtulmus-Yilmaz and Ulusoy²⁹ showed that zirconia-based all-ceramic systems had lower translucency than lithium disilicate-based glass ceramics, this lower level of translucency of zirconia is not sufficient to hide the substrate color according to the results of this study. Tuncel et al³⁰ showed that zirconia as a framework material had smaller grain size and more translucency compared to monolithic zirconia. In addition, colored zirconia framework material exhibited similar grain size and was less translucent than non-colored zirconia framework material.³⁰ The results of the present study, which

showed the effect of substrate color on the zirconia ceramic color, were consistent with those of a study by Tuncel et al,³⁰ indicating the high translucency of non-colored zirconia framework.

Based on the results of this study, the grey and black substrates can change the color of zirconia core beyond the perceptual threshold. Thus, zirconia-based restorations may be contraindicated on the black and grey discolored teeth, or the negative effects of these discolorations might be reduced by increasing the zirconia core thickness, applying sufficient porcelain veneers, and using suitable luting agents.

Light transmission via a zirconia core structure can be predictable in zirconia-based restorations, and therefore cements and dental substrates might affect the color of these restorations.³² The present study assessed the specific effects of three substrates with different values in this respect. In addition, the zirconia core veneering materials may affect the color of zirconia-based restorations, which were not evaluated in this study. Therefore, consideration of this factor is suggested in future studies. This research had some limitations such as testing a non-colored zirconia ceramic without veneer. More investigations are suggested in this respect.

Conclusion

Within the limitations of this study it was concluded that the tested zirconia ceramic did not exhibit sufficient color masking ability to hide the grey and black substrates.

Acknowledgments

This paper has been entirely drawn up from a "M.D. Thesis" which was successfully completed by Dr. Mahdiye Javadi Sharif under the supervision of Dr. Farhad Tabatabaian.

Authors' contributions

FT contributed to the concept and design of the work. The acquisition, analysis, and interpretation of data were accomplished by FT, MJS, and MN. FT, FM and MJS drafted and revised it critically for intellectual content. All the authors read and approved the final manuscript.

Funding

This project was supported and funded by the authors.

Competing interests

The authors declare no competing interests with regards to the authorship and/or publication of this article.

Ethics approval

Not applicable.

References

1. Shi JY, Li X, Ni J, Zhu ZY. Clinical evaluation and patient satisfaction of single zirconia-based and high-noble alloy porcelain-fused-to-metal crowns in the esthetic area: A retrospective cohort study. *J Prosthodont.* 2016; 25:526-530. doi: 10.1111/jopr.12344
2. Näpänkangas R, Raustia A. Twenty-year follow-up of metal-ceramic single crowns: a retrospective study. *Int J Prosthodont.* 2008; 21:307-11.
3. Jeong ID, Bae SY, Kim DY, Kim JH, Kim WC. Translucency of zirconia-based pressable ceramics with different core and veneer thicknesses. *J Prosthet Dent.* 2016; 115:768-72. doi: 10.1016/j.prosdent.2015.11.003
4. Harada K, Raigrodski AJ, Chung KH, Flinn BD, Dogan S, Mancl LA. A comparative evaluation of the translucency of zirconias and lithium disilicate for monolithic restorations. *J Prosthet Dent.* 2016; 116:257-63. doi: 10.1016/j.prosdent.2015.11.019
5. Vichi A, Louca C, Corciolani G, Ferrari M. Color related to ceramic and zirconia restorations: a review. *Dent Mater.* 2011; 27:97-108. doi:10.1016/j.dental.2010.10.018
6. Raigrodski AJ. Contemporary materials and technologies for all-ceramic fixed partial dentures: a review of the literature. *J Prosthet Dent.* 2004; 92:557-62. doi:10.1016/j.prosdent.2004.09.015
7. Wiedhahn K, Fritzsche G, Wiedhahn C, Schenk O. Zirconia crowns - the new standard for single-visit dentistry? *Int J Comput Dent.* 2016; 19:9-26.
8. Chu FC, Chow TW, Chai J. Contrast ratios and masking ability of three types of ceramic veneers. *J Prosthet Dent.* 2007; 98:359-64.
9. Mokhtarpour H, Eftekhari Ashtiani R, Mahshid M, Tabatabaian F, Alikhasi M. Effect of screw access hole preparation on fracture load of implant-supported zirconia-based crowns: an in vitro study. *J Dent Res Dent Clin Dent Prospects.* 2016; 10:181-8. doi: 10.15171/joddd.2016.029
10. Seghi RR, Hewlett ER, Kim J. Visual and instrumental colorimetric assessments of small color differences on translucent dental porcelain. *J Dent Res.* 1989; 68:1760-4. doi:10.1177/00220345890680120801
11. Douglas RD, Steinhauer TJ, Wee AG. Intraoral determination of the tolerance of dentists for perceptibility and acceptability of shade mismatch. *J Prosthet Dent.* 2007; 97:200-8. doi:10.1016/j.prosdent.2007.02.012
12. Lindsey DT, Wee AG. Perceptibility and acceptability of CIELAB color differences in computer-simulated teeth. *J Dent.* 2007; 35:593-9. doi:10.1016/j.jdent.2007.03.006
13. Ishikawa-Nagai S, Yoshida A, Sakai M, Kristiansen J, Da Silva JD. Clinical evaluation of perceptibility of color differences between natural teeth and all-ceramic crowns. *J Dent.* 2009; 37 Suppl 1:e57-63. doi:10.1016/j.jdent.2009.04.004
14. Ghinea R, Pérez MM, Herrera LJ, Rivas MJ, Yebra A, Paravina RD. Color difference thresholds in dental ceramics. *J Dent.* 2010; 38 Suppl 2:e57-64. doi: 10.1016/j.jdent.2010.07.008
15. Fabbri G, Mancini R, Marinelli V, Ban G. Anterior discolored teeth restored with pro-cera all-ceramic restorations: a clinical evaluation of the esthetic outcome based on the thickness of the core selected. *Eur J Esthet Dent.* 2011; 6:76-86.
16. Zhang F, Heydecke G, Razzoog ME. Double-layer porcelain veneers: effect of layering on resulting veneer color. *J Prosthet Dent.* 2000; 84:425-31. doi:10.1067/mpr.2000.110255

17. Chen YM, Smales RJ, Yip KH, Sung WJ. Translucency and biaxial flexural strength of four ceramic core materials. *Dent Mater.* 2008; 24:1506-11. doi:10.1016/j.dental.2008.03.010
18. Lee YK, Cha HS, Ahn JS. Layered color of all-ceramic core and veneer ceramics. *J Prosthet Dent.* 2007; 97:279-86. doi:10.1016/j.prosdent.2007.03.010
19. Suputtamongkol K, Tulapornchai C, Mamani J, Kamchatphai W, Thongpun N. Effect of the shades of background substructures on the overall color of zirconia-based all-ceramic crowns. *J Adv Prosthodont.* 2013; 5:319-25. doi:10.4047/jap.2013.5.3.319
20. Choi YJ, Razzoog ME. Masking ability of zirconia with and without veneering porcelain. *J Prosthodont.* 2013; 22:98-104. doi:10.1111/j.1532-849X.2012.00915.x
21. Vichi A, Ferrari M, Davidson CL. Influence of ceramic and cement thickness on the masking of various types of opaque posts. *J Prosthet Dent.* 2000; 83: 412-7. doi:10.1016/S0022-3913(00)70035-7
22. Oh SH, Kim SG. Effect of abutment shade, ceramic thickness, and coping type on the final shade of zirconia all-ceramic restorations: in vitro study of color masking ability. *J Adv Prosthodont.* 2015; 7: 368-74. doi:10.4047/jap.2015.7.5.368
23. Tabatabaian F, Habib Khodaei M, Namdari M, Mahshid M. Effect of cement type on the color attributes of a zirconia ceramic. *J Adv Prosthodont.* 2016; 8:449-56. doi: 10.4047/jap.2016.8.6.449
24. Sinmazisik G, Demirbas B, Tarcin B. Influence of dentin and core porcelain thickness on the color of fully sintered zirconia ceramic restorations. *J Prosthet Dent.* 2014; 111:142-9. doi:10.1016/j.prosdent.2013.09.016
25. Son HJ, Kim WC, Jun SH, Kim YS, Ju SW, Ahn JS. Influence of dentin porcelain thickness on layered all-ceramic restoration color. *J Dent.* 2010; 38Suppl 2:e71-7. doi:10.1016/j.jdent.2010.08.007
26. Barão VA, Gennari-Filho H, Goiato MC, dos Santos DM, Pesqueira AA. Factors to achieve aesthetics in all-ceramic restorations. *J Craniofac Surg.* 2010; 21:2007-12.
27. Bachhav VC, Aras MA. The effect of ceramic thickness and number of firings on the color of a zirconium oxide based all ceramic system fabricated using CAD/CAM technology. *J Adv Prosthodont.* 2011; 3:57-62. doi:10.4047/jap.2011.3.2.57.
28. Pecho OE, Ghinea R, Ionescu AM, Cardona JC, Della Bona A, Pérez Mdel M. Optical behavior of dental zirconia and dentin analyzed by Kubelka-Munk theory. *Dent Mater.* 2015;31:60-7. doi: 10.1016/j.dental.2014.11.012
29. Kurtulmus-Yilmaz S, Ulusoy M. Comparison of the translucency of shaded zirconia all-ceramic systems. *J Adv Prosthodont.* 2014; 6:415-22. doi: 10.4047/jap.2014.6.5.415
30. Tuncel İ, Turp I, Üşümez A. Evaluation of translucency of monolithic zirconia and framework zirconia materials. *J Adv Prosthodont.* 2016; 8:181-6. doi: 10.4047/jap.2016.8.3.181
31. Kim A, Campbell SD, Viana MA, Knoernschild KL. Abutment material effect on peri-implant soft tissue color and perceived esthetics. *J Prosthodont.* 2015 Sep 23. doi: 10.1111/jopr.12360. [Epub ahead of print].
32. Tabatabaian F, Masoomi F, Namdari M, Mahshid M. Effect of three different core materials on masking ability of a zirconia ceramic. *J Dent.* (Tehran) 2016; 13:340-8.