

Tissue Engineering of Articular Cartilage: A Mini-Review

¹Radoslav Zamborsky, ²Jana Rusnakova and ³Andreas Nicodemou

¹Department of Traumatology, Faculty of Medicine, Slovak Medical University, Bratislava, Slovakia

²Institute of Histology and Embryology,

³Institute of Medical Biology, Genetics and Clinical Genetics,
Faculty of Medicine, Comenius University, Bratislava, Slovakia

Article history

Received: 23-07-2014

Revised: 01-10-2014

Accepted: 10-10-2014

Corresponding Author:

Radoslav Zamborsky,
Department of Traumatology,
Faculty of Medicine, Slovak
Medical University, Bratislava,
Slovakia

Email: radozamborsky@gmail.com

Abstract: Damage of articular cartilage due to congenital anomaly, injury or pathological process may lead in decreasing of life quality of affected patients. In many cases, conventional therapeutical approaches may not bring expected results. Tissue engineering by the combination of material technology and cell-based therapy may represent hope for these patients. The main goal of this review article is to summarize current knowledge about biological characteristics of somatic stem cells, chondro-inductive substances and materials in respect to regeneration of articular cartilage.

Keywords: Articular Cartilage, Somatic Stem Cells, Growth Factors, Biomaterials, Regenerative Medicine

Introduction

Recently, despite the advances in medicine, damaged articular cartilage as a consequence of inborn defects, injury or pathological process still represent serious medical problem. It may lead in gradual immobilization and decreasing of life quality in affected individuals. Mentioned is mainly contributed to low self-healing potential of mature articular cartilage due to intrinsic properties. Articular cartilage is aneural and avascular tissue with low density of cells. Moreover, high level of protease inhibitors inhibit tissue repair (Zhang *et al.*, 2009a).

Small defects are usually regenerated by the migration of chondrocytes to cartilage lesions. They synthesize new ECM components of cartilage. In case of large scale and deep defects, this process is complicated by low cell density, by low mitotic potential of chondrocytes as well as by high level of protease inhibitors. It results in formation of the biomechanically insufficient fibrillar cartilage (Mobasheri *et al.*, 2009). Unfortunately, current treatment techniques for cartilage reparation are insufficient and it is not possible to obtain expected results.

The tissue engineering offers new concept to solve this serious problem. The first cell-based therapy for articular cartilage treatment was introduced by Brittberg *et al.* (1994) who injected autologous chondrocytes into the lesion covered by periosteal flap in 23 people with deep cartilage defects in the knee.

This lead into formation of the hyaline-like cartilage. However, this approach showed some disadvantages, including reacquisition of chondrocyte phenotype during *in vitro* expansion and non-uniform distribution of cells due to gravitational force.

More recently, it was shown that somatic stem cell undergo the process of chondrogenic differentiation under proper conditions, both *in vitro* and *in vivo*. They should be obtained from different tissue sources and easily expended *in vitro* (Danisovic *et al.*, 2011). Therefore, the great hope is addressed on their utilization in relation to repairing damaged articular cartilage.

The main goal of the present article is to review the current status and advances of the cartilage tissue engineering with respect to their potential application in orthopaedic surgery and traumatology.

Histology of Articular Cartilage

Articular cartilage is a type of hyaline cartilage (Fig. 1) and belongs to connective tissues. It is composed of abundant Extracellular Matrix (ECM) which contains predominantly collagen type II, chondroitine sulphate and proteoglycans. Articular cartilage is characterized by zonality. Different organization of collagen fibers and cross-linking to other components influence its biomechanical properties (Sophia Fox *et al.*, 2009).

The ECM is very poor for cells-chondrocytes. On the periphery they have elliptic morphology. Chondrocytes

localized inside ECM are of round morphology with average size of 10-30 μm . They formed isogenous cell groups in cavities, called cartilage *lacunae* (Mescher, 2013). They are responsible for production of ECM components. Moreover, they are involved in the maintaining and remodelling of the articular cartilage (Cucchiari *et al.*, 2012; Danisovic *et al.*, 2013).

Cell Sources for Articular Cartilage Tissue Engineering

Chondrocytes are the cells of first choice for cartilage tissue engineering, because they occurs within articular cartilage *in vivo*. They have been used in all current Autologous Chondrocyte Implantation (ACI) procedures. Chondrocytes have been isolated from different sources, including low load-bearing area of knee cartilage and auricular cartilage (Beris *et al.*, 2012; Malicev *et al.*, 2009). However, this technique has some limits due to low mitotic potential and senescence of chondrocytes. Moreover, they undergo dedifferentiation process when cultured *in vitro*, gradually changing their morphology to a fibroblast-like shape and the production of type II collagen is replaced by the production of collagen type I. This problem may be overlapped by adding specific growth factors.

Somatic Stem Cells (SSCs) because of their biological characteristics represent another promising tool for cartilage tissue engineering. SSCs are undifferentiated cells with unique potential of self-renewing and plasticity (Danisovic *et al.*, 2011).



Fig. 1. Schematic drawing of articular (hyaline) cartilage containing abundant ECM and chondrocytes

They have been isolated and expanded *in vitro* from different tissue sources, including bone marrow, adipose tissue, muscles, dental pulp, umbilical cord Wharton's jelly (Odabas *et al.*, 2014; Danisovic *et al.*, 2011; Varga *et al.*, 2011; Zhang *et al.*, 2009b).

SSCs are adherent cells, which express specific surface antigens, including Stro-1, CD29, CD44, CD73, CD90 and CD105. They are negative for CD31, CD34 and CD45. Moreover, Kestendjieva *et al.* (2008) demonstrated expression of antiapoptotic protein-survivin, which is also expressed in most human cancers (Adamkov *et al.*, 2012; 2011).

Since the end of 1990s, a lot of studies focused on chondrogenic differentiation were done. It was demonstrated that SSCs derived from bone marrow cultured in high densities with culture medium containing TGF- β 1 lead into increased expression of collagen type II and X typical for articular cartilage *in vivo*. On other hand the expression of collagen type I was significantly decreased (Fortier *et al.*, 2011). More recently, the spontaneous chondrogenesis of SSCs was also proved in case of pellet cultures (Havlas *et al.*, 2011).

Results from clinical case reports and clinical trials indicated that SSCs may positively affect the cartilage repair. Kuroda *et al.* (2007) isolated autologous SSCs from bone marrow. After their *in vitro* cultivation, SSCs were embedded within a collagen gel, which was applied to cartilage defect and covered by periosteal flap. After 7 months the defect was filled with a hyaline cartilage. Centeno *et al.* (2008) injected suspension of autologous SSCs isolated from bone marrow into the subject's knee with MRI proven degenerative joint disease. After 24 weeks it resulted in significant cartilage growth, decreased pain and increased joint mobility of patient.

More recently, the extensive study was conducted to compare the clinical effect of autologous chondrocytes implantation to patients treated with autologous SSCs from bone marrow. About 72 patients were divided in two groups, 36 were treated by chondrocytes and 36 with SSCs. The results proved that both types of cells had similar effect on cartilage defect treatment, but in case of SSCs it required 1 less knee surgery, reduced costs and minimized donor-site morbidity (Nejadnik *et al.*, 2010).

Induced Pluripotent Stem Cells (iPSCs) significantly expand options of cell therapy. iPSCs are type of pluripotent cells that can be generated directly from terminally differentiated somatic cells (Csobonyeiova *et al.*, 2013).

The first evidence that differentiated somatic cells may be reprogrammed into undifferentiated cells have been demonstrated by somatic nuclear transfer (Wilmut *et al.*, 1997). The first iPSCs have been prepared from fibroblasts of mouse with using 4 transcription factors Oct4, Sox2, c-myc a Klf4 (Takahashi and Yamanaka,

2013). This combination did not work in human. Moreover, utilization of c-myc led to malignant transformation (Shimizu *et al.*, 2010). The first human iPSCs have been prepared by two independent research groups in USA (University of Wisconsin-Madison) and Japan (Kyoto University) from fibroblasts by using of Oct4, Sox2, Nanog and LIN28 (Yu *et al.*, 2007; Takahashi *et al.*, 2007). iPSCs displayed similar morphological and biological properties as embryonic stem cells, including expression of specific antigens, increased proliferation and telomerase activity and pluripotency. Moreover, they were able to produce embryoid bodies and teratomas (Yu *et al.*, 2007). Since these discoveries, iPSCs belong to most promising tools of regenerative and personalized medicine. For overview of their biological properties, possibilities of preparation and utilization in biomedicine check article by (Csobonyeiova *et al.*, 2013).

iPSCs were also studied in context of cartilage tissue engineering. Diekman *et al.* (2012) fabricated artificial cartilage tissue from iPSCs using micromass culture for purification of chondrogenic cells and pellet culture system with TGF- β 3 to induce chondrogenic differentiation *in vitro*. Their results proved increased expression of collagen type II and aggrecan. More recently, Ko *et al.* (2014) demonstrated successful chondrogenesis and regeneration of damaged cartilage with human iPSCs. Chondrogenic differentiation was induced by using alginate hydrogel culture system. Afterwards, micro aggregates of alginate constructs were implanted in osteochondral defects created on the patellar groove of immunosuppressed rats. After 21 days, they observed greater glycosaminoglycan contents and better chondrocytic features including lacuna and abundant matrix formation. However, further studies are necessary for translation of iPSCs into clinical practice, mainly focused on their biological safety.

Biomaterials for Cartilage Tissue Engineering

Cartilage tissue engineering employs many biomaterials of natural or synthetic origin (Table 1). They may be in form of hydrogel, sponges, fibrous meshes and nanofibres. The crucial characteristics are their non-toxicity and biocompatibility. Other characteristics, such as porosity (size and orientation of pores) and structural strength also influence their final utilization (Liu *et al.*, 2013).

The most commonly used natural material is collagen which belongs to basic constituents of cartilage *in vivo*. The mechanical properties of collagen-based scaffolds may be easily controlled by chemical modifications (Danisovic *et al.*, 2013). It was shown that chondrocytes cultured within collagen scaffolds maintain their original phenotype and production of Glycosaminoglycans (GAGs) under *in vitro* conditions. Moreover, several authors provide evidence of strong chondroinductive effect on SSCs (Zhang *et al.*, 2012; Zheng *et al.*, 2010).

Table 1. Types of biomaterials used in cartilage tissue engineering

Natural polymers	Synthetic polymers
Agarose	Poly (α -hydroxy esters)
Alginate	Poly (ethylene glycol/oxide)
Cellulose	Poly (NiPAAm)
Collagen	Poly (propylene fumarate)
Chitosan	Poly (urethane)
Fibrin	Poly (vinyl alcohol)
Gelatine	
Hyaluronic acid	
Silk fibroin	

Hyaluronic Acid (HA) is another natural biopolymer studied in the context of cartilage tissue engineering. Ha also occurs in native cartilage and should be used itself or in combination with other biomaterials. It was shown that chondrocytes cultured within HA hydrogels are forced to produce collagen type II and aggrecan typical for hyaline cartilage. Furthermore, SSCs cultured within photo-cross-linked HA hydrogel undergo chondrogenic differentiation (Chung and Burdick, 2009).

Other natural biomaterials that have been used in cartilage tissue engineering include alginate, agarose, chitosan, silk fibroin (Nooeaid *et al.*, 2012; Yu *et al.*, 2012).

Besides the above mentioned natural biopolymers, a variety of synthetic polymers may be applied in cartilage tissue engineering. When compared with natural biomaterials, they have several advantages, including highly controlled physical characteristics, consistency, uniformity and unlimited production (Yu *et al.*, 2012).

The most widely used are Polylactic Acid (PLA) and Polyglycolic Acid (PGA) (and their co-polymer). Both of them belong to biodegradable polymers. It was demonstrated that they increase chondrocyte proliferation and GAGs production. Moreover, several authors provide evidence of their effect on SSCs proliferation and chondrogenic differentiation (Foldberg *et al.*, 2012; Xue *et al.*, 2012).

Poly (Ethylene Glycol) (PEG) and its derivatives, mainly in form of hydrogel were also evaluated in respect to cartilage regeneration. Hwang *et al.* (2010) demonstrated that chondrocytes cultured within PEG scaffold remain alive and underwent chondrogenic differentiation. More recently, Cui *et al.* (2014) prepared cartilage constructs by using 3D printing technology. They used PEG-based scaffold with chondrocytes and demonstrated their full viability and prominent production of collagen type II and GAGs.

There are a lot of other synthetic materials that have been studied in respect to cartilage tissue engineering, e.g., poly (α -hydroxy esters), poly (propylene fumarate), poly (urethane) (Yu *et al.*, 2012).

Growth Factors

Growth factors play pivotal role in the process of chondrogenesis. They represent a group of biologically

active polypeptides that may affect cell proliferation and differentiation. In the hyaline cartilage, specific growth factors regulate homeostasis, integrity and development. The effect of growth factor on chondrogenic differentiation may differ depending on its dose, specific cell type and cell differentiation (Yu *et al.*, 2012).

Most studied growth factors in respect to cartilage tissue engineering include members of Transforming Growth Factor- β (TGF- β) superfamily, Fibroblast Growth Factor (FGF) family and Insulin-like Growth Factor 1 (IGF-1).

TGF- β superfamily contains at least 20 members in vertebrates. The best candidates for cartilage tissue engineering are TGF- β 1, TGF- β 3, BMP-2, BMP-4, BMP-7 and CDMP-1 (also known as GDF-5). TGF- β 1 promotes the synthetic activity of chondrocytes and decreases catabolic activity of IL-1 and MMPs *in vivo*. TGF- β 3 enhances synthesis of sulphated GAGs. BMP-2 stimulates synthesis of cartilage-specific ECM. BMP-4 is essential for normal embryogenic development and exhibits osteogenic and chondrogenic potential *in vivo*. BMP-7 has significant anabolic activity by which protects cartilage against damage. GDF-5 increases proliferation of chondrocytes as well as play important roles during the development of skeleton and joints (Fortier *et al.*, 2011).

FGF family contains at least 23 members in vertebrates. Mainly FGF-2, FGF-4, FGF-8 and FGF-18 were studied in the context of cartilage tissue engineering. It was shown, that FGF-2 promotes the proliferation of chondrocytes *in vivo*. FGF-2 with FGF-4 and FGF-8 are involved in the process of anabolic pathways activation which leads to decrease of aggrecanase effect after cartilage load. Furthermore, FGF-18 is involved in a variety of biological processes, including embryonic development, cell growth, morphogenesis and tissue repair (Ellman *et al.*, 2013).

IGF-1 stimulates chondrocytes to synthesize cartilage-specific ECM and decreases catabolic responses. Moreover, it was demonstrated that IGF-1 has an additive effect on increase of cartilage matrix synthesis when acts with TGF- β 1, BMP2 and BMP7 (An *et al.*, 2010; Gow *et al.*, 2010).

Conclusion

Recently, cartilage tissue engineering provides new promising approach which should be used in healing patients with damaged articular cartilage. It combines different types of cells (chondrocytes and stem cells), various scaffolding materials and appropriate growth factors to prepare fully biologically active artificial cartilage tissue. However, prior to translation into clinical practice the further studies have to be carried out, mainly focused on safety of stem cells expanded

under *in vitro* conditions. Considerable progress can be expected also in field of material technology, mainly in combination with 3D bioprinting.

Acknowledgment

The present study was partly supported by the grant of Ministry of Health of the Slovak Republic No. 2012/4-UKBA-4.

Author's Contributions

All authors equally contributed in this work.

Ethics

This article is original and contains unpublished material. The corresponding author confirms that all of the other authors have read and approved the manuscript and no ethical issues involved.

References

- Adamkov, M., E. Halasova, J. Rajcani, M. Bencat and D. Vybohova *et al.*, 2011. Relation between expression pattern of p53 and survivin in cutaneous basal cell carcinomas. *Med. Sci. Monit.*, 17: BR74-80. DOI: 10.12659/MSM.881442
- Adamkov, M., K. Kajo, D. Vybohova, J. Krajcovic and F. Stuller *et al.*, 2012. Correlations of survivin expression with clinicomorphological parameters and hormonal receptor status in breast ductal carcinoma. *Neoplasma*, 59: 30-37. DOI: 10.4149/neo_2012_004
- An, C., Y. Cheng, Q. Yuan and J. Li, 2010. IGF-1 and BMP-2 induces differentiation of adipose-derived mesenchymal stem cells into chondrocytes-like cells. *Ann. Biomed Eng.*, 38: 1647-1654. DOI: 10.1007/s10439-009-9892-x
- Beris, A.E., M.G. Lykissas, I. Kostas-Agnantis and G.N. Manoudis, 2012. Treatment of full-thickness chondral defects of the knee with autologous chondrocyte implantation: A functional evaluation with long-term follow-up. *Am. J. Sports Med.*, 40: 562-567. DOI: 10.1177/0363546511428778
- Brittberg, M., A. Lindahl, A. Nilsson, C. Ohlsson and O. Isaksson *et al.*, 1994. Treatment of deep cartilage defects in the knee with autologous chondrocyte transplantation. *N Engl. J. Med.*, 331: 889-895. DOI: 10.1056/NEJM199410063311401
- Centeno, C.J., D. Busse, J. Kisiday, C. Keohan and M. Freeman *et al.*, 2008. Increased knee cartilage volume in degenerative joint disease using percutaneously implanted, autologous mesenchymal stem cells. *Pain Physician*, 11: 343-53. PMID: 18523506

- Chung, C. and J.A. Burdick, 2009. Influence of three-dimensional hyaluronic acid microenvironments on mesenchymal stem cell chondrogenesis. *Tissue Eng. Part A*, 15: 243-254. DOI: 10.1089/ten.tea.2008.0067
- Csobonyeiova, M., S. Polak and L. Danisovic, 2013. Induced pluripotent stem cells and their implication for biomedical sciences. *OnLine J. Biol. Sci.*, 13: 106-114. DOI: 10.3844/ojbsci.2013.106.114
- Cucchiariini, M., J.K. Venkatesan, M. Ekici, G. Schmitt and H. Madry, 2012. Human mesenchymal stem cells overexpressing therapeutic genes: From basic science to clinical applications for articular cartilage repair. *Biomed Mater Eng.*, 22: 197-208. DOI: 10.3233/BME-2012-0709
- Cui, X., G. Gao, T. Yonezawa and G. Dai, 2014. Human cartilage tissue fabrication using three-dimensional inkjet printing technology. *J. Vis. Exp.* PMID: 24961492
- Danisovic, L., I. Varga, S. Polák, B. Bajciková and M. Adamkov *et al.*, 2011. Biological and morphological characterization of *in vitro* expanded human muscle-derived stem cells. *Tsitologiya*, 53: 482-487. PMID: 21870504
- Danisovic, L., Z. Novakova-Varchulova, M. Bohac, D. Bakos and J. Vojtassak, 2013. *In vitro* testing of modified collagen/hyaluronan/beta-glucan scaffold. *OnLine J. Biol. Sci.*, 13: 40-45. DOI: 10.3844/ojbsci.2013.35.40
- Diekman, B.O., N. Christoforou, V.P. Willard, H. Sun and J. Sanchez-Adams *et al.*, 2012. Cartilage tissue engineering using differentiated and purified induced pluripotent stem cells. *PNAS*, 109: 19172-19177. DOI: 10.1073/pnas.1210422109
- Ellman, M.B., D. Yan, K. Ahmadinia, D. Chen and H.S. An *et al.*, 2013. Fibroblast growth factor control of cartilage homeostasis. *J. Cell Biochem.*, 114: 735-742. DOI: 10.1002/jcb.24418
- Foldberg, S., M. Petersen, P. Fojan, L. Gurevich and T. Fink *et al.*, 2012. Patterned poly (lactic acid) films support growth and spontaneous multilineage gene expression of adipose-derived stem cells. *Colloids Surf B Biointerfaces*, 93: 92-99. DOI: 10.1016/j.colsurfb.2011.12.018
- Fortier, L.A., J.U. Barker, E.J. Strauss, T.M. McCarrel and B.J. Cole, 2011. The role of growth factors in cartilage repair. *Clin. Orthop Relat Res.*, 469: 2706-2715. DOI: 10.1007/s11999-011-1857-3
- Gow, D.J., D.P. Sester and D.A. Hume, 2010. CSF-1, IGF-1 and the control of postnatal growth and development. *J. Leukoc Biol.*, 88: 475-481. DOI: 10.1189/jlb.0310158
- Havlas, V., P. Kos, P. Jendelova, P. Lesny and T. Trc *et al.*, 2011. Comparison of chondrogenic differentiation of adipose tissue-derived mesenchymal stem cells with cultured chondrocytes and bone marrow mesenchymal stem cells. *Acta Chir. Orthop. Traumatol. Cech.*, 78: 138-144. PMID: 21575557
- Hwang, Y., N. Sangaj and S. Varghese, 2010. Interconnected macroporous poly (ethylene glycol) cryogels as a cell scaffold for cartilage tissue engineering. *Tissue Eng. Part A*, 16: 3033-3041. DOI: 10.1089/ten.TEA.2010.0045
- Kestendjieva, S., D. Kyurkchiev, G. Tsvetkova, T. Mehandjiev and A. Dimitrov *et al.*, 2008. Characterization of mesenchymal stem cells isolated from the human umbilical cord. *Cell Biol. Int.*, 32: 724-732. DOI: 10.1016/j.cellbi.2008.02.002
- Ko, J.Y., K.I. Kim, S. Park and G.I. Im, 2014. *In vitro* chondrogenesis and in vivo repair of osteochondral defect with human induced pluripotent stem cells. *Biomaterials*, 35: 3571-81. DOI: 10.1016/j.biomaterials.2014.01.009
- Kuroda, R., K. Ishida, T. Matsumoto, T. Akisue and H. Fujioka *et al.*, 2007. Treatment of a full-thickness articular cartilage defect in the femoral condyle of an athlete with autologous bone-marrow stromal cells. *Osteoarthritis Cartilage*, 15: 226-2231. DOI: 10.1016/j.joca.2006.08.008
- Liu, M., X. Yu, F. Huang, S. Cen and G. Zhong *et al.*, 2013. Tissue engineering stratified scaffolds for articular cartilage and subchondral bone defects repair. *Orthopedics*, 36: 868-873. DOI: 10.3928/01477447-20131021-10
- Malicev, E., N. Kregar-Velikonja, A. Barlic, A. Alibegović and M. Drobnić, 2009. Comparison of articular and auricular cartilage as a cell source for the autologous chondrocyte implantation. *J. Orthop. Res.*, 27: 943-948. DOI: 10.1002/jor.20833
- Mescher, A., 2013. Junqueira's Basic Histology: Text and Atlas. 13th Edn., McGraw Hill Professional, ISBN-10: 0071807209, pp: 480.
- Mobasheri, A., C. Csaki, A.L. Clutterbuck, M. Rahmanzadeh and M. Shakibaei, 2009. Mesenchymal stem cells in connective tissue engineering and regenerative medicine: Applications in cartilage repair and osteoarthritis therapy. *Histol. Histopathol.*, 24: 347-366. PMID: 19130405
- Nejadnik, H., J.H. Hui, E.P. Feng Choong, B.C. Tai and E.H. Lee, 2010. Autologous bone marrow-derived mesenchymal stem cells versus autologous chondrocyte implantation: An observational cohort study. *Am. J. Sports Med.*, 38: 1110-1116. DOI: 10.1177/0363546509359067
- Nooeaid, P., V. Salih, J.P. Beier and A.R. Boccaccini, 2012. Osteochondral tissue engineering: Scaffolds, stem cells and applications. *J. Cell Mol. Med.*, 16: 2247-2270. DOI: 10.1111/j.1582-4934.2012.01571.x
- Odabas, S., A.E. Elçin and Y.M. Elçin, 2014. Isolation and characterization of mesenchymal stem cells. *Methods Mol. Biol.*, 1109: 47-63. DOI: 10.1007/978-1-4614-9437-9_3

- Shimizu, T., T. Ishikawa, E. Sugihara, S. Kuninaka and T. Miyamoto *et al.*, 2010. C-MYC overexpression with loss of Ink4a/Arf transforms bone marrow stromal cells into osteosarcoma accompanied by loss of adipogenesis. *Oncogene*, 29: 5687-5699.
DOI: 10.1038/onc.2010.312
- Sophia Fox, A.J., A. Bedi and S.A. Rodeo, 2009. The basic science of articular cartilage: Structure, composition and function. *Sports Health*, 1: 461-468.
PMID: 23015907
- Takahashi, K. and S. Yamanaka, 2013. Induced pluripotent stem cells in medicine and biology. *Development*, 140: 2457-2461. DOI: 10.1242/dev.092551
- Takahashi, K., K. Tanabe, M. Ohnuki, M. Narita and T. Ichisaka *et al.*, 2007. Induction of pluripotent stem cells from adult human fibroblasts by defined factors. *Cell*, 131: 861-872. DOI: 10.1016/j.cell.2007.11.019
- Varga, I., D. Holly, J. Vojtassak, D. Bohmer and S. Polak *et al.*, 2011. Morphological characterization of *in vitro* expanded human dental pulp-derived stem cells. *Biologia*, 66: 706-711.
DOI: 10.2478/s11756-011-0069-3
- Wilmot, I., A.E. Schnieke, J. McWhir, A.J. Kind and K.H. Campbell, 1997. Viable offspring derived from fetal and adult mammalian cells. *Nature*, 385: 810-813.
DOI: 10.1038/385810a0
- Xue, J.X., Y.Y. Gong, G.D. Zhou, W. Liu and Y. Cao *et al.*, 2012. Chondrogenic differentiation of bone marrow-derived mesenchymal stem cells induced by acellular cartilage sheets. *Biomaterials*, 33: 5832-5840.
DOI: 10.1016/j.biomaterials.2012.04.054
- Yu, D.A., J. Han and B.S. Kim, 2012. Stimulation of chondrogenic differentiation of mesenchymal stem cells. *Int. J. Stem. Cells*, 5: 16-22. PMID: 24298351
- Yu, J., M.A. Vodyanik, K. Smuga-Otto, J. Antosiewicz-Bourget and J.L. Frane *et al.*, 2007. Induced pluripotent stem cell lines derived from human somatic cells. *Science*, 318: 1917-1920. PMID: 18029452
- Zhang, L., J. Hu and K.A. Athanasiou, 2009a. The role of tissue engineering in articular cartilage repair and regeneration. *Crit. Rev. Biomed. Eng.*, 37: 1-57.
PMID: 20201770
- Zhang, Y.N., P.C. Lie and X. Wei, 2009b. Differentiation of mesenchymal stromal cells derived from umbilical cord Wharton's jelly into hepatocyte-like cells. *Cytotherapy*, 11: 548-558.
DOI: 10.1080/14653240903051533
- Zhang, L., T. Yuan, L. Guo and X. Zhang, 2012. An *in vitro* study of collagen hydrogel to induce the chondrogenic differentiation of mesenchymal stem cells. *J. Biomed Mater Res. A*, 100: 2717-2725.
DOI: 10.1002/jbm.a.34194
- Zheng, L., H.S. Fan, J. Sun, X.N. Chen and G. Wang *et al.*, 2010. Chondrogenic differentiation of mesenchymal stem cells induced by collagen-based hydrogel: An *in vivo* study. *J. Biomed Mater Res. A*, 93: 783-792.
DOI: 10.1002/jbm.a.32588