

2D-DIGE Proteomic Analysis of Mesenchymal Stem Cell Cultured on the Elasticity-tunable Hydrogels

Thasaneeya Kuboki¹, Fahsai Kantawong², Richard Burchmore³, Matthew J Dalby², and Satoru Kidoaki^{1*}

¹*Institute for Materials Chemistry and Engineering, Division of Biomolecular Chemistry, Kyushu University, 744 Moto-oka, Nishi-ku, Fukuoka 819-0395, Japan,* ²*Centre for Cell Engineering, Division of Infection and Immunity, Institute of Biomedical and Life Sciences, Joseph Black Building, University of Glasgow, Glasgow, G12 8QQ, UK,* ³*Sir Henry Wellcome Functional Genomics Facility, Institute of Biomedical and Life Sciences, Joseph Black Building, University of Glasgow, Glasgow, G12 8QQ, UK*

ABSTRACT. The present study focuses on mechanotransduction in mesenchymal stem cells (MSCs) in response to matrix elasticity. By using photocurable gelatinous gels with tunable stiffness, proteomic profiles of MSCs cultured on tissue culture plastic, soft (3 kPa) and stiff (52 kPa) matrices were deciphered using 2-dimensional differential in-gel analysis (2D-DIGE). The DIGE data, tied to immunofluorescence, indicated abundance and organization changes in the cytoskeletal proteins as well as differential regulation of important signaling-related proteins, stress-responding proteins and also proteins involved in collagen synthesis. The major CSK proteins including actin, tubulin and vimentin of the cells cultured on the gels were remarkably changed their expressions. Significant down-regulation of α -tubulin and β -actin can be observed on gel samples in comparison to the rigid tissue culture plates. The expression abundance of vimentin appeared to be highest in the MSCs cultured on hard gels. These results suggested that the substrate stiffness significantly affects expression balances in cytoskeletal proteins of MSCs with some implications to cellular tensegrity.

Key words: Mesenchymal stem cell/surface elasticity/2D-DIGE/cytoskeletal proteins/cellular tensegrity

Introduction

In general, living cells have characteristic abilities to passively sense and actively respond to extracellular mechanical stimuli or milieu. For example, vascular endothelial cells acutely perceive blood shear stress, which induces morphological and cytoskeletal remodeling, up-regulation of production of nitric oxide (Korenaga *et al.*, 1994; Davies *et al.*, 1997), acetylcholine (Milner *et al.*, 1990) and prostacyclin (Grabowski *et al.*, 1985), etc. The phenotype of chondrocytes is affected by hydrodynamic pressure (Smith

et al., 1995) and periodic compression forces (Jung *et al.*, 2008) of their surroundings. The activity of osteocytes for bone remodeling is regulated by the amplitude of mechanical load (Reijnders *et al.*, 2007). In addition to such the dynamic mechanical stimulus, mechanical microenvironment also affects cell behaviors. Surface elasticity is of significant interest because the mechanical conditions have potential to regulate a wide variety of the biological events of various cell types, including cell growth, signaling, replication, differentiation, adhesion and motility (Pelham and Wang, 1997; Lo *et al.*, 2000; Wang *et al.*, 2000; Discher *et al.*, 2005; Peyton *et al.*, 2006; Kidoaki and Matsuda, 2008; Kocgozlu *et al.*, 2010). A process known as mechanotransduction, through which the cells sense applied mechanical force and transduce this stimulus into biochemical signals has been extensively studied in the research area of cell mechanobiology (Wang *et al.*, 1993).

Related to this issue, mechanobiology of stem cells has recently drawn much attention. Hydrogels with tunable elasticity, mimicking the stiffness of native tissues, have increasingly been applied to study stem cell biology (Saha

*To whom correspondence should be addressed: Satoru Kidoaki, Institute for Materials Chemistry and Engineering, Division of Biomolecular Chemistry, Kyushu University, 744 Moto-oka, Nishi-ku, Fukuoka 819-0395, Japan.

Tel: +81-92-802-2507, Fax: +81-92-802-2509

E-mail: kidoaki@ms.ifoc.kyushu-u.ac.jp

Abbreviations: MSC, mesenchymal stem cell; CSK, cytoskeleton; 2D-DIGE, 2 dimensional differential in gel analysis; StG, styrenated gelatin; TCPS, tissue culture polystyrene; AFM, Atomic Force Microscope; MS, mass spectrometry; MALDI/TOF/TOF, Matrix-assisted laser desorption/ionization time of flight tandem mass spectrometer; MTs, microtubules; IFs, intermediate filaments.

et al., 2008; Evans *et al.*, 2009; Seib *et al.*, 2009; Winer *et al.*, 2009a, 2009b; Gilbert *et al.*, 2010). While the fate of stem cells is known to be regulated by certain biochemical soluble factors (Pittenger *et al.*, 1999; Bianco *et al.*, 2001), recent evidence shows that matrix elasticity can direct the lineage specification of MSCs (Engler *et al.*, 2006; Rowlands *et al.*, 2008). This provides the possibility of controlling stem cell fate via modulation of external stimuli generated by underlying substrate and design of the extracellular mechanical milieu. Considering approaches from biomaterials engineering to manipulate MSC, surface chemistry (McBeath *et al.*, 2004; Curran *et al.*, 2005; Benoit *et al.*, 2008; Curran *et al.*, 2010; Kilian *et al.*, 2010) and nanotopography of cell culture substrate (Dalby *et al.*, 2007; Oh *et al.*, 2009; McMurray *et al.*, 2011) have also been shown to be influential factors.

Considering the mechanism for such behaviors, the contribution of cytoskeletal mechanics are considered central, and regulation of cytoskeleton (CSK)-related molecules such as myosin light chain II and Rho A kinase (ROCK) have been investigated (Engler *et al.*, 2006; Kilian *et al.*, 2010; McMurray *et al.*, 2011). However, details of the biomechanical fate control mechanisms of MSCs are not well elucidated and their systematic exploitation for designing biomaterials has not been established. To achieve this, comprehensive analysis for behaviors of whole intracellular proteins especially including CSK-related molecules is required.

To systematically characterize the substrate-mechanics-induced biomechanical responses of MSCs, the present study focuses on the proteomic changes of MSCs in response to micro-engineered matrix elasticity, based on the analysis for global comparative proteomics. The differential expressions of MSCs cultured on the cell adhesive elasticity-tunable gels (as we have previously developed (Kidoaki and Matsuda, 2008; Kawano and Kidoaki, 2011)) were studied using the 2D-DIGE. DIGE-based proteomics has been applied for the study of the relative differences in protein abundance of human osteoprogenitor in response to surface topographies (Kantawong *et al.*, 2009a, 2009b, 2009c), demonstrating the advantage of DIGE as a powerful tool for quantitative proteomics study of scarce samples. The dynamic changes in proteomic level of MSCs in response to matrix elasticity were quantitatively characterized and the effect of extracellular stiffness on CSKs organization was elucidated by immunofluorescence, in relation to proteomic behaviors. The implication of these changes on their cellular physiology and function are discussed herein.

Materials and Methods

Cell culture

Immortalized human MSCs (Health Sciences Research Resource

Bank, Osaka, Japan) were cultured in Dulbecco's modified Eagles medium (DMEM); Gibco BRL, NY, USA) supplemented with 10% fetal bovine serum (FBS; Gibco BRL), 100 units/ml penicillin and 100 µg/ml streptomycin. Cells were maintained on tissue culture polystyrene dishes (TCPS) at 37°C under 5% CO₂ in a humidified incubator. The hMSC passages 4–7 were used in this study. For DIGE analysis, the hMSCs were seeded at density 2500 cells/cm² on TCPS, soft and hard gels for 3 weeks with every 3–4 days replacement of fresh medium.

Preparation of gelatinous gels with different surface elasticity

Cell adhesive hydrogels with different surface elasticity were prepared from gelatin based on photo gelation method. For preparation of the gel, photocurable styrenated gelatin (StG) synthesized in-house was employed (Kidoaki and Matsuda, 2008; Kawano and Kidoaki, 2011). A sol solution of phosphate buffer saline (PBS) including StG (30% w/w; degree of derivatization: 100%) and water-soluble carboxylated camphorquinone (Okino *et al.*, 2002) (0.1% w/v of gelatin) was spread between the vinyl-silanized glass substrate and the poly(N-isopropylacrylamide) coated glass substrate, and was irradiated by visible light with intensity of 100 mW/cm² (measured at 488 nm) for 40–360 s. The detached gels were immersed overnight with gently rocking in PBS for complete swelling of the hydrogels. Surface elasticity on each hydrogel was determined by microindentation analysis as previously described (Kawano and Kidoaki, 2011). The force-indentation curves of the gel surface were measured using Atomic Force Microscope (AFM) (NVB100; Olympus Optical Co. Ltd., Tokyo, Japan; AFM controller and software, Nanoscope IIIa; Veeco Instruments, CA, USA) with a silicon-nitride cantilever with a half pyramidal tip and nominal spring constant of 0.02 N/m at 10 randomly selected points (n=10) of 3 different samples (n=3). Young's Moduli of the surface were evaluated from the force-indentation curves of the gel surface by fitting to the Hertz model (Herzt, 1881; Sheddon, 1965). The prepared hydrogels with average Young modulus 3.3±1.1 kPa and 52.3±30.9 kPa will be referred to in this study as the soft and the hard gel, respectively. The TCPS dishes (elastic modulus~3 GPa (Callister and Rethwisch, 2000)) were used as the control substrate for MSC culture.

Protein extraction and precipitation

Three pairs of protein samples extracted from controls and tests substrates: Soft gel/TCPS, hard gel/TCPS, and hard gel/soft gel were compared with each other. To obtain statistically relevant data, results from three replicates experiments were matched for each experimental set. Cells were trypsinized from the substrates and the pellets were washed twice with PBS. The pellets were resuspended in DIGE lysis buffer (7M urea, 2M Thiourea, 4% CHAPS, 30 mM Tris pH 8.0 and 1X protease inhibitor cocktail; Sigma, Tokyo, Japan) and left at room temperature for 1 h with vigorously mixing every 20 min. The insoluble material was removed by centrifugation at 2100 rpm, 4°C and the protein in the

supernatant was precipitated by cold acetone. The pellets were air-dried and resuspended in DIGE lysis buffer. The protein concentration was determined by using Bio-Rad protein assay reagent according to the manufacturer's protocol.

Differential in-gel electrophoresis

Saturation labeling

Differential in-gel electrophoresis was performed as previously described (Kantawong *et al.*, 2009a, 2009b, 2009c). Briefly, 5 µg of the extracted proteins were reduced with TCEP (tris (2-carboxyethyl) phosphine) for 1 h at 37°C. The proteins were labeled with fluorescent dye Cy3 and Cy5 using saturation labeling method (2 nmol TCEP and 4 nmol CyDye per 5 µg of protein). The reactions were stopped by adding equal volumes of 2X sample buffer (7M urea, 2M thiourea, 4% w/v CHAPS, 2% v/v IPG buffer pH 4–7 and 2% w/v DTT). The Cy3 and Cy5 labeled proteins were mixed together prior to 2D gel electrophoresis.

2D- gel electrophoresis and image analysis

Two-dimensional gel electrophoresis was performed as previously described (Kantawong *et al.*, 2009a, 2009b, 2009c, 2011). Samples were rehydrated into 24 cm; linear gradient pH 4–7 immobilized pH gradient (IPG) strips and focused on Ettan IPGphor system (GE Healthcare). The isoelectric focusing (IEF) was carried out using the step gradient protocol (30 V 12 h, 300 V 1 h, 600 V 1 h, 1000V 1 h, 8000 V 3 h, 8000 V 8.5 h). The strips were equilibrated for 15 min in 5 ml of reducing solution (6M urea, 100 mM Tris-HCl pH 8.3, 30% (v/v) glycerol, 2% (w/v) SDS, 5 mg/ml DTT) then the proteins were further separated on 12% acrylamide gels. The fluorescent images were obtained by scanning gels on typhoon 9400 scanner (GE healthcare). Cy3 and Cy5 images were scanned at 532/580 nm and 633/670 nm excitation/emission wavelengths, respectively. Image analysis and statistical quantification of the relative protein expression was performed using DeCyder™ V. 5.1 software (GE Healthcare).

Protein digestion, mass spectrometry and protein identification

Preparative gel contained 500 µg of Cy3-labeled protein extracted from hMSC culture on TCPS were run for identification of protein of interest. Selected spots were picked automatically using an Ettan Spot Handling Workstation (Amersham Biosciences, UK). Mass spectrometry (MS) analysis and protein identification were performed as previously described (Kantawong *et al.*, 2009a, 2009b, 2009c, 2011). In gel tryptic digestion was performed and the trypsinized peptide solutions were transferred to MALDI samples plates (Applied Biosystems, Framingham, MA). Identification of proteins was carried out on MALDI/TOF/TOF mass spectrometer (4700 proteomic analyzer, Applied Biosystems). Mass spectra were obtained over the *m/z* range of 800–4000 and up to 10 peaks were selected for the MS/MS analysis. Protein identification was performed using Global Proteome Server Explorer software (Applied Biosystems) using the NCBI human protein database. The identification was assigned to a protein spot feature if the protein score was calculated to be greater than 66, correlating

with a 95% confidence interval. The protein identifications were assigned using the Mascot search engine, which gives each protein a probability-based MOWSE score. In all cases, variable methionine oxidation was used for searches. An MS tolerance of 1.2 Da for MS and 0.4 Da for MS/MS analysis was used. Only proteins identified with a MOWSE score of greater than 66 were considered as statistically significant ($p < 0.05$).

Protein network and pathway analysis

Proteins that differentially expressed upon different surface elasticity were uploaded to web based pathway analysis tool IPA (Ingenuity Systems, CA, USA) for the possible network and pathway analysis. Based on the large numbers of experimental evidences recorded in IPA database (Ingenuity Knowledge Base), the pathways were deduced among the proteins addressed in our data. The custom pathways were built by using pathway design tools. The molecules of interest were identified as Network Eligible molecules that served as seeds for generating pathway. IPA then generated hypothetical networks from these proteins by linking them with other proteins that were potentially be included in networks from database, based on known association in the published literatures.

Fluorescence observation for cytoskeletons and focal adhesions

Immunostaining for tubulin, vimentin and paxillin in the cells cultured on different substrates was performed. For this experiment, the cells were cultured on gel-coated cover slips (diameter 18 mm.). After 24 h or 3 weeks of cultivation, the cells were fixed in 4% paraformaldehyde for 20 min at room temperature. The cells were permeabilized and blocked with 0.5% triton-X, 10% donkey serum in PBS for 45 min. The cells were incubated with primary antibodies, polyclonal anti-mouse; α -tubulin (Sigma, Tokyo, Japan), polyclonal anti-rabbit; vimentin (AnaSpec, Inc., CA, USA) and paxillin (Santa Cruz Biotechnology Inc., CA, USA) and later with secondary antibodies (donkey anti-rabbit/mouse conjugated with Alexa Fluor®488, or donkey anti-rabbit conjugated with Alexa Fluor®568 Invitrogen, Tokyo, Japan). The Rhodamine-phalloidin (Cytoskeleton Inc. Denver, Co., USA) was added into this step for staining of F-actin filaments. A Carl Zeiss LSM 510 (Carl Zeiss Microimaging Co. Ltd., Tokyo, Japan) 20X-objective with 3.0–3.4X optical zoom was used for observation of fluorescent signal.

Results

Differential proteomic profiles of MSC on different matrix elasticity

A summary of proteins that differentially expressed in MSCs cultured on different surface elasticity is shown in Table I together with their known biological functions.

Table I. IDENTIFICATION OF PROTEIN THAT DIFFERENTIALLY EXPRESSED ON DIFFERENT MATRIX ELASTICITY

Spot no.	Protein match	Function	fold changes		
			H/TCPS	S/TCPS	H/S
1.	Alpha tubulin	Cytoskeleton (major component of microtubule)	-6.74±1.36	-4.51±1.15	-1.90±1.02
2.	Alpha collagen (COL1A)	Collagen biosynthesis, extracellular matrix structural constituent	-3.80±1.37	-2.83±0.17	-1.78±1.04
3.	Beta actin	Cytoskeleton (microfilament)	-3.19±0.90	-3.24±0.27	
4.	Vimentin	Cytoskeleton (intermediate filament)	1.47±0.22	—	3.00±1.42
5.	Tropomyosin 1 (TPM1)	Actin binding, structural constituent of cytoskeleton, cytoskeleton organization	—	-1.38±0.10	1.53±0.12
6.	Tropomyosin 2 (TPM2)	Actin binding, cell motion, tension	—	—	1.56±0.15
7.	Tropomyosin 4 (TPM4)	Actin binding, calcium ion binding, cell motion	1.60±0.19	1.44±0.17	1.51±0.61
8.	Laminin binding protein (LBP)	Cell migration, mechanosensing	1.63±0.02	1.74±0.21	—
9.	Actin capping protein G (CapG)	Inhibit actin bundling	1.80±0.19	1.76±0.32	—
10.	Actin capping protein Z (CapZ)	Inhibit actin bundling	2.12±0.09	2.17±0.24	—
11.	Microtubule associated proteins (MAP)	Structural molecule activity, microtubule assembly, depolymerization, stabilization	1.67±0.02	2.04±0.24	—
12.	Myosin light chain II (MYL2)	Actin monomer binding, structural constituent of muscle	—	—	1.49±0.20
13.	Myosin light chain VI (MYL6)	Motor protein, structural constituent of muscle, muscle filament sliding	1.72±0.18	1.34±0.05	—
14.	Alpha enolase (ENO1)	Transcription regulator	-1.53±0.20	-1.57±0.07	—
15.	Nucleophosmin (NPM)	Nucleocytoplasmic transport, positive regulation of cell proliferation	1.73±0.11	2.01±0.15	—
16.	Translational control tumor protein (TCTP)	Cell proliferation, anti-apoptosis	1.86±0.07	1.83±0.06	—
17.	Prolyl-4-hydroxylase (PH4A)	Key enzyme in collagen synthesis	-2.09±0.25	-1.97±0.19	—
18.	Galactin-1 (GAL-1)	Signal transduction, regulation of apoptosis	2.15±0.10	1.95±0.09	—
19.	Superoxide dismutase (SOD)	Anti-oxidant, activation of MAPK activity, stress response	2.15±0.10	1.79±0.03	1.42±0.63
20.	Glutathione S transferase (GST)	Xenobiotic metabolism signaling, detoxifying enzyme	2.17±0.07	1.77±0.10	1.38±0.22
21.	Chloride channel 4 (CLIC4)	Ion transport, signal transduction, differentiation, negative regulation of cell migration	2.21±0.17	1.80±0.08	—
22.	Ubiquitin carboxy-terminal Esterase L1 (UCHL1)	Cell proliferation, stress response	2.47±0.16	2.57±0.11	—
23.	Chloride channel 1 (CLIC1)	Ion transport, signal transduction	3.06±0.71	3.05±0.67	—
24.	14-3-3 zeta (YWHAZ)	Signal transduction, transcription factor binding, protein targeting	2.13±0.31	2.72±0.05	
25.	Heat shock protein 27 (Hsp27)	Molecular chaperon	—	—	1.51±0.21
26.	Annexin V (ANX5)	Anti-apoptosis, signal transduction	1.64±0.07	1.37±0.11	1.49±0.21
27.	Cathepsin D (CTSD)	Lysosomal peptidase	1.58±0.18	—	1.43±0.09
28.	Ribosomal protein large subunit P0 (P0)	Protein synthesis, translational elongation	1.51±0.25	1.49±0.14	—




Fig. 1. Reference gel image analyses by DeCyder™ software. Reference gel image obtain from 2D gel of Cy3 labeled hMSC extract. Numbers indicate protein spots that differentially expressed in this study, corresponding to spot numbers in the first column of Table I.




Fig. 2. Categorization of proteins that differentially expressed on various substrate elasticities. The proteins that change their expressions in this study were classified into 5 categories according to their potential biological function (CSKs-related, cell proliferation/differentiation, signal transduction/transport processes, stress response and collagen synthesis).

Twenty-eight protein spots were detected with greater than 1.3 fold average changes in abundance after 3 weeks of culture. The corresponding spot numbers are indicated in the reference gel image (Fig. 1). These proteins were arbitrary categorized according to their possible biological functions (Fig. 2). The details of fold changes of each protein spot and their related functions are provided in supplementary data (Table S1). The majority of proteins (12 out of 28) that changed their expressions in response to matrix stiffness belonged to CSK-related proteins such as tubulin, actin and vimentin. The remaining were groups of protein with diverse functions such as signal transduction and transport processes (14-3-3Z, GAL1, CLIC1, CLIC4, etc), cell proliferation and differentiation (UCHL1, nucleophosmin, P0, enolase, etc), stress response (GST,

SOD) and collagen synthesis (P4HA, COL1A).

Comparisons of the up- or down-regulated degree of expression of those proteins on the different culture surfaces are shown in Fig. 3. Three sets of the comparison on hard gels against TCPS (Fig. 3A), soft gels against TCPS (Fig. 3B) and hard gels against soft gels (Fig. 3C) were demonstrated. Proteomic expression patterns observed on the gel matrices against TCPS showed almost similar trends with some minor differences (Fig. 3A and 3B). In both hard and soft gels against TCPS, significant down-regulation of α -tubulin and β -actin was observed, together with up-regulation of inhibitory proteins for actin bundling or organization such as actin capping proteins G and Z. As for the minor differences between hard and soft gels, up-regulated proteins on the hard gels only were CLIC4, cathepsin D and vimentin, whereas tropomyosin 1 was down-regulated only on soft gels.

Direct comparison of the differential proteomic expression between hard and soft gels revealed differences in their expression profiles (Fig. 3C). Up-regulated proteins detected only in this comparison were tropomyosin 2, heat shock protein 27 and myosin light chain II. In comparison to the soft gels, cells cultured on hard gels show marked up-regulation of vimentin and decreased expression of tubulin. Peak volumes analysis and log abundance of vimentin and α -tubulin are shown in supplementary data (Fig. S1).

In summary, the following trends were noted for CSK proteins: (1) on the gel surface compared with TCPS, α -tubulin and β -actin were down-regulated, (2) on the hard




Fig. 3. Differential proteomic expression of hMSC cultured on TCPS, hard and the soft gels. Graphical display represented Cy5 and Cy3 ratio of comparison between extracted from cells cultured on the hard gel against TCPS (a), the soft gels against TCPS (b) and the hard gels against soft gels (c). The bar charts show the mean fluorescent intensity of three spots plotted from three replicate experiments with error bars that represented standard deviation. Filled bars show up-regulated proteins and opened bars show down-regulated proteins.




Fig. 4. Immunofluorescence and actin staining of single hMSC cultured on different substrate elasticity. The figures show confocal images of a) F-actin b) α -tubulin, c) vimentin and d) paxillin of the hMSCs cultured on the soft, hard gels and glass for 24 hr. The scale bar is 10 μ m.

gels compared with soft gels, α -tubulin was down-regulated and vimentin was up-regulated.

Substrate-elasticity-dependent cytoskeletal features of MSC

After 24 hr cultured on the substrates with different surface-elasticity, the isolated cells changed their cytoskeletal features as demonstrated by immunofluorescence (Fig. 4 and Fig. S2–5). While rigid glass substrates induced thick stress fibers, the cells on softer matrices showed significant less bundling of actin filaments (Fig. 4a and Fig. S2). The microtubule (MT) structures in the cells, particularly those on the very soft substrate exhibited a notable disassembly of microtubule structures (Fig. 4b and Fig. S3). The intermediate filaments (IFs), vimentin, exhibited less organization on the softest substrate (Fig. 4c and Fig. S4). Furthermore, the formation of mature focal adhesions was also reduced as the elasticity of the gels decreased (Fig. 4d and Fig. S5).

The CSK was also examined after 3 weeks of culture (Fig. 5). In contrast to the observation for single cells in Fig. 4, abundant actin stress fibers could be observed for all samples. On the other hand in the comparison between the control and test materials, the glass induced a highly denser stress fibers than the soft and hard gels did. In addition, the density of the stress fibers appeared to be lower on the soft-

est gels, although, interestingly, the fibers appeared more polarized (Fig. 5a).

In the densely confluent cells where the MTs were poorly resolved, slightly different organization of the structures on different stiffness still could be observed (Fig. 5b). On the glass substrates, though not so clear as in the single cell observations, filamentous MTs were still noticeable. The cells showed strong association of MTs, as demonstrated by an intense staining of tubulin at the cell periphery. This staining pattern was reduced in the cells cultured on soft gels whereas those on the hard gel showed no remarkable association of MT structures.

The substrate mechanical properties demonstrated the most profound effects on the organization of the IFs. The well-defined filamentous vimentin structures were evident only in the cells that grown on the hard gels (Fig. 5c). No detectable lattice was observed in the confluent monolayer of the cells cultured on the glass or the softest gels.

Network analysis of identified proteins

IPA software was used to generate interactive networks of proteins in MSCs that change their expression in response to different surface elasticity in order to help explain biological relevance of the identified proteins. The pathways predicted from the published literatures (see supplementary




Fig. 5. Immunofluorescence and actin staining of confluent hMSC cultured on different substrate elasticity. The figures show confocal images of a) F-actin staining, b) α -tubulin and c) vimentin of the confluent hMSCs cultured on the soft, hard gels and glass for 3 weeks. The scale bar is 10 μ m.

excel file) are shown in Fig. 6, demonstrating how the proteins interact with each other along with their sub-cellular localization. The up- and down-regulated proteins are shown in blue and red, respectively. The proteins that exhibit direct (solid lines) or indirect relationships (dashed lines) with our input proteins were included in the network. The comparison between protein profiles of cells cultured on the hard gels against TCPS (Fig. 6a) and that of the soft gels against TCPS (Fig. 6b) revealed the significant affect of surface elasticity on cell physiology. The CSK related proteins were highlighted at the center since these proteins showed significant up and down regulation in our system. While generally sharing similar trends, some minor differences can be observed between 2 pathways. Substrate elasticity appeared to induce universal down-regulation of CSK proteins in both conditions. The pathway of MSCs proteoms on hard gels illustrated an effect derived from the substrates on vimentin, whereas on the soft gels, affect on a group of tropomyosin proteins was noted.

Discussion

Recent evidence strongly suggests that besides the extensively studied soluble factors, mechanical signals are also potent regulators of stem cell behavior (Engler *et al.*, 2006; Rowlands *et al.*, 2008; Evans *et al.*, 2009; Seib *et al.*, 2009). Elucidation of the underlying mechanism of this mechanical modulation of stem cell functions is important for tissue engineering applications. This study aimed to extend our knowledge on the substrate-stiffness-induced mechanotransduction in MSCs by the DIGE-based proteomic analysis, focusing on the contribution of major CSKs-related proteins. Although previous genomic approaches, including transcriptome analysis, have provided informative data on the matrix-stiffness-dependent differences in the expressed mRNA transcripts (Engler *et al.*, 2006; Rowlands *et al.*, 2008), insufficient correlation between changes in expression levels of mRNAs and proteins is sometimes inevitable due to factors such as the stability of mRNA or post-




Fig. 6. Pathway analysis of proteomic profiles of hMSC on various surface elasticity conditions. IPA generated networks where differentially proteins can be related. The potential pathway between cells cultured on the hard gel against TCPS (a), the soft gels against TCPS (b) are illustrated.

translational modification.

In this study, to characterize the substrate-stiffness-induced MSC behaviors more directly, DIGE-based proteomic investigation was applied for immortalized MSCs (Kassem *et al.*, 2004; Abdallah *et al.*, 2005). Summarizing the trends observed in the DIGE data, we observe: (1) on the gel surfaces compared to TCPS, α -tubulin and β -actin were strongly down-regulated, (2) on the hard gel surface compared with soft gel surface, α -tubulin was down-regulated and vimentin up-regulated.

The effect of substrate elasticity appeared to be strongest on the expression of α -tubulin, which was 6 and 4 fold down-regulated in the cells cultured on the hard and soft gels compared with TCPS. This was further highlighted by immunofluorescence. The α -tubulin forms heterodimer with β -tubulin as the building block of microtubule structures. The stability of the dimer depends on the presence of GTP-bound β -tubulin (Cleveland *et al.*, 1980). We note, however, that no significant difference in β -tubulin expression abundance could be observed between different substrates in our study (data not shown). Our data is consistent with the previous report that the human trabecular meshwork cells grown on stiff polyacrylamide gels expressed less tubulin than those on TCPS or soft gels (Schlunck *et al.*, 2008). They suggested that the delay of degradation of tubulin monomer was caused by a lack of binding between the cells and the extracellular matrix (ECM) (Mooney *et al.*, 1994). Concomitant with the reduction in stress fiber bundling shown by phalloidin staining, our DIGE data demonstrated a 3-fold down regulation of β -actin expression in cells cultured on gelatinous gels (soft and hard) compared with TCPS.

In addition to α -tubulin and β -actin, our data showed vimentin as being mechano-responsive. Direct comparison of differential expression degree of vimentin between hard and soft gels showed marked 3-fold up-regulation of vimentin on the hard gels (Fig. 3). Cell shape was more spread and flattened, and the structure of the IFs exhibited a more developed lattice on the hard gels than on the soft gels. These observations appear to suggest that harder substrate may induce the well-spread cell shape, well-developed IF structure, and hence a higher degree of vimentin expression. Again, these results tie in with those seen in other systems with either poorly or well spread cells (Ben-Ze'ev, 1983; Matesic *et al.*, 1997).

Besides the above-mentioned changes in CSK protein expression, several proteins that play pivotal role in cellular physiology and functions were also found to change their expression profiles in response to the mechanical conditions of the underlying substrates:

(1) Proteins with highest modulation are chloride channels. We observed significant up-regulation of CLIC11 and CLIC4 in the cells cultured on both hard and soft gels. Chloride channels are important for maintaining resting membrane potential together with potassium channels

(Hill *et al.*, 1996). These proteins play important roles in a variety of cellular events such as organic solute transport, cell migration, cell proliferation and differentiation. Mechano-activated chloride channels are represented by various types of Cl⁻ channels, they may be activated by different mechanical mechanisms depending on the cell type (Nilius *et al.*, 1996).

(2) Ubiquitin carboxyterminal esterase L1 (UCHL1), which belongs to the family of enzymes responsible for hydrolyzing carboxyl terminal esters and amides of ubiquitin, were found to be up-regulated on the soft and hard gels. A recent report suggests that *UCHL1* can inhibit MT formation in a ubiquitination- dependent manner (Bheda *et al.*, 2010). Up-regulation of this enzyme may partly contribute to the depolymerization of MTs observed in our study.

(3) Down-regulation of proteins related to collagen synthesis, COLA1 and P4HA, was evidenced on the gel surfaces. Decreased expression of key enzyme in biosynthesis of collagen, P4HA, and the most abundant form of collagen in the human body, COL1A1, may partly related to the affect of CSK tension generated by underlying substrate. For instance, disruption of actin CSK with cytochalasin D decreases collagen accumulation (Hubchak *et al.*, 2003). It has also been shown that TGF- β 1-mediated collagen I accumulation is associated with CSK rearrangement and Rho-GTPase signaling (Hubchak *et al.*, 2003), which were mediated by matrix elasticity and CSK tension-dependent signaling (Arora *et al.*, 1999).

IPA software was used to generate interactive networks by linking the proteins that based on the published literatures (supplementary excel file), known to interact with the identified proteins in this study. When consider CSKs as a central hub, the predicted pathway demonstrated the interconnectedness between several proteins with important biological functions. For example, proteins related to signal transduction (YWHAZ) and transport processes (Cl-channels), which up-regulated in our study, exhibited direct interaction with CSKs. The CLIC4 binds directly to brain dynamin I in a complex containing actin, tubulin and YWHAZ (Suginta *et al.*, 2001). The YWHAZ proteins are involved in most of the cellular processes such as cell signaling, division, apoptosis and cytoskeletal organization (Aitken *et al.*, 1995; van Hemert *et al.*, 2001). They have overall inhibitory effect on cell cycle progression and involved in mediating integrin-induced cytoskeletal changes via RhoGTPase activation. Tropomyosin family of CSKs plays a role in stabilizing actin microfilament (Shah *et al.*, 2001). Many isoforms including TPM1 are down-regulated in transformed cells. The tropomyosin molecules played a dual role of both mechanical and chemical regulation of actin monomers (Honda *et al.*, 1996). All TPMs bind to actin with varying affinities and the precise function of each isoforms remain largely unknown. In our study, comparison between cells cultured on gelatinous gels and TCPS revealed the changes in the expression of TPMs family,

emphasizing the effect of mechanical microenvironment to the CSKs. From these observations, the predicted pathway illustrated how the mechanical signal affect CSKs and transduce message to the downstream effector molecules. With the additional verification approach, the identified networks do provide a useful potential pathway for future studies of these relationships

The proteomic expression profiles of the major CSK proteins show a dependency on the substrate elasticity analyzed by 2D-DIGE. This suggests that the expression levels of CSK proteins appear to be related to structural features and mechanical balancing of MTs, MFs, and IFs. Our data suggests that the mechanical conditions (stiffness) of ECM influence intracellular tension through CSK architecture (likely through focal adhesion regulation), thus contributing to cell shape determination. The most plausible explanation for this manner of CSK/ stiffness relationship to control intracellular tension balance is cellular tensegrity as proposed by Ingber (Ingber, 2008). The cellular tensegrity theory states that MF (tensional unit), IF (tensional unit), and MT (anti-compressive struts) form a stable total CSK architecture realizing tensional integrity under the dynamical regulation of a mechanical balance with ECM (Ingber, 2003). In deed, from CSK disruption experiments using drugs, it has been shown that MT disruption by colchicine induces an increase in tractional force for ECM due to compensation balancing for remained tensional stress from higher fraction of the actin (Danowski, 1989; Kolodney and Wysolmerski, 1992; Kolodney and Elson, 1995; Wang *et al.*, 2001). In contrast, depolymerization of F-actin by cytochalasin is associated with a decrease in the tractional force (Kolodney and Wysolmerski, 1992; Eckes *et al.*, 1998). IFs disruption by acrylamide reduce cell stiffness and prestress (Wang and Stamenovic, 2000), inducing decrease in traction force. Further quantification of CSKs might provide a better understanding of how the substrate stiffness modulates the CSK organization in correlation with cellular tensegrity balance.

In our results, increase in elasticity of the gel surface was associated with down-regulation of α -tubulin and up-regulation of vimentin. Since the gel surface with higher elasticity modulus bears larger traction force from cells (Wang *et al.*, 2000), contribution to intracellular prestress from the tensional units such as MF and IF should be increased to balance with the higher anti-tractional force generated on gel surface, while the compressive units of MT may be reduced due to its relatively lowered contribution to the prestress. This means that substrate mechanics could modulate cellular prestress, tensegrity balance by regulation of the amount of CSK monomers supplied to produce filamentous proteins. We hypothesized that our results suggest that the substrate-stiffness-dependent mechanotransduction in MSCs, which have been shown to control the fate of the cells (McBeath *et al.*, 2004; Engler *et al.*, 2006; Kilian *et al.*, 2010; McMurray *et al.*, 2011), may be, at least partially, related to the tensegrity behaviors of

their CSK components.

It should be noted that in our system, we could be able to detect lineage specification marker of stem cells cultured on gel (Fig. S6). The expression of early neurogenic marker β 3 tubulin and the early osteogenic marker Runx2 was highest on the soft and hard gels, respectively. These results indicated that the gel stiffness could initially guide the stem cells fate. However, from DIGE analysis after 3 weeks culture, it was not clear whether the cells we studied at this time point could reach terminal differentiation or not. Limited expression of the late markers for differentiation also reported in matrix elasticity induced stem cell differentiation (Engler *et al.*, 2006) as the expression of some terminal markers such as lineage specific integrin of myoblast-like cells was not evidenced. In our study, for the cells on the hard gels, protein related to collagen synthesis during osteogenic differentiation and osteogenic marker such as P4HA (Pihlajaniemi *et al.*, 1991) and collagen I were still down-regulated. As the changes in expression abundance of the differentiating cells respond to mechanical stimuli appeared to be time dependent (Kantawong *et al.*, 2009c), further investigation of proteomic profiles of cells culture on gels at different time point will provide a better understanding of dynamic of protein changes upon differentiation.

Conclusion

Proteomic analysis of MSCs cultured on gelatinous hydrogels with tuned surface elasticity was performed by 2D-DIGE. Large changes in the abundance of CSK proteins was noted, in agreement with alterations in CSK organization. These results suggested that the substrate stiffness significantly affects expression balances in cytoskeletal proteins of MSCs with some implications to cellular tensegrity.

Acknowledgments. The authors sincerely thank Prof. Takehisa Matsuda of Kanazawa Institute of Technology, Japan, for his assistance with the synthesis of styrenated gelatins. We thank to Mr Yusuke Shinohara, Dr. Takahito Kawano, Dr. Tatsuya Okuda from Kyushu University and Dr. Kamburapola Jayawardena from University of Glasgow for their technical assistance. This work was supported by the following grants: Management Expenses Grants for National Universities Corporations “Nano-Macro Materials, Devices and System Research Alliance from” from the Ministry of Education, Culture, Sports, Science and Technology (MEXT) of Japan, the PRESTO program “Nanosystems and Emergent Functions” from the Japan Science Technology (JST) Agency, and Funding Program for World-Leading Innovative R&D on Science and Technology “Innovative NanoBiodevice based on Single Molecule Analysis” from Cabinet Office, Government Of Japan.

References

- Abdallah, B.M., Haack-Sorensen, M., Burns, J.S., Elsnab, B., Jakob, F., Hokland, P., and Kassem, M. 2005. Maintenance of differentiation potential of human bone marrow mesenchymal stem cells immortalized by human telomerase reverse transcriptase gene despite [corrected] extensive proliferation. *Biochem. Biophys. Res. Commun.*, **326**: 527–538.

- Aitken, A., Jones, D., Soneji, Y., and Howell, S. 1995. 14-3-3 proteins: biological function and domain structure. *Biochem. Soc. Trans.*, **23**: 605–611.
- Arora, P.D., Narani, N., and McCulloch, C.A. 1999. The compliance of collagen gels regulates transforming growth factor-beta induction of alpha-smooth muscle actin in fibroblasts. *Am. J. Pathol.*, **154**: 871–882.
- Ben-Ze'ev, A. 1983. Cell configuration-related control of vimentin biosynthesis and phosphorylation in cultured mammalian cells. *J. Cell Biol.*, **97**: 858–865.
- Benoit, D.S., Schwartz, M.P., Durney, A.R., and Anseth, K.S. 2008. Small functional groups for controlled differentiation of hydrogel-encapsulated human mesenchymal stem cells. *Nat. Mater.*, **7**: 816–823.
- Bheda, A., Gullapalli, A., Caplow, M., Pagano, J.S., and Shackelford, J. 2010. Ubiquitin editing enzyme UCH L1 and microtubule dynamics: implication in mitosis. *Cell Cycle*, **9**: 980–994.
- Bianco, P., Riminucci, M., Gronthos, S., and Robey, P.G. 2001. Bone marrow stromal stem cells: nature, biology, and potential applications. *Stem Cells*, **19**: 180–192.
- Callister, W. and Rethwisch, D. 2000. Fundamentals of Materials Science and Engineering: An Interactive E-Text, Wiely, Somerset, NJ, ed.5
- Cleveland, D.W., Lopata, M.A., MacDonald, R.J., Cowan, N.J., Rutter, W.J., and Kirschner, M.W. 1980. Number and evolutionary conservation of alpha- and beta-tubulin and cytoplasmic beta- and gamma-actin genes using specific cloned cDNA probes. *Cell*, **20**: 95–105.
- Curran, J.M., Chen, R., and Hunt, J.A. 2005. Controlling the phenotype and function of mesenchymal stem cells *in vitro* by adhesion to silane-modified clean glass surfaces. *Biomaterials*, **26**: 7057–7067.
- Curran, J.M., Stokes, R., Irvine, E., Graham, D., Amro, N.A., Sanedrin, R.G., Jamil, H., and Hunt, J.A. 2010. Introducing dip pen nanolithography as a tool for controlling stem cell behaviour: unlocking the potential of the next generation of smart materials in regenerative medicine. *Lab. Chip.*, **10**: 1662–1670.
- Dalby, M.J., Gadegaard, N., Tare, R., Andar, A., Riehle, M.O., Herzyk, P., Wilkinson, C.D., and Oreffo, R.O. 2007. The control of human mesenchymal cell differentiation using nanoscale symmetry and disorder. *Nat. Mater.*, **6**: 997–1003.
- Danowski, B.A. 1989. Fibroblast contractility and actin organization are stimulated by microtubule inhibitors. *J. Cell Sci.*, **93** (Pt 2): 255–266.
- Davies, P.F., Barbee, K.A., Volin, M.V., Robotewskyj, A., Chen, J., Joseph, L., Griem, M.L., Wernick, M.N., Jacobs, E., Polacek, D.C., dePaola, N., and Barakat, A.I. 1997. Spatial relationships in early signaling events of flow-mediated endothelial mechanotransduction. *Annu. Rev. Physiol.*, **59**: 527–549.
- Discher, D.E., Janmey, P., and Wang, Y.L. 2005. Tissue cells feel and respond to the stiffness of their substrate. *Science*, **310**: 1139–1143.
- Eckes, B., Dogic, D., Colucci-Guyon, E., Wang, N., Maniotis, A., Ingber, D., Merckling, A., Langa, F., Aumailley, M., Delougee, A., Koteliensky, V., Babinet, C., and Krieg, T. 1998. Impaired mechanical stability, migration and contractile capacity in vimentin-deficient fibroblasts. *J. Cell Sci.*, **111** (Pt 13): 1897–1907.
- Engler, A.J., Sen, S., Sweeney, H.L., and Discher, D.E. 2006. Matrix elasticity directs stem cell lineage specification. *Cell*, **126**: 677–689.
- Evans, N.D., Minelli, C., Gentleman, E., LaPointe, V., Patankar, S.N., Kallivretaki, M., Chen, X., Roberts, C.J., and Stevens, M.M. 2009. Substrate stiffness affects early differentiation events in embryonic stem cells. *Eur. Cell Mater.*, **18**: 1–13; discussion 13–14.
- Gilbert, P.M., Havenstrite, K.L., Magnusson, K.E., Sacco, A., Leonardi, N.A., Kraft, P., Nguyen, N.K., Thrush, S., Lutolf, M.P., and Blau, H.M. 2010. Substrate Elasticity Regulates Skeletal Muscle Stem Cell Self-Renewal in Culture. *Science*, **329**: 1078–1081.
- Grabowski, E.F., Jaffe, E.A., and Weksler, B.B. 1985. Prostacyclin production by cultured endothelial cell monolayers exposed to step increases in shear stress. *J. Lab. Clin. Med.*, **105**: 36–43.
- Herzt, H. 1881. Ueber die Berührung fester elastischer Körper. *J. Reine. Angew. Mathematik*, **92**: 156–171.
- Hill, P.B., Martin, R.J., and Miller, H.R. 1996. Characterization of whole-cell currents in mucosal and connective tissue rat mast cells using amphotericin-B-perforated patches and temperature control. *Pflugers. Arch.*, **432**: 986–994.
- Honda, H., Kitano, Y., Hatori, K., and Matsuno, K. 1996. Dual role of tropomyosin on chemically modified actin filaments from skeletal muscle. *FEBS letters*, **383**: 55–58.
- Hubchak, S.C., Runyan, C.E., Kreisberg, J.I., and Schnaper, H.W. 2003. Cytoskeletal rearrangement and signal transduction in TGF-beta1-stimulated mesangial cell collagen accumulation. *J. Am. Soc. Nephrol.*, **14**: 1969–1980.
- Ingber, D.E. 2003. Tensegrity I. Cell structure and hierarchical systems biology. *J. Cell Sci.*, **116**: 1157–1173.
- Ingber, D.E. 2008. Tensegrity-based mechanosensing from macro to micro. *Prog. Biophys. Mol. Biol.*, **97**: 163–179.
- Jung, Y., Kim, S.H., Kim, S.H., Kim, Y.H., Xie, J., Matsuda, T., and Min, B.G. 2008. Cartilaginous tissue formation using a mechano-active scaffold and dynamic compressive stimulation. *J. Biomater. Sci. Polym.*, **Ed 19**: 61–74.
- Kantawong, F., Burchmore, R., Gadegaard, N., Oreffo, R.O., and Dalby, M.J. 2009a. Proteomic analysis of human osteoprogenitor response to disordered nanotopography. *J. Royal Soc. Interface*, **6**: 1075–1086.
- Kantawong, F., Burchmore, R., Wilkinson, C.D., Oreffo, R.O., and Dalby, M.J. 2009b. Differential in-gel electrophoresis (DIGE) analysis of human bone marrow osteoprogenitor cell contact guidance. *Acta biomaterialia*, **5**: 1137–1146.
- Kantawong, F., Burgess, K.E., Jayawardena, K., Hart, A., Burchmore, R.J., Gadegaard, N., Oreffo, R.O., and Dalby, M.J. 2009c. Whole proteome analysis of osteoprogenitor differentiation induced by disordered nanotopography and mediated by ERK signalling. *Biomaterials*, **30**: 4723–4731.
- Kantawong, F., Burgess, K.E., Jayawardena, K., Hart, A., Riehle, M.O., Oreffo, R.O., Dalby, M.J., and Burchmore, R. 2011. Effects of a surface topography composite with puerariae radix on human STRO-1-positive stem cells. *Acta biomaterialia*, **6**: 3694–3703.
- Kassem, M., Kristiansen, M., and Abdallah, B.M. 2004. Mesenchymal stem cells: cell biology and potential use in therapy. *Basic Clin. Pharmacol. Toxicol.*, **95**: 209–214.
- Kawano, T. and Kidoaki, S. 2011. Elasticity boundary conditions required for cell mechanotaxis on microelastically-patterned gels. *Biomaterials*, **32**: 2725–2733.
- Kidoaki, S. and Matsuda, T. 2008. Microelastic gradient gelatinous gels to induce cellular mechanotaxis. *J. Biotechnol.*, **133**: 225–230.
- Kilian, K.A., Bugarija, B., Lahn, B.T., and Mrksich, M. 2010. Geometric cues for directing the differentiation of mesenchymal stem cells. *Proc. Natl. Acad. Sci. USA*, **107**: 4872–4877.
- Kocgozlu, L., Lavalley, P., Koenig, G., Senger, B., Haikel, Y., Schaaf, P., Voegel, J.C., Tenenbaum, H., and Vautier, D. 2010. Selective and uncoupled role of substrate elasticity in the regulation of replication and transcription in epithelial cells. *J. Cell Sci.*, **123**: 29–39.
- Kolodney, M.S. and Wysolmerski, R.B. 1992. Isometric contraction by fibroblasts and endothelial cells in tissue culture: a quantitative study. *J. Cell Biol.*, **117**: 73–82.
- Kolodney, M.S. and Elson, E.L. 1995. Contraction due to microtubule disruption is associated with increased phosphorylation of myosin regulatory light chain. *Proc. Natl. Acad. Sci. USA*, **92**: 10252–10256.
- Korenaga, R., Ando, J., Tsuboi, H., Yang, W., Sakuma, I., Toyo-oka, T., and Kamiya, A. 1994. Laminar flow stimulates ATP- and shear stress-dependent nitric oxide production in cultured bovine endothelial cells. *Biochem. Biophys. Res. Commun.*, **198**: 213–219.
- Lo, C.M., Wang, H.B., Dembo, M., and Wang, Y.L. 2000. Cell movement

- is guided by the rigidity of the substrate. *Biophys. J.*, **79**: 144–152.
- Matesic, D., Attardi, B., Dellovade, T., Pfaff, D., and Germak, J. 1997. Differential LHRH secretion, dye coupling, and protein expression in two morphologically distinct cell types identified in GT1-7 cultures. *J. Neuroendocrinol.*, **9**: 467–478.
- McBeath, R., Pirone, D.M., Nelson, C.M., Bhadriraju, K., and Chen, C.S. 2004. Cell shape, cytoskeletal tension, and RhoA regulate stem cell lineage commitment. *Dev. Cell*, **6**: 483–495.
- McMurray, R.J., Gadegaard, N., Tsimbouri, P.M., Burgess, K.V., McNamara, L.E., Tare, R., Murawski, K., Kingham, E., Oreffo, R.O., and Dalby, M.J. 2011. Nanoscale surfaces for the long-term maintenance of mesenchymal stem cell phenotype and multipotency. *Nat. Mater.*, **10**: 637–644.
- Milner, P., Kirkpatrick, K.A., Ralevic, V., Toothill, V., Pearson, J., and Burnstock, G. 1990. Endothelial cells cultured from human umbilical vein release ATP, substance P and acetylcholine in response to increased flow. *Proc. Biol. Sci.*, **241**: 245–248.
- Mooney, D.J., Hansen, L.K., Langer, R., Vacanti, J.P., and Ingber, D.E. 1994. Extracellular matrix controls tubulin monomer levels in hepatocytes by regulating protein turnover. *Mol. Biol. Cell*, **5**: 1281–1288.
- Nilius, B., Eggermont, J., Voets, T., and Droogmans, G. 1996. Volume-activated Cl-channels. *Gen. Pharmacol.*, **27**: 1131–1140.
- Oh, S., Brammer, K.S., Li, Y.S., Teng, D., Engler, A.J., Chien, S., and Jin, S. 2009. Stem cell fate dictated solely by altered nanotube dimension. *Proc. Natl. Acad. Sci. USA*, **106**: 2130–2135.
- Okino, H., Nakayama, Y., Tanaka, M., and Matsuda, T. 2002. *In situ* hydrogelation of photocurable gelatin and drug release. *J. Biomed. Mater. Res.*, **59**: 233–245.
- Pelham, R.J., Jr. and Wang, Y. 1997. Cell locomotion and focal adhesions are regulated by substrate flexibility. *Proc. Natl. Acad. Sci. USA*, **94**: 13661–13665.
- Peyton, S.R., Raub, C.B., Keschrumrus, V.P., and Putnam, A.J. 2006. The use of poly(ethylene glycol) hydrogels to investigate the impact of ECM chemistry and mechanics on smooth muscle cells. *Biomaterials*, **27**: 4881–4893.
- Pihlajaniemi, T., Myllyla, R., and Kivirikko, K.I. 1991. Prolyl 4-hydroxylase and its role in collagen synthesis. *J. hepatol.*, **13** Suppl 3: S2–7.
- Pittenger, M.F., Mackay, A.M., Beck, S.C., Jaiswal, R.K., Douglas, R., Mosca, J.D., Moorman, M.A., Simonetti, D.W., Craig, S., and Marshak, D.R. 1999. Multilineage potential of adult human mesenchymal stem cells. *Science*, **284**: 143–147.
- Reijnders, C.M., Bravenboer, N., Holzmann, P.J., Bhoelan, F., Blankenstein, M.A., and Lips, P. 2007. *In vivo* mechanical loading modulates insulin-like growth factor binding protein-2 gene expression in rat osteocytes. *Calcif. Tissue Int.*, **80**: 137–143.
- Rowlands, A.S., George, P.A., and Cooper-White, J.J. 2008. Directing osteogenic and myogenic differentiation of MSCs: interplay of stiffness and adhesive ligand presentation. *Am. J. Physiol. Cell Physiol.*, **295**: C1037–1044.
- Saha, K., Keung, A.J., Irwin, E.F., Li, Y., Little, L., Schaffer, D.V., and Healy, K.E. 2008. Substrate modulus directs neural stem cell behavior. *Biophys. J.*, **95**: 4426–4438.
- Schlunck, G., Han, H., Wecker, T., Kampik, D., Meyer-ter-Vehn, T., and Grehn, F. 2008. Substrate rigidity modulates cell matrix interactions and protein expression in human trabecular meshwork cells. *Invest. Ophthalmol. Vis. Sci.*, **49**: 262–269.
- Seib, F.P., Prewitz, M., Werner, C., and Bornhauser, M., 2009. Matrix elasticity regulates the secretory profile of human bone marrow-derived multipotent mesenchymal stromal cells (MSCs). *Biochem. Biophys. Res. Commun.*, **389**: 663–667.
- Shah, V., Bharadwaj, S., Kaibuchi, K., and Prasad, G.L. 2001. Cytoskeletal organization in tropomyosin-mediated reversion of ras-transformation: Evidence for Rho kinase pathway. *Oncogene*, **20**: 2112–2121.
- Shedden, I.N. 1965. The relation between load and penetration in the axisymmetric Boussinesq problem for a punch of arbitrary profile. *Int. J. Eng. Sci.*, **3**: 47–57.
- Smith, R.L., Donlon, B.S., Gupta, M.K., Mohtai, M., Das, P., Carter, D.R., Cooke, J., Gibbons, G., Hutchinson, N., and Schurman, D.J. 1995. Effects of fluid-induced shear on articular chondrocyte morphology and metabolism *in vitro*. *J. Orthop. Res.*, **13**: 824–831.
- Suginta, W., Karoulias, N., Aitken, A., and Ashley, R.H. 2001. Chloride intracellular channel protein CLIC4 (p64H1) binds directly to brain dynamin I in a complex containing actin, tubulin and 14-3-3 isoforms. *Biochem. J.*, **359**: 55–64.
- van Hemert, M.J., Steensma, H.Y., and van Heusden, G.P. 2001. 14-3-3 proteins: key regulators of cell division, signalling and apoptosis. *Bioessays*, **23**: 936–946.
- Wang, H.B., Dembo, M., and Wang, Y.L. 2000. Substrate flexibility regulates growth and apoptosis of normal but not transformed cells. *Am. J. Physiol. Cell Physiol.*, **279**: C1345–1350.
- Wang, N., Butler, J.P., and Ingber, D.E. 1993. Mechanotransduction across the cell surface and through the cytoskeleton. *Science*, **260**: 1124–1127.
- Wang, N. and Stamenovic, D. 2000. Contribution of intermediate filaments to cell stiffness, stiffening, and growth. *Am. J. Physiol. Cell Physiol.*, **279**: C188–194.
- Wang, N., Naruse, K., Stamenovic, D., Fredberg, J.J., Mijailovich, S.M., Tolic-Norrelykke, I.M., Polte, T., Mannix, R., and Ingber, D.E. 2001. Mechanical behavior in living cells consistent with the tensegrity model. *Proc. Natl. Acad. Sci. USA*, **98**: 7765–7770.
- Winer, J.P., Janmey, P.A., McCormick, M.E., and Funaki, M. 2009a. Bone marrow-derived human mesenchymal stem cells become quiescent on soft substrates but remain responsive to chemical or mechanical stimuli. *Tissue Eng. Part A*, **15**: 147–154.
- Winer, J.P., Oake, S., and Janmey, P.A. 2009b. Non-linear elasticity of extracellular matrices enables contractile cells to communicate local position and orientation. *PLoS One*, **4**: e6382.

(Received for publication, April 25, 2012, accepted, August 22, 2012 and published online, August 31, 2012)