

Modification of Pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with Solid State Reaction Method using a Mechanical Milling

Y Sarwanto and W A Adi

Centre for Science and Technology of Advanced Materials, BATAN, Kawasan Puspiptek Serpong Tangerang Selatan Banten, Indonesia

Email: yosef@batan.go.id

Abstract. Modification of pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with solid state reaction method using a mechanical milling has been synthesized. Raw materials used to prepare these samples were Fe_2O_3 , MnCO_3 , and TiO_2 . Fe_2O_3 and TiO_2 powders (ratio of 1:1) were mixed with MnCO_3 powder at various composition of $x = 0; 0.1; 0.2; 0.3; 0.4; 0.5$; and 1, which each composition was added with 50 ml ethanol and then milled for 5 hours through high energy milling, after that sintered at 1000°C for 5 hours by using box furnace. The phases of $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ were measured by using X-ray diffraction (XRD) and then identified by using Match program. The crystal structure was analyzed by using the program of General Structure Analysis System (GSAS). Quality fitting of Rwp and χ^2 (chi-squared) are relatively good because based on the curve of normalized error distribution looks just left background and its normal probability plot shows the value of comparable between observation and expectation. The refinement analyses of X-ray diffraction patterns showed that the samples formed single phase for $x \leq 0.3$. However, the samples of $x > 0.3$ were multi-phases. The single phase of sample had composition of pseudobrookite Fe_2TiO_5 with orthorhombic structure, space group of $Cmcm$ (63), the lattice parameters of $a = 3.7390 \text{ \AA}$, $b = 9.7790 \text{ \AA}$, and $c = 9.9780 \text{ \AA}$, $\alpha = \beta = \gamma = 90^\circ$, $V = 364.83 \text{ \AA}^3$, and $\rho = 4.360 \text{ g.cm}^{-3}$. Meanwhile, the other phase analysis for the composition of $x > 0.3$ is bixbyite (FeMnO_3). The bixbyite has a cubic structure, under the space group of $Ia-3$ (206), the lattice parameters of $a = b = c = 9.40 \text{ \AA}$, $\alpha = \beta = \gamma = 90^\circ$, $V = 830.58 \text{ \AA}^3$, and $\rho = 5.078 \text{ g.cm}^{-3}$.

Keywords: Pseudobrookite, $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$, Milling, Modification, Crystal Structure.

1. Introduction

Absorber materials of electromagnetic waves is now becoming one of the interesting topics to be studied and understood for electronic application [1,2]. The main requirement needed as a material absorbing electromagnetic waves is the presence of intrinsic characteristics, namely magnetic loss and dielectric loss on the materials. At first, the absorber materials developed until now are a carbon-based material that has a high dielectric loss [3]. However, recently it is found that many studies of electromagnetic wave absorber materials began to lead to the use of magnetic materials [4-5]. This study has done structure engineering on the paramagnetic material of pseudobrookite Fe_2TiO_5 -based. The main reason for choosing this system is the magnetic material has a stable structure up to high temperatures. Pseudobrookite Fe_2TiO_5 may also be obtained from the phase transformation of ilmenite (FeTiO_3) [6-7], while ilmenite itself can be obtained from the iron sand where their reserves is very



large in Indonesia. Therefore, this material becomes an excellent product at low price as well as the raw materials are easily obtained.

Pseudobrookite Fe_2TiO_5 previously can be used for multiple applications such as microelectronics materials, gas sensors, non-linear optics, magnetic applications, filter optics, photocatalyst, photoelectrode, anode batteries, pigments, and a membrane at high temperatures for fuel cell applications [8-10]. Thus the application of Pseudobrookite Fe_2TiO_5 material is very wide and makes this material is one of the multi-functional materials, so the further understanding of this material is very interesting to study. Previous research has carried out preliminary studies about the effect of composition on the phase and parameter of crystal structure pseudobrookite $\text{Fe}_{2-x}\text{Ti}_{1+x}\text{O}_5$ [11]. This research conducted modification through structural engineering on the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ materials by solid-state reaction using a wet milling process. The addition of nickel (Mn) atoms is expected able to replace most of the position of the iron (Fe) atoms so that the interaction between the magnetic spin Fe^{3+} ions with Mn^{3+} occur it and can affect the magnetic properties of this material. Thus, the aim of this study is to synthesize and characterize pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ material with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$ and 1). The discussion will be focused on the analysis of the crystal structure (phase and parameter structures), the morphology of particles and primary content of the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ due to the addition of Mn atoms in the system.

2. Experimental Method

Pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ was synthesized by solid state reaction method with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1). The raw materials used were Fe_2O_3 , TiO_2 (anatase) and MnCO_3 . The three materials were weighed according to the calculation of stoichiometric composition, then mixed and placed in a media made of stainless steel. Once it was added with ethanol and balls also made of stainless steel with a mass ratio between the balls and the material are $1:2$. The mixture was then milled for 5 hours by using high energy milling equipment of Spex8000. The mixture of milling result was then dried and compacted with a pressure of 5000 psi. Furthermore, the samples were sintered at 1000°C for 5 hours in a furnace.

Crystalline phase identification was measured by X-ray diffractometer (XRD), Pan Analytical. Measurement of the diffraction pattern by using X-ray tube with a wavelength of $\lambda = 1.5406 \text{ \AA}$, mode: continuous scan, step size: 0.02° , and time per step: 0.5 seconds and qualitative-quantitative phases analysis formed in the sample was used by GSAS (General Structure Analysis System) software. Meanwhile, the particle morphology was observed by using transmission electron microscope (TEM) of JEOL brand.

3. Results and Discussion

Figure 1 shows the results of measurements of X-ray diffraction pattern of the sample pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1). Based on the results of phase identification appears that the reaction successfully formed a single phase $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ on the composition of $x = 0.1 - 0.3$, while for the composition of $x > 0.3$, the sample could not react perfectly so the sample consisted of two phases, namely phases of $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ and FeMnO_3 . Results of phase identification are fascinating to understand because for $x = 0.1 - 0.3$ show that atoms of manganese have succeeded in substituting partially of the atoms Fe in the structure $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$, and for $x > 0.3$ is thought to occur reaction imbalance when the amount of Fe content was reduced, the Mn content increased. In Figure 1 we can see that the increasing Mn content ($x > 0.3$) in the sample caused the phases of FeMnO_3 increased as well. Thus, it required further analysis to determine the changes in the crystal structure parameters, the amount of mass fraction formed, and cationic distribution on the results of substitution Mn into the Fe atom as shown in Figure 2.




Figure 1. X-ray diffraction pattern of the sample of pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1)

Figure 2 shows the results of refinement X-ray diffraction pattern of the sample pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with the variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1).




Figure 2. The refinement results of XRD pattern of the sample pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$

Figure 2(a – c) show the results of refinement of the XRD patterns for $x = 0.1 - 0.3$ that formed Bragg diffraction peaks with a single phase following the Fe_2TiO_5 structure. Figure 2(d – f) show the results of refinement of the XRD patterns for $x = 0.4 - 1.0$ that formed Bragg diffraction peaks with a multi-phases, which follows the structure of Fe_2TiO_5 and FeMnO_3 . Qualitative and quantitative analysis refers to the Crystallography Open Database with the card number (COD: 1011342) and (COD: 9008068) respective for phases of Fe_2TiO_5 and FeMnO_3 .

Refinement complete summary of the X-ray diffraction pattern results of the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ sample with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1) for all of samples is shown in Table 1.

Table 1. The value of structure parameters, criteria of fit (R_{wp}), the goodness of fit (χ^2) and the mass fraction of phase formed in the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ sample with the variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1).

Mn (x)	Phase	Lattice parameter (Å)			V (Å ³)	ρ (g/cm ³)	Fraction wt%	R_{wp} (%)	χ^2
		a	b	c					
0 [11]	Fe_2TiO_5	3.7188(4)	9.7569(1)	9.9466(1)	360.90(2)	4.360	100.00	-	-
0.1	Fe_2TiO_5	3.7254(1)	9.7766(4)	9.9636(4)	362.89(3)	4.297	100.00	3.29	1.25
0.2	Fe_2TiO_5	3.7287(2)	9.7790(6)	9.9634(6)	363.30(5)	4.292	100.00	3.42	1.29
0.3	Fe_2TiO_5	3.7292(2)	9.7791(6)	9.9636(5)	363.36(4)	4.291	100.00	3.45	1.31
0.4	Fe_2TiO_5	3.7304(2)	9.7795(6)	9.9647(6)	363.52(5)	4.288	95.04	3.45	1.32
	FeMnO_3	9.4310(1)	9.4310(1)	9.4310(1)	838.84(1)	5.030	4.96		
0.5	Fe_2TiO_5	3.7311(1)	9.7805(5)	9.9649(5)	363.63(4)	4.283	87.64	3.54	1.30
	FeMnO_3	9.4372(1)	9.4372(1)	9.4372(1)	840.48(4)	5.035	12.36		
1	Fe_2TiO_5	3.7318(9)	9.7811(5)	9.9654(5)	363.74(4)	4.281	72.54	3.65	1.31
	FeMnO_3	9.4379(7)	9.4379(7)	9.4379(7)	840.69(2)	5.018	27.46		

Figure 2 and Table 1 show that the refinement results of X-ray diffraction pattern have a very good fitting quality based on the criteria of fit (R_{wp}) and the goodness of fit (χ^2) in accordance with the agreement [12]. Table 2 shows that based on the refinement pattern of X-ray diffraction pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ samples with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1), the samples having a single phase are in the composition of $x = 0.1 - 0.3$. Data supporting the other is from the analysis of changes in the volume of the unit cell as shown in Figure 3.




Figure 3. The volume of unit cells as a function of composition

In Figure 3(a) it appears that when composition x increased, the expansion of unit cell volume occurred up to $x = 0.3$. After that, the composition ($x > 0.3$) under net saturation. This phenomenon was due to the atomic radius of Mn ($r = 1.79 \text{ \AA}$) was longer than the atomic radius of Fe ($r = 1.72 \text{ \AA}$). Thus it resulted in lattice parameter which also increased for the third axis. Then, for the composition $x > 0.3$, the unit cell volume gradually saturated caused by the lattice distortion and by the presence of another phase formed. The addition of Mn excess ($x > 0.3$) resulted in an imbalance of the reaction so that Mn preferred to bind Fe to form Ferromanganite since the composition of these compounds was relatively stable compared with $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$. Meanwhile, another Fe will bind to Mn forming FeMnO_3 . Figure 3 (b) shows that on the composition of $x > 0.3$, there was no change in the unit cell volume on the phases of FeMnO_3 . It means that Mn had reacted with Fe to form FeMnO_3 . This phenomenon can be explained accordance to the results of the analysis of mass fractions as shown in Figure 4.

These refinement results are also supported by observations of the surface morphology of particles for both single phases using transmission electron microscope (TEM) as shown in Figure 3. Figure 3 shows that the particle morphology of the composition of $x = 0.3$ had a good particle homogeneity and uniform in across the sample surface with a polygonal particle shape and the particle size varied from 20 – 100 nm. In general, a single phase characteristic of polycrystalline samples by observation of TEM image is homogeneity and uniformity particle shape in across the sample surface.




Figure 4. The particle morphology of the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ ($x = 0.3$) by TEM

The presence of this Mn can be proven based on the result of EDS (Energy Dispersive Spectroscopy) data as shown in Figure 5 and Table 2.




Figure 5. EDS spectrum of the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ ($x = 0.3$)

The interesting thing is both materials have a single phase with the same structure, but their compositions are different. On the composition of $x = 0.3$, there was a 0.3 % Mn atoms succeeded substituting partially Fe atoms. Thus, the substitution of Mn into Fe on pseudobrookite Fe_2TiO_5 system was only capable of 0.3 at.% without changing the crystal structure of the material.

Table 2. Element distribution on the $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ ($x = 0.3$) measured by EDS.

Element	Energy (keV)	Mass fraction (%)	
		wt.%	at.%
O	0.525	17.63	41.61
Ti	4.508	23.35	18.40
Mn	5.894	7.61	5.23
Fe	6.398	52.41	34.75

4. Conclusion

Synthesis of pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ with variations in composition ($x = 0.1, 0.2, 0.3, 0.4, 0.5$, and 1) has been successfully carried out. The refinement pattern of X-ray diffraction samples of pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ shows that the sample has a single phase in the composition of $x = 0.1 - 0.3$. The particle morphology of the composition of $x = 0.1 - 0.3$ has a good particle homogeneity and is uniform in across the sample surface with a polygonal particle shape, and the particle size varies. Thus, substitution of Mn into Fe on the pseudobrookite $\text{Fe}_{2-x}\text{Mn}_x\text{TiO}_5$ is only capable of 0.3 at.% without changing the crystal structure of the material.

5. References

- [1]. Eswaraiah V, Sankaranarayanan V and Ramaprabhu S 2011 Functionalized Graphene–PVDF Foam Composites for EMI Shielding *Macromol. Mater. Eng.* **296** 1-5.
- [2]. Wu Z and Li M 2011 Electromagnetic interference shielding of carbon nanotube macrofilms *Scripta Mater* **64** 809-12
- [3]. Wang X 2011 Investigation of Electromagnetic Shielding Effectiveness of Nanostructural Carbon Black/ABS Composites *Journal of Electromagnetic Analysis and Applications* **3** 160-164.
- [4]. Zhang S, Cao Q 2012 Electromagnetic and microwave absorption performance of some transition metal doped $\text{La}_{0.7}\text{Sr}_{0.3}\text{Mn}_{1-x}\text{TM}_x\text{O}_{3\pm 1}$ (TM = Fe, Co or Ni) *Materials Science and Engineering B* **177** 678–684.
- [5]. Adi W A and Manaf A 2012 Structural and Absorption Characteristics of Mn-Ti Substituted Ba-Sr Hexaferrite Synthesized by Mechanical Alloying Route *Journal of Basic and Applied Scientific Research* **2** (8) 7826-7834.
- [6]. Xiao W, Lu X, Zou X, Wei X and Ding W 2013 Phase Transitions, Micro-Morphology and its Oxidation Mechanism in Oxidation of Ilmenite (FeTiO_3) Powder., *Trans. Nonferrous Met. Soc. China* **23** 2439–2445.
- [7]. Rochman N T and Adi W A 2013 Preliminary study of the development of absorber electromagnetic wave materials by modifying iron sand. *International Journal of Academic Research Part A* **5**(4) 91-96.
- [8]. Jin L and Zhou 2013 Electronic structures and optic properties of Fe_2TiO_5 using LSDA+U approach *Progress in Natural Science Materials International* **23** (4) 413–419.
- [9]. Khosravi E, Razi M K and Enhessari M 2012 Photocatalytic and Magnetic Behavior of Fe_2TiO_5 -5A Zeolite Nanocomposites *Int. J. Bio-Inorg. Hybd. Nanomat* Vol. 1 No. 2 115-122.
- [10]. Houshyari K, Javanbakht M, Naji L and Enhessari M 2012 Physical and Electrochemical Study of Nafion/ Fe_2TiO_5 Nanocomposite Membranes for High Temperature PEM Fuel Cells *Proceedings of the 4th International Conference on Nanostructures (ICNS4)* 12-14.
- [11]. Yosef S and Wisnu A A 2015 Effect of Pseudobrookite $\text{Fe}_{2+x}\text{Ti}_{1+x}\text{O}_5$ Composition on the Changes in Phase and Parameter of Crystal Structure *Proc. National Seminar of X-ray and Neutron Scattering* 97-101

- [12]. Toby B H 2001 EXPGUI A Graphical User Interface for GSAS *J. Appl. Crystallogr.* **34** 210-221

Acknowledgments

This work is supported by the program for research and development of smart magnetic material (DIPA 2015), Center for Science and Technology of Advanced Materials, National Nuclear Energy Agency. The authors are thankful to Drs. Bambang Sugeng, for his kind help to characterize using XRD.