

Growth and Magnetic Properties of Ultrathin Fe on Pd(110)

Beatriz Roldan Cuenya,^a J. Pearson, Chengtao Yu, Dongqi Li, and S.D. Bader

*Materials Science Division
Argonne National Laboratory, Argonne, IL 60439*

The submitted manuscript has been created by the University of Chicago as Operator of Argonne National Laboratory ("Argonne") under Contract No. W-31-109-ENG-38 with the U.S. Department of Energy. The U.S. Government retains for itself, and others acting on its behalf, a paid-up, nonexclusive, irrevocable worldwide license in said article to reproduce, prepare derivative works, distribute copies to the public, and perform publicly and display publicly, by or on behalf of the Government.

Submitted for the Proceedings of the 47th International Symposium of the American Vacuum Society, Boston, MA, October 2-6, 2000 (to be published in Journal of Vacuum Science and Technology)

Work supported by the U.S. Department of Energy, Office of Science under contract #W-31-109-ENG-38.

^aPermanent address: Laboratory für Angewandte Physik, Gerhard-Mercator-Universität Duisburg, Germany.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Growth and Magnetic Properties of Ultrathin Fe on Pd(110)

Beatriz Roldan Cuenya,[†] J. Pearson, Chengtao Yu, Dongqi Li^{*} and S. D. Bader

Materials Science Division
Argonne National Laboratory
Argonne, IL 60439

RECEIVED
DEC 08 2000
OSTI

We have investigated the growth and magnetic properties of 0-3 ML (monolayers) Fe on stepped Pd(110) with reflection high-energy electron diffraction (RHEED), low-energy electron diffraction (LEED) and the surface magneto-optic Kerr effect (SMOKE) in order to relate the morphology, structure and magnetic properties in a low-dimensional system. The Fe films, grown at 340 K, are smooth and pseudomorphic up to 1.5 ML, where three-dimensional growth and lateral lattice relaxation ensues. The in-plane row spacing along the [110] decreases by ~ 5-6 % at 3 ML. RHEED oscillations with 1-ML period are observed in the (1,0), (2,0) and the center of the (0,0) streak intensity. The tail of the (0,0) streak at low exit angle, however, has a 0.5-ML period oscillation, which suggests step decoration growth. Submonolayer Fe films remain ferromagnetic above ~ 0.3 ML. The magnetic easy axis is initially perpendicular to the surface and is in-plane for Fe thickness > 1.5 ML. Between 0.9 - 1.2 ML, there appear to be mixed magnetic phases as indicated by an increase in coercivity.

* To whom correspondences should be addressed. Electronic mail: dongqi@anl.gov

I. Introduction

The field of two-dimensional (2D) magnetic ultrathin films and multilayers has advanced both in fundamental science and industrial applications thanks to new magnetic phenomena that occur at small lengthscales.¹ Lower dimensional systems, such quasi-1D magnetic wires, however remains less investigated due to difficulties in fabrication at the length scale < 10 nm. Recently, self-assembly of nanowires has started to attract attention because of its potential in making regular arrays at a length scale beyond the lithographic limit. One approach is to decorate step edges of a vicinal surface by depositing metal atoms.^{2,3,4} Some promising magnetic characterizations have been reported for Fe/W(110)⁵ and Fe/Cu(111)⁶, though the wires are less than perfect.

We choose to study Fe on stepped Pd(110) for several reasons. First, the formation of smooth metallic nanowires requires not only that adatoms diffuse across terraces to stick at step edges, but also enough edge diffusion along the step edges in order to form smooth, straight chains. It is known that initial metal growth on Pd(110) surfaces is highly anisotropic and tends to form nanoscale wires even on flat surfaces.⁷ This would ensure that, on a stepped surface with the edges along the fast diffusing direction, the growth front of the wires would be straight as long as step decoration occurs. Secondly, Pd is known to be nearly magnetic and can have an induced magnetic moment through proximity when placed next to ferromagnetic atoms.⁸ This makes it more likely for the Fe wires to remain ferromagnetic. The magnetic properties of submonolayer Fe on Pd(110), to our knowledge, have not been reported before. In this work, we mainly investigate the growth of Fe on stepped Pd(110) in the 0 – 3 ML region. Smooth, pseudomorphic growth is observed < 1.5 ML, where 3D growth and in-plane lattice relaxation then ensues. The peculiar RHEED oscillations suggest that step decoration occurs. The system remains ferromagnetic down to ~ 0.3 ML and has a magnetic easy axis perpendicular to the substrate at very low coverage.

II. Experimental

The experiments were carried out in an ultrahigh vacuum (UHV) chamber equipped with RHEED, LEED, Auger electron spectroscopy and SMOKE. The stepped Pd(110) was cleaned in UHV by cycles of Ar sputtering at 700 K and annealing at 950 K. We also occasionally annealed the crystal in oxygen at 1×10^{-7} Torr for several minutes to eliminate residual C and S impurities. The resultant substrate and the subsequent Fe films are free of any measurable contamination within the Auger sensitivity. Fe was evaporated with a typical rate of 0.2-0.3 Å/min via electron-beam bombardment of a W crucible filled with pure Fe. The base pressure of the chamber is $\sim 1 \times 10^{-10}$ Torr, and the pressure during deposition was $2-4 \times 10^{-10}$ Torr. Fe wedges of 0 - 3 ML were grown with a slope of $\sim 0.2-0.4$ ML/mm by moving the substrate behind a mask during deposition at 343 K. The ordering of the crystal and the films were confirmed with RHEED and LEED, recorded using a charge-coupled diode (CCD) camera. The images were analyzed digitally to quantify both the changes in atomic spacing along the wedges and the average terrace size of the substrate. Figure 1 shows LEED image of the substrate. The spots are elongated due to the steps along the Pd [110]. While double spots, typical of an ordered stepped surface, are not observed, the asymmetric diffuse scattering of the spots suggest that the average terrace size is about 5-6 atomic rows, or ~ 20 Å. Magnetic properties were studied *in-situ* at ~ 40 K by means of longitudinal and polar SMOKE. A He-Ne laser beam focused to 0.2 mm was used to scan along the wedge to obtain Kerr-ellipticity hysteresis loops for different Fe thicknesses. The height of the loops in remanence denoted M_R is proportional to the remanent magnetization.

III. Results and discussions

Figure 2 shows typical RHEED patterns of the Pd(110) substrate and Fe films at different thickness, where the electron beam is along the [001] of the Pd surface. For both

the clean surface and the Fe films of less than ~ 1.5 ML, sharp streaks are observed, indicating smooth, well-ordered surfaces. Above ~ 1.6 ML, the streaks begin to break up into spots, indicating the initiation of 3D growth. Clear RHEED patterns with similar characteristics, though increasingly spotty and diffuse, are observed at up to 11 ML where the experiment was terminated. The distance among the streaks / spots is proportional to the inverse lattice spacing of the surface and is plotted in Fig. 3. Within the first ~ 1.5 ML, the inverse lattice spacing remains virtually constant, though a small amount of relaxation may occur between 1 – 1.5 ML. Thus, the films are pseudomorphic in this thickness range. Then the inverse lattice spacing starts to increase quickly, which is evidence of structural relaxation of the Fe films. This is consistent with the 3D growth that starts in the same thickness range as shown in Fig. 2. This inverse spacing approaches saturation at ~ 3 ML with a total relaxation of 5-6%. It is interesting to note that such relaxation increases the inverse spacing and therefore decreases the lattice spacing in real space. If we assume the epitaxy is for bcc Fe(110) to match the fcc Pd(110), then pseudomorphic bcc Fe should experience an in-plane strain of $\sim 4.2\%$. Conventional wisdom, therefore, would suggest a relaxation towards the larger bulk Fe lattice constant and smaller inverse spacing, which disagrees with our experimental data. Another possibility is that the initial growth is fcc Fe, whose lattice constant (extrapolated to a room temperature value of 3.59 \AA) is 8% smaller than that of the Pd (3.89 \AA). So a fcc Fe phase at the initial growth would be consistent with the observed lattice relaxation, though it would represent a much larger lattice mismatch than for bcc Fe. A study of Fe growth on Pd(001) suggests that above 10 ML the epitaxial Fe films are body-centered tetragonal; but the researchers could not fit their LEED I/V results at lower coverage.⁹ Our measurements cannot conclusively determine if the initial growth is bcc or fcc Fe.

Figure 4(a) shows a typical set of RHEED oscillations taken at (i) the (1,0) streak and at (ii) the center, and (iii) the tail of the (0,0) streak as marked on Fig. 2. Both (i) and

(ii) show the normal oscillation with 1-ML period in the first 1-2 ML. Similar oscillations are also observed on the (2,0) streak. They indicate initial smooth, layer-by-layer growth of Fe on Pd(110). But (iii), taken at very glancing angle, exhibits an oscillation with a half-ML period up to 1.5 ML. Such behavior can only be observed on the (0,0) streak at the glancing exit angle end closest to the direct beam. It is well known that the phase and intensity of RHEED oscillation should vary at different angle or on different streak. A change in periodicity is, however, difficult to explain by an ordinary layer-by-layer growth mode.

A peak at 0.5 ML was first observed with atom beam scattering by Kern's group on stepped surface.^{3,4} Suppose the starting substrate surface is stepped with a relatively broad terrace width distribution as illustrated in Fig. 4(b). If the adatoms are confined to their landing terrace and diffuse to the step edges to form smooth stripes, then at each given coverage, more atomic rows will appear on wider terraces than on the narrow ones. At around 0.5 ML, all the terraces would be half-filled, giving rise to a much narrower distribution of terrace width as indicated in Fig. 4(b). When intensity oscillations of atom or electron beam are monitored with glancing incidence and exit angles, lateral structure is probed. A peak at 0.5 ML therefore appears in the oscillation due to the change in lateral morphology. The fact that we observe a half-ML oscillation suggests that step decoration occur for this system. The width and spacing of the Fe stripes, however, is likely to have a relatively broad distribution due to irregularities in the substrate.

This system is ferromagnetic down to submonolayer Fe coverage. Figure 5 demonstrates the remanent magnetization measured with polar and longitudinal SMOKE at 42 K. In both sets of measurements, remanent and saturation magnetization remain virtually the same (not shown). Polar Kerr signals are observed for as low as ~ 0.3 ML and persist up to ~ 1.3 ML. They are strongly coverage dependent and peak at ~ 0.6 ML. Normally, for submonolayer films consisting of small islands, ferromagnetic order starts to

appear at island percolation coverage of ~ 0.6 ML. One possibility for a lower ferromagnetic onset in our system is that the nearby Pd atoms could be polarized to make the magnetic islands larger and therefore coalesce earlier. Such an onset for Fe/Pd(001), however, was observed between 0.5-1.0 ML at low temperature, which corresponds to its island percolation seen with STM.¹⁰ This demonstrates that Pd polarization does not contribute to an earlier onset, which is possibly because magnetic proximity is very short range and may only polarize the nearest Pd atoms directly below Fe atoms. Comparing Fe on Pd(110) and Pd(001), we suggest that the low ferromagnetic onset for Fe/Pd(110) is related to the chain-like growth as discussed earlier.

Longitudinal signals, taken with the magnetic field along the step edges, are observed ≥ 0.5 ML. Above ~ 1.5 -2 ML, the longitudinal Kerr increases linearly with film thickness as expected. This region coincides with the start of 3D-growth and lattice relaxation. Between 0.5 – 1.3 ML, an anomalous peak exists, where the Kerr signals are even larger than those of the thicker films. Its origin will be discussed in detail with additional experiments in the future. The results indicate that the magnetic easy axis at very low coverage of 0.3-0.5 ML is perpendicular to the surface, while it is clearly in plane above 1.5 ML. A theoretical calculation¹¹ suggests that the easy axis of a freestanding Co chain is in-line to the chain, while it switches to perpendicular to the surface for Co/Pd(110). No calculation, however, is available for Fe/Pd(110). At ~ 0.9 - 1.5 ML, the coercive field of the in-plane magnetization significantly increases, an indication of mixed magnetic phases at a phase transition boundary.¹²

IV. Conclusions

We have investigated Fe growth on a stepped Pd(110) surface and the magnetic properties at 0-3 ML. RHEED oscillations suggests that step decoration occurs in the first 1.5 ML, when the films are pseudomorphic. The Fe films are ferromagnetic even at low

submonolayer coverage, and initially have a magnetic easy axis perpendicular to the surface. Since such a system seems to be quasi-1D, it will be interesting to further investigate the submonolayer magnetic properties in the future.

Acknowledgement

This work was supported by DOE BES-MS #W-31-109-ENG-38. We thank W. Keune for valuable discussions. One of us, BRC, would like to thank the Department of Physics of the Gerhard-Mercator-Universität Duisburg for travel support.

† Permanent address: Laboratory für Angewandte Physik, Gerhard-Mercator-Universität Duisburg, Duisburg, Germany.

Figure Captions

Figure 1. LEED pattern of the Pd(110) substrate. The high symmetry directions are marked on the schematics. The elongated spots are caused by steps along the [110] as discussed in the text.

Figure 2. RHEED images of (a) the Pd(110) substrate; (b) 1.06 ML; (c) 1.65 ML; and (d) 10.90 ML of Fe on Pd(110) grown at 343 K. Note that the streaks start to become spotty in (c), indicating 3D growth. The electron beam incidence plane is parallel to the Pd [001]. (i), (ii), and (iii) indicates the positions where RHEED oscillations are taken in Fig. 4(a).

Figure 3. Inverse lattice spacing along the Pd [110] as a function of Fe film thickness derived from a series of RHEED images taken along a Fe wedge. Significant lattice relaxation is observed after 1.5 ML of Fe.

Figure 4. (a) RHEED oscillations observed at (i) the (1,0) streak; (ii) the center of the (0,0) streak; (iii) the low angle tail of the (0,0) streak. (b) Schematic of the proposed growth mode for Fe on stepped Pd(110) with step decoration. Note that after 0.5 ML Fe deposition, the terrace widths become significantly more uniform.

Figure 5. Thickness dependence of the polar and longitudinal remanent magnetization along with the coercivity in the longitudinal signals measured with SMOKE.

References

- 1 See, for example, articles in *J. Magn. Magn. Mater.* **200**, (1999).
- 2 F.J. Himpsel, T. Jung, A. Kirakosian, J.-L. Lin, D. Y. Petrovykh, H. Rauscher, and J. Viernow, *Nanowires by Step Decoration*, *MRS Bulletin* **24** (8), 20 (1999); F.J. Himpsel, T. Jung, and J.E. Ortega, *Surf. Rev. Lett.* **4**, (1997) 371.
- 3 P. Gambardella, M. Blanc, H. Brune, K. Kuhnke, and K. Kern, *Phys. Rev. B* **61**, 2254 (2000).
- 4 P. Gambardella, M. Blanc, L. Bürgi, K. Kuhnke, and K. Kern, *Surf. Sci.* **449**, 93 (2000).
- 5 H. J. Elmers, J. Hauschild, H. Höche, U. Gradmann, H. Bethge, D. Heuer, and U. Köhler, *Phys. Rev. Lett.* **73**, 898 (1994); J. Hauschild, H.J. Elmers, and U. Gradmann, *Phys. Rev. B* **57**, R677 (1998).
- 6 J. Shen, M. Klaua, P. Ohresser, H. Jerniches, J. Barthel, C.V. Mohan, and J. Kirschner, *Phys. Rev. B* **56**, 11134 (1997).
- 7 J.-P. Bucher, E. Hahn, P. Fernandez, C. Massobrio, and K. Kern, *Europhysics Lett.*, **27**, 473 (1994).
- 8 H. J. Choi, R. K. Kawakami, E. J. Escorcia-Aparicio, Z. Q. Qiu, J. Pearson, J.S. Jiang, Dongqi Li, and S.D. Bader, *Phys. Rev. Lett.*, **82**, 1947 (1999), and references therein.
- 9 J. Quinn, Y.S. Li, H. Li, D. Tian, F. Jona, and P. M. Marcus, *Phys. Rev. B* **43**, 3959 (1991).
- 10 X.F. Jin, J. Barthel, J. Shen, S. S. Manoharan, and J. Kirschner, *Phys. Rev. B* **60**, 11809 (1999)
- 11 J. Dorantes-Dávila and G.M. Pastor, *Phys. Rev. Lett.* **81**, 208 (1998).

12 Dongqi Li, M. Freitag, J. Pearson, Z. Q. Qiu, and S. D. Bader, *Phys. Rev. Lett.*, 72, 3112 (1994); S. D. Bader, Dongqi Li, and Z. Q. Qiu, *J. Appl. Phys.*, 76, 6419 (1994).




Fig. 1




Fig. 2






Fig. 3

(a)



(b)






Fig. 5