

Resin and Bagasse, Co-Products of Guayule Rubber Extraction: Applications in Different Fields for an Economic Viability and Ecological Approach [†]

Hind Houria Bougherra *, Lamia Taouzinet , Sabiha Bechir, Khoukha Mouhoubi, Lynda Messaoudene , Ayoub Allam and Khodir Madani 

Centre de Recherche en Technologies Agroalimentaires, Route de Targa Ouzemmour, Campus Universitaire, Bejaia 06000, Algeria; lamia.taouzinet@crtaa.univ-bejaia.dz (L.T.); sabiha.bechir@crtaa.univ-bejaia.dz (S.B.); khoukha.mouhoubi@crtaa.univ-bejaia.dz (K.M.); lynda.messaoudene@crtaa.univ-bejaia.dz (L.M.); ayoub.allam@crtaa.univ-bejaia.dz (A.A.); khodir.madani@univ-bejaia.dz (K.M.)

* Correspondence: hind.bougherra@crtaa.univ-bejaia.dz

[†] Presented at the 2nd International Electronic Conference on Processes: Process Engineering—Current State and Future Trends (ECP 2023), 17–31 May 2023; Available online: <https://ecp2023.sciforum.net/>.

Abstract: The economic viability of guayule as an industrial crop for natural rubber production depends largely on the potential valorization of these co-products. According to the studies carried out on the subject, there is a broad consensus on the added value of the resin and bagasse in different fields of application. The process of extracting natural rubber from guayule produces mainly bagasse ($\pm 80\%$ of the total dry mass) and resin ($\pm 10\%$ of the total dry mass). According to guayule research, high-value co-products significantly improve the economic viability of guayule as an industrial crop and offset a substantial portion of the cultivation and processing costs. According to studies, resin remains the most fluctuating value; reducing this uncertainty, through future research on resin applications, it is essential to the success of guayule as a natural rubber raw material. It finds applications in different industrial fields, such as coatings, varnishes, paints, treated wood, biocontrol agents and controlled-release formulations. Bagasse is composed primarily of cellulose, hemicellulose, lignin and resin, and has a high calorific value, making bagasse a suitable fuel for on-site combustion to produce electricity and thermal energy. Bagasse combustion in this scenario is less complex than the logistics of biofuel production. Resin-containing guayule bagasse has been combined with a plastic binder to make high-density composite panels resistant to termite degradation. In addition, the resinous material can be solvent-extracted and used to impregnate wood with raw resin extract so that the wood is protected from destructive organisms. Guayule bagasse containing resin can modify the soil nature and improve the growth of vegetables compared to de-resinated bagasse.

Keywords: guayule; co-products; bagasse; resin; application; latex; natural rubber



Citation: Bougherra, H.H.; Taouzinet, L.; Bechir, S.; Mouhoubi, K.; Messaoudene, L.; Allam, A.; Madani, K. Resin and Bagasse, Co-Products of Guayule Rubber Extraction: Applications in Different Fields for an Economic Viability and Ecological Approach. *Eng. Proc.* **2023**, *37*, 60. <https://doi.org/10.3390/ECP2023-14661>

Academic Editor: Antoni Sánchez

Published: 17 May 2023



Copyright: © 2023 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

1. Introduction

Guayule (*Parthenium argentatum* Gray) is a perennial shrub belonging to the Asteraceae family and native to the Chihuahuan desert, zones spread from northern Mexico to southern Texas. This plant is commonly known to produce high-quality rubber, an elastomer called polyisoprene, accounting for up to 10% of the dry weight of the branches [1,2]. Natural rubber is required not only for commercial-grade tires but also for defence and hypoallergenic medical articles [3,4]. In addition to its promising natural rubber production and relative drought tolerance, guayule derives its economic value from exploitation and valorisation of the whole plant biomass for the production of bioenergy and non-rubber co-products, such as resin and bagasse which can be converted into raw materials with high added-value [3,5]. Furthermore, the potential of valorisation guayule processing residue might contribute to reducing rubber production costs by 26–49% [6].

In light of the potential of guayule, many researches mentioned the industrial rubber extraction processes and the exploitation of its byproducts. Presently, resin stands as the most important unknown in the guayule supply chain, consequently, researches on high-value guayule resin products are underway. However, the proportion of resin is relatively small (5–10%) of the guayule biomass, in the same proportion as rubber yields. The most significant proportion is bagasse, which comprises 80–90% of the biomass. As a result, bagasse valorisation could have a major effect on guayule's overall value [7]. The remaining unused lignocellulosic biomass from guayule rubber extraction, often referred to as bagasse, is considered one potential solution for bioenergy production [8], a rich source of bioactive compounds for potential exploitation in fodder, nutraceuticals and pharmacological sectors.

2. Guayule Resin Valorization

The economic aspect of guayule valorisation has led to the development of guayule resin applications in different fields. The first step to estimate the real added value of resin as raw material is to identify the range of active compounds that resin can substitute. The guayule resin, is a viscous liquid, its chemical composition has already been described in the literature, around 50 secondary metabolites have been reported, such as terpenes (guayulins A, B, C, D, argentatines), polyphenols, triglycerides, waxes, sugars, organic acids, phytosterols. Guayule resin composition varies with shrub strain, harvest date, cultivation site, and extraction processing [4,7].

In the literature, several studies mentioned resin applications such as coatings, biocontrol agents [9], and controlled-release formulations [10]. Argentatins have been reported to have antimicrobial, insecticidal, and antitumoral properties [10].

Polyphenolics, cinnamyl derivatives and terpenoids are the most likely compounds responsible for the observed termite resistance characteristics of guayule resin [11]. The recently-identified phenolic compounds in the leaves and twigs have potential uses in antioxidant, anticancer, anti-inflammatory, and antidiabetic applications [12].

It can be used as a wood preservative against damage caused by highly destructive termite species [13,14], as pesticide [11], in the formulation of coatings and paints, providing good properties, abrasion resistance, gloss, drying time and water resistance [3]. In addition, guayule resin combined with epoxy polymers is used to make strippable coatings for the protection of equipment in storage [5]. It has been also reported that an acetone-extractable, residual guayule resin could be used as a bio-based recycling agent in hot mix asphalt [15].

3. Guayule Bagasse Valorization

Bagasse is mostly made up of cellulose, hemicellulose, lignin and resin [3,16]. Guayule resin-containing bagasse combined with a plastic binder is used to produce high-density composite boards resistant to termite degradation [10]. Ref. [1] have successfully manufactured a Mycelium-based bio-composite using bagasse from guayule and a wild strain of *Ganoderma curtisii* by a simple pressed method, which is cost-effective, eco-friendly, and fully compostable.

In a recent study, the use of bagasse to produce biofuels and refractory bricks has been reported [1]. The energy value of bagasse is increased by the guayule resin, which accounts for 10% of the material, and has a heating value of 38 MJ/kg, which is comparable to the oil obtained from the majority of oilseed crops [17]. Bagasse is a suitable feedstock fuel for direct combustion, in accordance with Schloman and Wagner (1999). Furthermore, resinous bagasse has a high heating energy value between 21,000 and 24,000 kJ/kg, and can be converted directly into liquid hydrocarbons [16]; it has been also used for energy production as fireplace logs [18], as pelletized fuel with a mixture of cotton gin trash [5].

According to a previous study, guayule bagasse can be utilized as an amendment to heavier soils for its lightning effect. The same author also claims that guayule leaves removed by parboiling can be utilised as fertilizer. Taylor makes no mention of the use of resin in any of his works. Another study observes that when added at a rate of up to

11 t/ha in Guayule bagasse slows lettuce growth in the absence of supplementary nitrogen fertilizer [19]. Guayule bagasse and resin can be used, for example, in the pulp paper and chemical industries [20], as a soil amendment [5,19].

4. Conclusions

This review provides insight into the applications of guayule byproducts. Natural resins have numerous applications in the food, pharmaceutical, cosmetic, paint and adhesive industries. Through energy applications, the residual biomass from guayule represents a valuable fuel resource collected on-site and is a suitable lignocellulosic conversion feedstock. Guayule byproducts have the potential to improve the sustainability and economic feasibility of guayule rubber production.

Author Contributions: Conceptualization, K.M. (Khodir Madani) and H.H.B.; methodology, H.H.B., L.T. and S.B.; investigation, H.H.B., K.M. (Khoukha Mouhoubi), L.M. and A.A.; writing—original draft preparation, H.H.B.; writing—review and editing, H.H.B.; supervision, H.H.B. and K.M. (Khodir Madani). All authors have read and agreed to the published version of the manuscript.

Funding: This research received no external funding.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: All data supporting this study are included in the manuscript.

Acknowledgments: The authors thank the General Directorate of Scientific Research and Technological Development (DGRSDT/MESRS-Algeria).

Conflicts of Interest: The authors declare no conflict of interest.

References

1. César, E.; Castillo-Campohermoso, M.A.; Ledezma-Pérez, A.S.; Villarreal-Cárdenas, L.A.; Montoya, L.; Bandala, V.M.; Rodríguez-Hernández, A.M. Guayule Bagasse to Make Mycelium Composites: An Alternative to Enhance the Profitability of a Sustainable Guayule Crop. *Biocatal. Agric. Biotechnol.* **2023**, *47*, 102602. [\[CrossRef\]](#)
2. Elshikha, D.E.M.; Wang, G.; Waller, P.M. Guayule Growth and Yield Responses to Deficit Irrigation Strategies in the US Desert. *Agric. Water Manag.* **2023**, *277*, 108093. [\[CrossRef\]](#)
3. Rasutis, D.; Soratana, K.; McMahan, C.; Landis, A.E. A Sustainability Review of Domestic Rubber from the Guayule Plant. *Ind. Crops Prod.* **2015**, *70*, 383–394. [\[CrossRef\]](#)
4. Rousset, A.; Amor, A.; Punvichai, T.; Perino, S.; Palu, S.; Dorget, M.; Pioch, D.; Chemat, F. Guayule (*Parthenium Argentatum* A. Gray), a Renewable Resource for Natural Polyisoprene and Resin: Composition, Processes and Applications. *Molecules* **2021**, *26*, 664. [\[CrossRef\]](#) [\[PubMed\]](#)
5. Nakayama, F.S. Guayule Future Development. *Ind. Crops Prod.* **2005**, *22*, 3–13. [\[CrossRef\]](#)
6. Schloman, W.W., Jr.; Garrot, D.J., Jr.; Ray, D.T.; Bennett, D.J. Seasonal Effects on Guayule Resin Composition. *J. Agric. Food Chem.* **1986**, *34*, 177–179. [\[CrossRef\]](#)
7. Dehghanizadeh, M.; Mendoza Moreno, P.; Sproul, E.; Bayat, H.; Quinn, J.C.; Brewer, C.E. Guayule (*Parthenium Argentatum*) Resin: A Review of Chemistry, Extraction Techniques, and Applications. *Ind. Crops Prod.* **2021**, *165*, 113410. [\[CrossRef\]](#)
8. Moreno, P.M.; Sproul, E.; Quinn, J.C. Economic and Environmental Sustainability Assessment of Guayule Bagasse to Fuel Pathways. *Ind. Crops Prod.* **2022**, *178*, 114644. [\[CrossRef\]](#)
9. Isman, M.B.; Rodriguez, E. Larval Growth Inhibitors from Species of *Parthenium* (asteraceae). *Phytochemistry* **1983**, *22*, 2709–2713. [\[CrossRef\]](#)
10. Pascual-Villalobos, M.J. López New Application of Guayule Resin in Controlled Release Formulations. *Ind. Crops Prod.* **2013**, *43*, 44–49. [\[CrossRef\]](#)
11. Bultman, J.D.; Gilbertson, R.L.; Adaskaveg, J.; Amburgey, T.L.; Parikh, S.V.; Bailey, C.A. The Efficacy of Guayule Resin as a Pesticide. *Bioresour. Technol.* **1991**, *35*, 197–201. [\[CrossRef\]](#)
12. Piluzza, G.; Campesi, G.; Molinu, M.G.; Re, G.A.; Sulas, L. Bioactive Compounds from Leaves and Twigs of Guayule Grown in a Mediterranean Environment. *Plants* **2020**, *9*, 442. [\[CrossRef\]](#) [\[PubMed\]](#)
13. Nakayama, F.S.; Chow, P.; Vinyard, S.H.; Deppe, N.A. Termite Resistance of Kenaf Composite Boards Treated with Guayule Resin. In Proceedings of the Association for the Advancement of Industrial Crops 2023 Annual Meeting, Portland, OR, USA, 12–15 October 2003.
14. Nakayama, F.S.; Vinyard, S.H.; Chow, P.; Bajwa, D.S.; Youngquist, J.A.; Muehl, J.H.; Krzysik, A.M. Guayule as a Wood Preservative. *Ind. Crops Prod.* **2001**, *14*, 105–111. [\[CrossRef\]](#)

15. Lusher, S.M.; Richardson, D.N. Guayule Plant Extracts as Recycling Agents in Hot Mix Asphalt with High Reclaimed Binder Content. *J. Mater. Civ. Eng.* **2015**, *27*, 04014269. [[CrossRef](#)]
16. Boateng, A.A.; Mullen, C.A.; Goldberg, N.M.; Hicks, K.B.; McMahan, C.M.; Whalen, M.C.; Cornish, K. Energy-Dense Liquid Fuel Intermediates by Pyrolysis of Guayule (*Parthenium Argentatum*) Shrub and Bagasse. *Fuel* **2009**, *88*, 2207–2215. [[CrossRef](#)]
17. Nakayama, F.; Holt, G.; Coffelt, T.; Vinyard, S.; Faber, A.L. Pellet Fuel from Guayule Plant Material. In Proceedings of the Association for the Advancement of Industrial Crops 2023 Annual Meeting, Portland, OR, USA, 12–15 October 2003.
18. Wagner, J.P.; Soderman, K.L.; Konzen, R.; Akgerman, A. Toxic Species Evolution from Guayule Fireplace Logs. *Bioresour. Technol.* **1991**, *35*, 203–208. [[CrossRef](#)]
19. Schloman, W.W., Jr. Free-Flowing Guayule Resin and Bagasse Mixtures and Their Use as Fuel or Soil Amendent. US4988388A, 29 January 1991.
20. Chow, P.; Nakayama, F.S.; Blahnik, B. Chemical Constituents and Physical Properties of Guayule Wood and Bark. *Ind. Crops Prod.* **2008**, *28*, 303–308. [[CrossRef](#)]

Disclaimer/Publisher’s Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.