


# Accepted Manuscript

The potential for the use of waste products from a variety of sectors in water treatment processes

Maebh A. Grace, Eoghan Clifford, Mark G. Healy



PII: S0959-6526(16)31009-5

DOI: [10.1016/j.jclepro.2016.07.113](https://doi.org/10.1016/j.jclepro.2016.07.113)

Reference: JCLP 7685

To appear in: *Journal of Cleaner Production*

Received Date: 11 May 2016

Revised Date: 28 June 2016

Accepted Date: 20 July 2016

Please cite this article as: Grace MA, Clifford E, Healy MG, The potential for the use of waste products from a variety of sectors in water treatment processes, *Journal of Cleaner Production* (2016), doi: 10.1016/j.jclepro.2016.07.113.

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

## The potential for the use of waste products from a variety of sectors in water treatment processes

Maebh A. Grace, Eoghan Clifford\*, Mark G. Healy

*Civil Engineering, College of Engineering and Informatics, National University of Ireland, Galway*

*\*Corresponding author: E-mail address: eoghan.clifford@nuigalway.ie*

### **Abstract**

This review examines the utilisation of waste products from three sectors (industry, agriculture, and construction and demolition) in filters for the removal of contaminants from water. Sand is commonly used in drinking water filtration in water treatment plants. However, the use of alternative, low-cost materials could address the limitations of sand, particularly for the removal of emerging contaminants, and address European legislation which fosters the development of a ‘circular’ economy, in which materials are used effectively. This review assesses the suitability of potential media by quantifying their adsorption potential across a variety of common drinking water contaminants. The media investigated were fly ash, Bayer residue, ground granular blast furnace slag, coconut shell, tea/coffee waste, rice husk, crushed concrete, masonry waste, and wood waste. There is a potential for the use of these media in the water treatment sector, although certain precautions must be taken to ensure any concerns are mitigated, such as release of metals into water. Recommendations, following this review, include testing the media in large-scale applications, and also constructing filters so as potential media are placed in layers to harness their contrasting adsorptive potentials.

**Keywords:** Media utilisation, water treatment, sustainability, cost-efficiency; filtration; review

## 1 Introduction

The European Union (EU) produces 2.3 billion tonnes of waste annually, of which 10% (or 250 million tonnes) includes municipal waste, and 90% includes industrial, commercial, agricultural, and other business related waste (Ruggiero, 2013). In agriculture, wastes are generated at production, post-harvest and processing stages (Parfitt et al., 2010), and amount to 1.3 billion tonnes per year worldwide (FAO, 2011). About 850 million tonnes of construction and demolition (C&D) waste is generated in the EU per year, representing 31% of the total waste generation in the EU (Fischer and Werge, 2009). However, the level of recycling and reuse of C&D waste varies greatly (between less than 10% to over 90%) across the EU. The concept of a ‘zero waste’ industry is not feasible, and while industries such as the C&D industry have a policy of reduction, reuse, recycle and disposal (Yuan and Shen, 2011), there is a tendency amongst stakeholders to only consider the use of wastes within the same sector (Duran et al., 2006), without considering their use in other sectors. One such avenue for the use of these wastes is in the water treatment sector, particularly as less than half the population of some countries in the developing world have access to clean, potable water (FAO, 2015), and as a need has been identified for cost-effective and robust solutions to improve water purification in both the developed and developing world (Shannon et al., 2008). Although drinking water improvement trends are increasing, in 2015, 663 million people were deprived of good quality drinking water, leaving much scope for improvements (WHO/UNICEF, 2015).

Improvements must include sophisticated strategies to combine water and energy savings, while striving for the ultimate goal of a circular economy (Bagatin et al., 2014). Although a ‘zero-waste’ society is not yet achievable, steps in this direction are continuing. Total recycling of

used products and an entirely circular economy may not be realistic in all scenarios, but it is possible to achieve a sustainable future by attempting to reach this goal (Reh, 2013). It is also important to maintain environmental and economic benefits while investigating material recovery concepts (Dahlbo et al., 2015), and so, either disposal or use post-treatment must also be considered to ensure a holistic design approach. It is also necessary to ensure new production processes do not create extra environmental impacts, which could even undermine those beneficial changes found by utilizing waste products (Mirabella et al., 2014).

Sand filtration is commonly used in drinking water purification. However, it can have shortfalls regarding the removal of certain contaminants (Water\_Team, 2012). The use of a multi-layer filter containing a variety of media may have the potential to tackle problematic contaminants. Anthracite and coal are most commonly used in multi-layer filters, but these are costly and unsustainable adsorbents (EPA, 1995). The use of adsorption is evolving, as it produces satisfactory results while being cost-efficient and easy to design and operate (Bibi et al., 2015). The exploration of different adsorbents, both manufactured and recycled, is paving the way for a new generation of filters, containing a variety of media from many different sources (Bhatnagar and Sillanpää, 2010). The utilization of waste from sectors such as industry, agriculture and C&D as adsorbents allows for the development of sustainable and effective treatment technologies. The use of waste from certain processes could provide a more sustainable alternative for water treatment systems than abstraction of sand, for example by providing a use for an otherwise landfilled waste material.

There is increasing interest in the utilisation of waste materials, and there is a gap in knowledge in terms of the application to water treatment processes. This paper investigates a variety of media from three sectors (industry, agriculture and C&D) that could be used in filters for the removal of contaminants from water.

### **1.1 Adsorption classification and contaminant definitions**

The potential adsorption capacity of media can be classified mathematically using a number of adsorption isotherm models (Foo and Hameed 2010), allowing for a comparison between the theoretical adsorption capacity of novel versus traditional media. In turn, these data would allow the relative efficacy of one type of filter media over another to be evaluated. There has been considerable research into the adsorption capacities of a huge variety of media to adsorb a variety of contaminants, such as clays, zeolites and chitosan for nitrate removal (Bhatnagar and Sillanpää, 2011), carbon nanotubes, biosorbents and low cost adsorbents for heavy metal removal (Fu and Wang, 2011), and agricultural wastes for water purification (Bhatnagar et al., 2015). However, for the purposes of this review, common drinking water contaminants will be investigated against a selection of media arising from industrial, C&D, and agricultural sectors.

The legislation discussed in the current review is Irish drinking water legislation (SI No 278 of 2007, 2007); however, this is based on the European Communities (Drinking Water) (No 2) Regulations 2007. Discrepancies between these and United States regulations, where they arise, are stated in the current paper. The European Communities set out clear quality standards for water for human consumption. A total of 39 parameters must be tested for on a regular basis, and 95% of samples must comply with the regulations. There are further requirements for those

samples which do not pass. To allow for a broad overview of media and contaminants, a small selection has been chosen on which the review is based.

Phosphorus (P) is not currently legislated for under drinking water quality legislation. However, given that most potable water uses surface- or ground-water as its abstraction source, P is likely to be found in abstraction water. The Water Framework Directive (2000/60/EC; EC, 2000) states the threshold level of P in water to be  $0.035 \text{ mg L}^{-1}$ . However there is a likelihood that certain locations in the EU will not meet this objective, based on current trends (EPA, 2015a). Phosphorus causes detrimental eutrophication effects when present in surface water sources, and can have negative effects following human consumption. Phosphorus is also likely to cause problems in the water distribution network, with excessive amounts increasing microbial growth (Miettinen et al., 1997).

Nitrogen (N) can be present in water as ammonium ( $\text{NH}_4^+\text{-N}$ ), nitrate ( $\text{NO}_3^-\text{-N}$ ) and nitrite-N ( $\text{NO}_2^-\text{-N}$ ) and organic nitrogen. The maximum allowable concentration (MAC) for  $\text{NH}_4^+\text{-N}$  in drinking water is  $0.3 \text{ mg L}^{-1}$ . The presence of  $\text{NH}_4^+\text{-N}$  in water treatment plants can have a negative impact on (i) disinfection by resulting in increased chlorine consumption or reducing the effect of chlorine-based disinfection systems (Wilczak et al., 1996) and (ii) both pH and dissolved oxygen (DO) in the distribution system (Feng et al., 2012). The MAC for  $\text{NO}_3^-\text{-N}$  in drinking water is  $11 \text{ mg L}^{-1}$ . Nitrate can enter drinking water abstraction sources from anthropogenic sources, generally from municipal wastewater treatment plants where denitrification was incomplete, and from agricultural land (Bagatin et al., 2014). The MAC for  $\text{NO}_2^-\text{-N}$  in drinking water is  $0.5 \text{ mg L}^{-1}$ , and its presence has also been linked to blue-baby syndrome (Fan and Steinberg, 1996). Nitrogen is most

commonly removed at filtration stage by a combination of biological and chemical removal mechanisms, with the biological activity occurring at the surface of the filters.

There is no MAC for dissolved organic carbon (DOC), with legislation stating “no abnormal change” must be observed. However, the presence of organic carbon in water can, following disinfection, result in the formation of multiple disinfection by-products (DBP) (EPA, 2012). Total trihalomethanes (TTHM) are the most commonly occurring disinfection by-products, and are the only ones regulated by legislation, with a MAC of TTHM in Ireland of  $0.1 \text{ mg L}^{-1}$  (SI No 278 of 2007, 2007) and in the United States of  $0.08 \text{ mg L}^{-1}$  (USEPA, 2009). Disinfection by-products are carcinogenic and have been linked to reproductive issues and birth defects (Richardson, 2003). The composition of DOC has an impact on the formation potential of DBP, with the hydrophobic fraction, comprising mainly humic substances, most likely to form DBP (Tran et al., 2015). Humic acid is a constituent of natural organic matter in surface and ground water sources, and is often used in adsorption studies. The potential formation will also differ depending on temperature, rainfall, pH, alkalinity, surrounding soils, and time of year (EPA, 2012). For the purposes of this paper, the focus is on DOC adsorption, rather than the by-products.

Metals are most likely to enter drinking water abstraction sources by anthropogenic sources, such as mining, drainage, corrosion of pipes (EPA, 2015b), and by industrial processes (Mohod and Dhote, 2013). In legislation, each metal has a different MAC, depending on the severity of the effects on human health. For example, the MAC of aluminium (Al) is  $200 \text{ } \mu\text{g L}^{-1}$ , chromium (Cr) is  $50 \text{ } \mu\text{g L}^{-1}$ , copper (Cu) is  $2 \text{ mg L}^{-1}$ , lead (Pb) is  $10 \text{ } \mu\text{g L}^{-1}$ , and iron (Fe) is  $200 \text{ } \mu\text{g L}^{-1}$ . The presence of metals in water can be associated with many physiological illnesses attacking the major organs of the human body (Mohod and Dhote, 2013).

Although adsorption of individual contaminants onto various media is well examined in the literature, reviews tend to group the literature based on a single contaminant or in terms of wastewater treatment, and often investigate commercial adsorbents. This review focuses on a variety of drinking water contaminants, solely from the point-of-view of reusing by-products or waste material, and it provides researchers and practitioners with a comprehensive overview on a number of different materials. This would not only allow for improved water treatment, but also improvements for the environment as a whole, by aiming to reduce waste products and disposal of same.

## **2 Methodology**

A detailed literature search was carried out by initially selecting several key words. Those used include: adsorption, waste products, waste reuse, water treatment, regeneration, agricultural-based adsorbents, construction-based adsorbents, and industrial-based adsorbents. Each media mentioned was also included in a search. The search was limited to papers published in the last ten years, where possible. Exceptions were made for highly cited papers and areas where there was limited research available. No geographical limitations were applied. Search engines used included databases such as Scopus, as well as publisher-specific search engines such as ScienceDirect, Royal Society of Chemistry, American Chemical Society, and Materials Research Society, and the Boolean operator “AND” was used to include several keywords in one search. References from selected papers were also explored for relevant information.

Articles were selected based on relevance to the review, with a focus on the selected media from industry, agriculture, and construction and demolition sectors. Particular attention was paid to those contaminants of concern, although all adsorption studies were considered for inclusion.

Post-treatment use and regeneration were also considered when selecting articles. A total of 210 references were selected, of which most are journal papers from chemistry, engineering, and material science research areas. A small number of books and reports were also included.

### **3 Industrial waste**

Industrial activities generate products and residues from both production and consumption. As industrial activity continues to increase, so too does the creation of excessive waste. In 2012, 48% of total waste in the EU was disposed, and the remainder was either recycled, or used for energy recovery, backfilling or incineration (Eurostat, 2015). The utilisation of industrial by-products and wastes in water treatment is infrequently examined in the literature. The wastes that will be considered in this paper are fly ash and ground granular blast furnace slag (GGBS), and Bayer residue. Fly ash was chosen as it comprises 85% of all ash produced in coal combustion products (CCP), with approximately 780 million tonnes produced worldwide (Heidrich et al., 2013). Ground granular blast furnace slag was chosen as it is a product of over 1 billion tonnes of steel produced (Juckes, 2011), and Bayer residue because of the increasing accumulation of the waste (EAA, 2013).

#### **3.1 Fly ash**

Fly ash (specifically coal fly ash) is a waste product of the incineration process. It is defined as a non-hazardous mineral combustion waste, with coal fly ash falling under the category of slags and ashes from thermal treatment combustion (Eurostat, 2010). It has a recognised potential use as a raw/construction material in applications such as cement and concrete addition (ESB Moneypoint, 2012), with more than half of the concrete used in the USA containing fly ash (World Coal Association, 2015). The current utilisation rate for fly ash use in the EU is approximately 43%, leaving over 17 million tonnes for disposal or stockpiling (Ecoba, 2015).

Fly ash is produced by the incineration process when coal is burned as a power source, and in incineration of municipal solid wastes, sugar cane bagasse, rice husks and tea dusts. For many years production has exceeded utilisation capabilities, meaning a large proportion is landfilled (Ecoba, 2015). For the purposes of this review, power station fly ash (coal combustion) is of most interest, as it is the largest source of fly ash production (Iyer and Scott 2001). The major components are silica, Al, Fe oxides, carbon, calcium (Ca), magnesium (Mg), and sulphur in varying amounts, depending on the original source (Iyer and Scott 2001). Chemical characteristics are detailed in Table 10. With such a large variety of elements, fly ash has potential for many uses (Figure 3), and efforts should be made to avoid landfilling.

### **3.1.1 Current Uses**

In the construction industry, fly ash is mostly used in concrete addition (35.9% of total use of fly ash in 2010), with other uses including blended cement, road construction and concrete blocks (Ecoba, 2015). Research has been carried out on increasing the amount of fly ash in certain concrete mixtures to increase performance (Mehta, 2002). This must be cautioned however, as fly ash can adsorb concrete surfactants which may have negative effects on the mixture (Ahmed and Hand, 2014). The fine nature and elemental composition of fly ash has led to investigations into the use of fly ash as a fertiliser (Jala and Goyal, 2006) and for soil conditioning, which has demonstrated positive results on a short-term basis (Kalra et al., 1998), though this should only be used where the fly ash will not compromise the soil quality (Pandey and Singh, 2010).

### 3.1.2 Potential for use in water treatment

Fly ash has been well recognised for its efficacy as an adsorptive material for various contaminants in aqueous solutions (Ahmaruzzaman, 2010). Table 11 gives an overview of the adsorption potential, based on adsorption isotherm modelling, targeting in particular those contaminants of interest in this review. Fly ash also has the ability to uptake metals, such as Pb and Cu (Alinnor, 2007), and zinc (Zn) and manganese (Nascimento et al., 2009) from aqueous solutions, and its capacity may be improved by the presence of humic acid in water (Wang, et al., 2008a). Metal removal using fly ash can also be enhanced by coating with chitosan (Adamczuk and Kołodyńska, 2015). Lignin removal can be achieved by fly ash (Andersson et al., 2011), as can phenanthrene (An and Huang, 2012). Little research has been carried out on  $\text{NH}_4^+\text{-N}$  adsorption, other than cation exchange capacity (CEC) investigations with synthesised zeolite from fly ash.

Many studies have been carried out to investigate the efficacy of zeolite that is synthesised from fly ash (ZFA), for example to remove heavy metals from wastewater (Querol et al., 2002), phosphate from an aqueous solution (Chen et al., 2006), and for humic acid removal from water (Li et al., 2011). Synthetic zeolites from fly ash have been shown to have a CEC of up to  $3 \text{ meq g}^{-1}$ , allowing for the uptake of heavy metals and cations such as  $\text{NH}_4^+\text{-N}$  (Querol et al., 2002). Wu et al. (2006) investigated the increase of CEC of ZFA by salt treatment, and simultaneous P and  $\text{NH}_4^+\text{-N}$  removal, which was particularly effective at low concentrations. A mild acid treatment has been shown to have a similar effect on ZFA (Zhang et al., 2007).

The main disadvantage to using fly ash in water treatment is the potential for metal leaching. By its nature, metals are an intrinsic characteristic of fly ash (Chou et al., 2009). However, with the introduction of some precautionary measures, where necessary, this can be mitigated. Measures

may include a leaching behaviour test (for example, where systems may contain other adsorptive media), forced extraction, immobilisation of elements, and destruction of persistent pollutants (Wang and Wu 2006).

Acid, heat, and activation all have a positive effect on the adsorption capacity of fly ash (Li et al., 2006). However, for the most sustainable and cost-effective approach, the raw state is generally stated to be most desirable (Alinnor, 2007). Phosphorus and humic acid can also be successfully removed from water (Table 11) using fly ash. However, there is little investigation of co-adsorption and contaminant interaction. Wang et al. (2008a) studied the positive effect of humic acid presence on metal adsorption, but to comprehensively assess the potential for the use of fly ash in a sustainable technology, it is necessary to study the raw water contaminants in a combined and natural environment.

### **3.2 Ground granulated blast furnace slag**

Ground granular blast furnace slag is a waste product of the steel production industry. It is non-hazardous, and is a finely ground powder. Similar to fly ash, GGBS falls under the category of mineral combustion wastes, and is hazardous if it contains toxic heavy metals (Eurostat, 2013). Over a billion tonnes of steel is manufactured per annum, leading to the availability of a large amount of GGBS (Juckes, 2011).

Ground granulated blast furnace slag is produced from blast furnaces used in Fe production. Molten slag is produced when iron-ore, coke and limestone are melted in a blast furnace. Slag floats on the molten iron, and once removed, is granulated and ground to produce GGBS (Siddique and Bennacer, 2012). Ground granulated blast furnace slag typically contains oxides of calcium, silica, Al and Mg in varying proportions (Ecocem, 2012).

### **3.2.1 Current Uses**

In Europe, almost 18 million tonnes of GGBS is currently used in the cement and concrete industries (Ecocem, 2015). This is the most common use for GGBS. It acts as a direct replacement for cement, and has many advantages including extending the life cycle of concrete, making concrete more durable, and reducing the carbon and energy footprint of concrete production (Ecocem, 2015). Blended cements (GGBS and ordinary Portland cement) have a superior resistance to sulphates and an increased chloride binding capacity (Siddique and Bennacer, 2012).

### **3.2.2 Potential for use in water treatment**

Ground granulated blast furnace slag has not been previously identified as an adsorptive material, and little research has been carried out in this regard. The chemical composition of GGBS would indicate potential for a strong CEC for cation and metal adsorptions. Grace et al. (2015) found that GBS (granular blast furnace slag) had good adsorption properties but solidified upon immersing in water, which would counteract the usefulness in a water treatment system. Further research is necessary to investigate pre-treatments which would allow the adsorption potential of GGBS to be harnessed and utilised.

### **3.3 Bayer residue**

Bayer residue (also called bauxite residue or red mud) is a primary waste product of the Al production industry. Accumulation of the residue is estimated to be increasing by 110 million tonnes per annum, with 2700 million tonnes already in storage in 2010 (EAA, 2013). Bayer residue is highly alkaline and has a fine particle size, leading to environmental issues around disposal and storage.

Aluminium is most often refined from bauxite ore, which is readily available all over the world. The ore contains high levels of Al oxides, which can be extracted by the Bayer process. This involves heating the bauxite in caustic soda under high temperature and pressure, to form sodium aluminate and an insoluble residue - known as Bayer residue (Deelwal et al., 2014). The sodium aluminate is further treated to form Al hydroxide or oxide. The Bayer residue typically contains Fe oxide, Al oxide, titanium oxide, calcium oxide, silica oxide and sodium oxide (EAA, 2013).

### **3.3.1 Current Uses**

Bayer residue is stored at or close to the alumina manufacturing facility in a bauxite residue storage area or in dry stacking facilities (Nikraz et al., 2007). Bauxite residue storage areas should be carefully controlled, with hydrosphere monitoring to avoid any negative environmental or ecological impacts (EAA, 2013). It is a concerning issue for many nations; indeed the Chinese government set a target of utilising 20% of fresh mud by the end of 2015 (Liu et al., 2014). Approximately 110 million tonnes of Bayer residue are produced and stored worldwide annually (EAA, 2013), and amount currently in storage is expected to increase to 4 billion tonnes by 2015 (Liu and Naidu, 2014). Therefore, it is the subject of ongoing research to identify potential uses and alternative disposal mechanisms such as soil amelioration, construction and groundworks restoration (EAA, 2013). Work has been carried out on the use of Bayer residue as a construction additive or filling material (Deelwal et al., 2014). Limited work has been carried out on the use of Bayer residue as a coagulant or as an industrial catalyst, showing it may have potential in this area (Wang, et al., 2008b), for example to purify a bio-diesel waste stream (Resende et al., 2013). Work has also been carried out on iron recovery from Bayer residue (Liu and Naidu, 2014).

### 3.3.2 Potential for use in water treatment

Previous studies indicate that Bayer residue has potential as an adsorptive material for removal of contaminants from water supplies, and it has been suggested that exhausted material be re-used in the construction sector (Ali and Gupta, 2006). Metal removal from aqueous solution has been examined successfully (Hua et al., 2014), although further work is required to understand the removal techniques and consequences (Brunori et al., 2005). Phosphorus removal is very effective using Bayer residue (Table 12), and limited studies of  $\text{NO}_3^-$ -N, along with other anion adsorption studies (Bhatnagar et al., 2011), have produced positive results. Gaps exist in the adsorption potential of  $\text{NH}_4^+$ -N and DOC, although Lopez et al. (1998) observed  $\text{NH}_4^+$ -N removal from secondary effluent from a wastewater treatment plant. Bayer residue can also achieve more than 90% bromate removal from aqueous solutions (Chen et al., 2016). The positive results indicate that further research should be carried out to assess the removal capabilities of a spectrum of contaminants.

The most relevant disadvantage to using Bayer residue in water treatment processes is reflected in environmental concerns (Liu et al., 2011). Its chemical and mineralogical characteristics require treatment before storage and it is important to ensure it does not further pollute water or leach contaminants. The adsorption potential may outweigh the concerns, and carefully designed systems could mitigate any possible concerns.

## 4 Agricultural waste

The agricultural sector is constantly growing, particularly as trade relations strengthen between countries and demographics continue to put pressure on food production systems. Thirty-eight percent of the EU budget is spent on agriculture, with exports steadily rising and currently estimated to have a value of €122 billion (European Commission, 2015a). Globally, trade flow values have increased fivefold in the past 50

years (United Nations, 2015). Twelve percent of the total land area of the world is used for crop production in the agricultural sector (United Nations, 2015). This produces many different types of wastes and by-products. In this review, those examined are coconut shell, tea and coffee wastes, and rice husk.

#### **4.1 Coconut Shell**

Coconut shell is frequently used as a carbonaceous source for activated carbon, as it results in a strong, dense carbon (Cooney, 1999). Although powdered coconut shell can be used for adsorption, the most common use is as an activated carbon source. This is a successful adsorbent, but the activation process can be expensive, and using the raw material as is would be a more sustainable approach.

Activated carbon is manufactured in a two-step process. First, raw materials go under a carbonization process in an inert environment, and then the carbonized product is activated with oxidising gases (Hu and Srinivasan, 1999). The oxidation process erodes a network of internal channels and pores, while creating a surface of oxides, to increase the surface area and make the material more suitable for adsorption (Cooney, 1999).

##### **4.1.1 Current Uses**

In developing countries, coconut shells have practical uses such as bowls and utensils, but the most common large-scale use for coconut shell is the production of activated carbon. More than 61 million tonnes of coconuts are grown worldwide annually, most commonly used for drinking, coconut oil, and desiccated coconut (UNCTAD, 2012). This volume of raw material gives much scope for activated carbon production. Coconut

shells have also been used in construction, to create coconut shell aggregate concrete; however, this is not commonly used (Gunasekaran et al., 2012).

#### **4.1.2 Potential for use in water treatment**

Table 13 presents a selection of previous studies investigating adsorption using coconut shell in terms of relevant contaminants for drinking water treatment. Coconut-based adsorbents are well studied in terms of biosorption for water treatment. Bhatnagar et al. (2010) reviewed a variety of coconut biosorbents for removal of metals, dyes, pollutants, anions and radionuclides from water, concluding that the potential for use is great, although knowledge gaps still exist in terms of real effluent use, regeneration and recovery studies.

Coconut shell has been successfully used in adsorption of metals such as Cu, Pb, cadmium (Cd) and Zn (Sousa et al., 2010), and dye adsorption (Cazetta et al., 2011), various anions such as those mentioned in Table 13, and fluoride (Sathish et al., 2007). Nickel can also be adsorbed using coconut shell (Vocciante et al., 2014). Adsorption of dyes can be indicative of an adsorbent's affinity to adsorb various molecular weights of organic matter (Zhang et al., 2007), thus activated carbon from coconut shell has good potential to adsorb natural organic matter (NOM). Studies have shown that the presence of NOM in aqueous solutions can inhibit or at least compete with adsorption of other trace organic compounds that are commonly found in drinking water by pore blockage and site competition (Quinlivan et al., 2005).

Evidence suggests that coconut shell-derived activated carbon is useful in terms of water treatment. However, the carbonization and activation process can be expensive and technology-intensive, meaning that it is not as sustainable as other by-products. It is also likely to become

saturated and exhausted, requiring a regeneration treatment. Coconut shell could be combined with another adsorbent to reduce the need for regeneration yet achieve effective and sustainable water treatment.

## **4.2 Tea/Coffee wastes**

Worldwide coffee and tea production is a large industry, with the total coffee production per crop year 2014/15 at 141.7 million 60 kg bags (ICO, 2015) and world tea crop production in 2013 was 5.3 million tonnes (FAOSTAT, 2015). The chemical composition of tea varies depending on the type, but the largest proportion generally comprises polyphenols, as well as sugars, some amino acids, lipids and some minerals (Harbowy et al., 1997). Similarly, coffee varies depending on the type, but major constituents are fatty acids, hydrocarbons and sterols (Pujol et al., 2013).

### **4.2.1 Current Uses**

Coffee and tea grounds/leaves are most commonly disposed of in compost or in landfill disposal. Coffee grains can be beneficial for vermicomposting, by allowing the kitchen waste to become more stable for earthworm populations (Adi and Noor, 2009). Biofuel production has also proved successful with coffee grains (Caetano et al., 2014). However, if a potential use is identified, it would reduce the need for landfill. Studies have also been carried out to investigate the preparation of activated carbon from these wastes by pyrolysis (Reffas et al., 2010) and acid impregnation for improved adsorption of dyes (Ma and Ouyang, 2013).

#### **4.2.2 Potential for use in water treatment**

Coffee grounds (Safarik et al., 2012) and tea grains have been used successfully in dye adsorption (Nasuha et al., 2010), which can be used to indicate a potential for use in cationic adsorption requirements (Franca et al., 2009). Metal removal has been achieved using both coffee grounds and tea leaf wastes (Djati Utomo and Hunter, 2010). Phenol removal has also been successful with activated carbon prepared from coffee residue (Lamine et al., 2014). Wang et al. (2014) reported a  $\text{NO}_3^-$ -N removal efficiency of almost 52% using green tea extract.

The above evidence would suggest that there is scope for tea and coffee wastes to be used in a technology for water treatment, particularly for adsorption of cationic compounds; however, further analysis is required on nutrient and carbon adsorption to fully understand the benefits.

#### **4.3 Rice husk**

Rice husks (hulls) are the outer covering on the grain, separated from rice during milling. In Asia, 700 million tonnes of rice husk are produced annually (Santiaguel, 2013), accounting for 92% of the worldwide rice production (Ricehusk.com, 2015). The chemical composition of rice husk includes cellulose, hemicellulose, lignin, silica, ash, and protein (Krishnani et al., 2008).

##### **4.3.1 Current Uses**

Rice husk was generally considered a waste product, but in recent years, it has become a commodity, and has uses such as power production (from biomass gasification) and a raw material for chopstick manufacture (Santiaguel, 2013). It can also be used in horticulture, animal bedding,

and as a material in composites (Ricehusk.com, 2015). Thermal treatment of the husk can aid in oil (Angelova et al., 2011) and petroleum adsorption (Kenes et al., 2012).

When rice husk is burnt, it produces an ash, with a high silica content, that can be used in concrete production and insulation products (Singhania, 2004). The ash has also been used in purification methods, such as the preparation of biodiesel from frying oil (Manique et al., 2012). Similarly, oil polluted water can be cleaned using the ash (Vlaev et al., 2011).

#### **4.3.2 Potential for use in water treatment**

From various studies and reviews, it is clear that rice husk is a successful adsorbent (Ahmaruzzaman and Gupta, 2011). K: Freundlich adsorption capacity factor

Table 14 K: Freundlich adsorption capacity factor

ACCEPTED MANUSCRIPT

1

2 Table 14 details the previous adsorption studies of the contaminants examined in this review,  
3 indicating that rice husk can be used in a treatment technology.

4 Rice husk has proven to adsorb metals from wastewater successfully, particularly when used  
5 as a starting material for activated carbon preparation (Daifullah et al., 2003). A partial alkali  
6 digestion of rice husk also improved the metal binding ability, showing a good affinity for  
7 eight different heavy metals (Krishnani et al., 2008). Mohan and Sreelakshmi (2008) found  
8 that treating rice husk with P increased its affinity for metal adsorption. Other studies confirm  
9 the affinity of rice husk for adsorption of metals such as Cd (Ye et al., 2010), nickel and Zn  
10 (Srivastava et al., 2007), and Pb and mercury (Feng et al., 2004), and also for dye adsorption  
11 (Kumar et al., 2014). Rice husk ash can also be used as a precursor to activated carbon, which  
12 has been successful for dye removal (Liu et al., 2012).

13 To further assess the potential of using rice husk in a water treatment technology, it is  
14 necessary to compare the advantages to its current uses, to ensure it is a viable adsorption  
15 source. It is also necessary to assess the cost of having to modify the husk, compared to using  
16 a raw, untreated material.

## 17 **5 Construction and demolition waste**

18 Construction and demolition wastes encompass a wide variety of media, from wood, metals  
19 and plastics, to textiles and paper, oils and minerals (Eurostat, 2013). Figure 4 shows the  
20 composition of C&D wastes, for EU member states, excluding Estonia and Finland  
21 (European Commission, 2011). Large quantities of C&D waste is produced every year and it  
22 accounts for 25-30% of all waste in the EU (European Commission, 2015b). Although  
23 recycling efforts are substantial (greater than 50%), there is still a necessity for further re-use  
24 of some of this material (Fischer and Werge, 2009). In 2012 in Europe, 40 million tonnes, of

25 a total 295 million tonnes, of mineral waste from C&D was deposited onto or into land,  
26 meaning there is a large quantity of potential mineral waste available (Eurostat, 2015). This  
27 will allow for compliance with the EU Waste Framework Directive (2008/98/EC; EC, 2008),  
28 which states that recycling efforts must be raised to at least 70% (Fischer and Werge, 2009).  
29 To aid in reaching this target, it is necessary to examine the potential for certain C&D wastes  
30 for other purposes, such as water and wastewater treatment. The wastes of interest in this  
31 review are crushed concrete, masonry waste and wood waste.

## 32 **5.1 Crushed Concrete**

33 Crushed concrete is a waste product from the C&D industry, resulting from the demolition of  
34 buildings and concrete structures. Crushed concrete comprises the largest fraction of C&D  
35 waste (Figure 4), so finding an alternative use is extremely important. It comprises the  
36 standard components of a concrete mixture, aggregates, water, cement and sand. This results  
37 in a chemical composition of Ca oxides, Al oxides and Fe oxides (Egemose et al., 2012).

38 Production of crushed concrete arises from the need to reduce landfill waste from all  
39 industries, including the C&D industry, with crushing meaning it is more suitable for use  
40 elsewhere. Debris and rubble from buildings that have been damaged in destructive  
41 earthquakes, along with regeneration demolition, and rebuilding roads and runways result in  
42 large amounts of waste. The debris is crushed and ground using various techniques dependent  
43 on the required use (Topçu and Şengel, 2004).

### 44 **5.1.1 Current Uses**

45 A certain amount of old concrete from the C&D sector still goes to landfill. Crushed concrete  
46 can be reused as a form of aggregate; however, this must be done with caution, as increasing  
47 amounts of waste concrete aggregate can decrease density, workability, hardness and  
48 compressive strength (Topçu, 1997).

### 49 **5.1.2 Potential for use in water treatment**

50 Table 15 details previous work on adsorption studies using crushed concrete. Egemose et al.  
51 (2012) investigated the use of crushed concrete as a filter material for urban and agricultural  
52 runoff. The study found that it was effective in P removal, but observed that caution must be  
53 taken to ensure the pH and alkalinity of the effluent is controlled. During a column study to  
54 treat secondary effluent wastewater from a municipal wastewater treatment plant, Berg et al.  
55 (2005) discovered that although crushed gas concrete (lightweight concrete) was effective at  
56 reducing the concentration of P by 80-100%, the DOC was unchanged, meaning crushed  
57 concrete may not be effective as a stand-alone filter media, depending on the contaminants in  
58 question. Crushed concrete has shown potential for metal adsorption, with successful  
59 adsorption of Cu, Zn and Pb (Coleman et al., 2005). There are indications that crushed  
60 concrete may be a successful filter media for removal of contaminants from aqueous  
61 solutions, but further work would have to be carried out across a broad spectrum of  
62 contaminants to fully assess its potential.

### 63 **5.2 Masonry**

64 Masonry waste comprises a large proportion of the C&D waste generated in the EU (Figure  
65 4), approximately 30%, and is classified under the same waste stream as concrete and  
66 gypsum-based materials. It refers to a mixed waste comprising bricks, tiles and ceramics, and  
67 any other masonry rubble; and can arise from construction of civil infrastructure, or from  
68 demolition (European Commission, 1999). The properties of masonry, both physical and  
69 chemical, vary depending on the proportions of the components present in any one sample  
70 (del Rio Merino et al., 2010). It can also vary depending on location, given that different  
71 regions may use different types of bricks. In some countries, such as Pakistan, brick powder  
72 is readily available and may have few costs associated with its use (Bibi et al., 2015). In

73 general, it comprises silicate minerals, rich in silicon, Al oxides and hydroxides (Naceri and  
74 Hamina, 2009).

### 75 **5.2.1 Current Uses**

76 Masonry waste from the C&D industry can be reused in the same industry, particularly as  
77 aggregate for concrete production, mortars, roof elements, concrete blocks and concrete tiles  
78 (del Rio Merino et al., 2010). There have also been studies carried out to investigate the use  
79 of masonry waste as a replacement of clinker in cement (Naceri and Hamina, 2009), and as a  
80 pozzolonic admixture (Lavati et al., 2009).

### 81 **5.2.2 Potential for use in water treatment**

82 Table 16 details the studies which have investigated those contaminants of interest in this  
83 review. Crushed brick has been used to remove dye from aqueous solutions effectively  
84 (Hamdaoui, 2006). Metals, such as Cu (Djeribi and Hamdaoui, 2008) and mercury (Labidi,  
85 2008), have also been removed from aqueous solutions using crushed brick. Brick has also  
86 been used for microbiological adsorption, with *Clostridium beijerinckii* found to adsorb onto  
87 the surface (Qureshi et al., 2000). Ceramics have also been used in contaminant removal from  
88 aqueous solutions. Fluoride has been successfully adsorbed by granular ceramic (Chen et al.,  
89 2011), and silica ceramic has been used to remove arsenic from aqueous solution (Salim and  
90 Munekage 2009). Brick powder has also been successfully used for both fluoride and arsenic  
91 removal (Bibi et al., 2015).

92 It is clear that there is potential in the use of masonry waste as an adsorbent for water  
93 treatment. With the ability to adsorb such a variety of contaminants, the next step would be to  
94 assess its potential to adsorb multiple contaminants simultaneously. The biggest  
95 disadvantage, however, is the lack of uniformity. Depending on the source, the masonry  
96 waste composition could have a huge variance, which will in turn affect the potential for use.

### 97 **5.3 Wood waste**

98 Although wood waste only accounts for 2% of the EU C&D waste (Figure 4), it is a relevant  
99 waste to investigate, given that in certain countries this figure may be higher. For example, in  
100 Ireland, in 2010, wood accounted for 5% of total C&D waste collected, amounting to 45,000  
101 tonnes (EPA, 2010). Wood waste can arise from discarded treated and untreated wood  
102 products, off-cuts, shavings, chip and dust from wood processing and virgin wood mixed in  
103 with waste wood (EPA, 2013). The composition of wood varies depending on the source of  
104 the timber. It is imperative to encourage the use of wood in a material recovery sense, as  
105 currently a significant proportion is used in energy (Dahlbo et al., 2015).

#### 106 **5.3.1 Current Uses**

107 Waste wood has many different uses, including fuel, landscaping, bedding, composite  
108 boarding manufacture, landfill cover and composting. It can be used both as biofuel and as a  
109 fuel in its raw state (Lippke et al., 2012). However, the use of waste wood as fuel brings  
110 environmental concerns, given the likelihood of halogenated organic compounds or heavy  
111 metals to be present, following preservation methods (EPA, 2013).

#### 112 **5.3.2 Potential for use in water treatment**

113 Wood waste, in the form of wood chips, has been successfully used in adsorption of dye from  
114 aqueous solutions (Nigam et al., 2000). Sawdust has been successfully used in the same way  
115 (Hanafiah et al., 2012). Wood also has good capacities for metal adsorption (Rafatullah et al.,  
116 2012). Alternative methods for using wood waste in water treatment would be as a biochar,  
117 for nutrient (Wang et al., 2015), perchlorate (Fang et al., 2014), or metal adsorption (Jiang et  
118 al., 2015); or as an activated carbon, for dye (Ma et al., 2014) and metal adsorption (Lo et al.,  
119 2012). Table 17 details adsorption studies that have been carried out using relevant  
120 contaminants, mainly in the form of biochar adsorption, indicating that there is a possibility  
121 of using this material, though further research should be carried out.

122 It is clear that waste wood does have potential for use in water treatment. However, there will  
123 be a lot of variability depending on the original type of wood used. Another issue could be  
124 the release of organics into the water. To avoid a release, a pre-treatment could be advised  
125 and perhaps the use of a multi-media technology to harness different sorption capacities.

## 126 **6 Post-treatment use of media**

127 It is clear from the review of previous studies that the scope for alternative media use as  
128 adsorbents in water treatment is broad, encompassing many types of media and contaminants.  
129 However, a problem still remains with disposal of the media post-treatment. The recycling of  
130 waste does often create larger environmental benefits, particularly than energy recovery  
131 methods, but this is not always the case and should be carefully analysed (Dahlbo et al.,  
132 2015). Although adsorption can create a purpose for an otherwise discarded material,  
133 adsorption is not an infinite solution. Once used in an adsorption system in water treatment, it  
134 will be necessary to either regenerate or find a safe disposal mechanism for the media. This  
135 will also ensure any contaminants adsorbed onto the media will not pollute land or water.

136 The use of the media post-treatment depends on the constituents of the water it was used to  
137 treat. If the raw water contained heavy metals, it is necessary to ensure that metals would not  
138 pose a threat to the next purpose of the media. In the case of adsorption of organic pollutants,  
139 successful regeneration and desorption techniques, such as biological degradation, chemical  
140 desorption, oxidation, and thermal desorption, may be used to restore the quality of the media  
141 (Zhu et al., 2009). Where nutrients are problematic contaminants, land fertilisation may be a  
142 potential area of utilisation post-treatment. This would be doubly beneficial as it would  
143 improve the land quality and provide a useful purpose for what is otherwise a waste material.

## 144 **6.1 Regeneration**

145 It is recognised that there exists a knowledge gap on large-scale regeneration of adsorbents,  
146 particularly non-carbonaceous adsorbents (Omorie et al., 2014). Traditional regeneration  
147 techniques include thermal, chemical, and bioregeneration. Emerging regeneration techniques  
148 include electrochemical, ultrasound, oxidation, and supercritical fluid methods (Duan et al.,  
149 2013). Although many of these techniques have proved effective, it is necessary to implement  
150 large-scale regeneration of media, for both economic and environmental benefits (Omorie  
151 et al., 2014).

152 Regeneration of metal oxides, such as fly ash and Bayer residue, has not been extensively  
153 studied. The studies which have been carried out tend to refer to treated media, such as  
154 impregnated fly ash (Yang et al., 2016) or activated carbon prepared from fly ash (Aslam et  
155 al., 2015). However, it has been found that where these media have been used to adsorb  
156 various metals, it can make the media more stable (Jacukowicz-Sobala et al., 2015). It has  
157 also been shown that methods such as thermal desorption can be used to restore the media to  
158 its previous condition (Yang et al., 2016). This can result in the media being used for land  
159 reclamation, or in construction methods such as those mentioned in the “current uses”  
160 sections above. Fly ash, once exhausted from certain adsorbents, can be used as a filler in  
161 paper-making with few side-effects (Saakshy et al., 2015). Although similar studies have not  
162 been carried out in relation to GGBS, the chemical composition would suggest similar  
163 potential. The United States Environmental Protection Agency (USEPA) have developed a  
164 number of tests which can be used to investigate the potential leaching and toxicity of spent  
165 sorption material and suitability for use on land (Jacukowicz-Sobala et al., 2015).

166 Regeneration of coconut shell activated carbon is well researched, with up to five adsorption-  
167 regeneration cycles being tested. For adsorption of gaseous sulphur, complete regeneration  
168 can be achieved using water vapour (Shi et al., 2015). Microwave regeneration was not as

169 effective when used to regenerate from benzene and toluene adsorption, achieving just 50%  
170 removal efficiency after five cycles (Mohammed et al., 2015). Thermal regeneration with  
171 0.1M NaOH was very effective for regeneration from Pb removal, with removal efficiencies  
172 of over 90% after cycling (Itodo et al., 2014). Other activated carbons have been regenerated  
173 successfully by electrical-assisted acid washing (Weng et al., 2014), supercritical carbon  
174 dioxide operating conditions (Carmona et al., 2014), and pyrite-activated sodium persulfate  
175 oxidation (Liang and Chen, 2010).

176 Similar to the other agricultural wastes, several regeneration techniques have proved  
177 successful for both tea wastes (Fadhil et al., 2012) and coffee wastes (Plaza et al., 2012).  
178 These wastes can be used as a source material for activated carbon and so respond well to  
179 regeneration. Although regeneration can still mean the pollutant is present, it becomes  
180 concentrated, and thus may be more easily disposed of (Kyzas, 2012), while the material can  
181 be returned to its original state. Alternative disposal mechanisms include manufacturing  
182 blended fuel briquettes from tea and coffee wastes, due to high calorific values (Nandal et al.,  
183 2014).

184 Bioregeneration has successfully been used for rice husk regeneration (Aktas and Cecen,  
185 2007), as have chemical techniques. Chemically modified rice husk for mercury adsorption  
186 was successfully regenerated using 0.1M HCl, only losing 10% adsorption capacity (Song et  
187 al., 2016). Regeneration by NaOH has been successfully used for rice husk that has been used  
188 for arsenate (Luo et al., 2016) and Pb adsorption (Masoumi et al., 2016). Rice husk ash, a  
189 product of the incineration of rice husk, has many uses including catalyst carriers, fillers in  
190 cement, fertilisers, and production of gels and polymers (Kumar et al., 2016). This would be a  
191 useful post-treatment use of rice husk, provided that the contaminants would be contained  
192 and not leached to the environment.

193 Construction and demolition wastes are not well researched in terms of regeneration  
194 processes. Where an activated carbon was produced from wood waste, regeneration would be  
195 most likely successful. For concrete and masonry, depending on the source water  
196 contaminants, there is potential for use as aggregate or fill in the construction industry.  
197 However, extensive testing would be necessary to ensure no damage would occur to the  
198 environment.

199

## 200 **6.2 Economic and environmental outlook**

201 When considering regeneration techniques, it is important to recognise the economic and  
202 environmental costs of regeneration techniques. Where acid regeneration is used, it can be  
203 corrosive and difficult to store. Thermal regeneration techniques can require complex  
204 instrumentation and large capital expenditure (Aslam et al., 2015). Regeneration can also  
205 produce a high concentrate waste stream, which can bring about further issues of waste  
206 management (Igunnu and Chen, 2012). Therefore, it is important to analyse filter media  
207 holistically, including potential regeneration and costs, to ensure the most sustainable  
208 approach is taken.

209 It is important ensure that the use of the media in water treatment does not devalue the  
210 original product. Desorption techniques may be used to restore the product, although it may  
211 create another issue regarding waste creation as the pollutant will now be concentrated. In  
212 some instances, the original product may become more stable, and may still be useful in its  
213 current uses. In other cases, for example when used for nutrient capture, the media may then  
214 be used as a fertiliser. The ultimate use of the media will depend on the raw water being  
215 treated, and how that impacts on the media. However, it is clear that this is an area worth  
216 researching with clear gaps in knowledge evident.

217 The notion of a ‘circular economy’ requires products, materials, and services to be  
218 maintained within the economy for as long as possible, and is a major step towards a zero-  
219 waste society (European Commission, 2015c). Although the utilisation of these products does  
220 not result in an infinitely long solution, and further disposal mechanisms must be  
221 investigated, it does result in a more sustainable use for waste products. Evidently, in certain  
222 circumstances, regeneration of adsorption material is a possibility, although there is a large  
223 scope for further research in this area. The European Commission have identified waste  
224 management as a critical aspect of the circular economy, and recognises the need to involve  
225 public authorities, businesses, and investors (European Commission, 2015c). In order to fully  
226 engage these entities, it is important to have a viable solution to a difficult-to-solve problem.  
227 If the media can be sufficiently exploited to treat water in a sustainable fashion, those entities  
228 will have an invested interest in aiming to develop the technologies to their full potential.  
229 There is a recognised lack of studies considering industrial symbiosis, logistics and large-  
230 scale operation (Mirabella et al., 2014), and it is clear from the review that there is a large  
231 scope for development in this area. In this instance, the combination of research and industry,  
232 along with public authorities, could work together to fully develop a sustainable method of  
233 removing contaminants from water, while avoiding the creation of waste, and therefore  
234 leading towards a circular economy.

## 235 **7 Conclusion**

236 A brief summary of the advantages and disadvantages of each media, along with the raw  
237 material availability, is presented in Table 18. Where definite amounts are not available,  
238 figures for the parent material have been given. This review indicates that there is a large  
239 scope for use of media in water treatment, therefore mitigating current environmental issues  
240 such as waste disposal and storage, while aiming to improve water treatment services  
241 globally.

242 It is important to note that some media can also be successfully regenerated, once the  
243 adsorption potential has been reached, meaning that the filter can be used incurring much less  
244 cost than a full replacement. With the use of alternative media, clogging should also be  
245 considered. Certain media, although successful adsorbents, may have too fine a particle size,  
246 and become clogged within a short period of operation. This can be tested fully at a pilot-  
247 scale test.

248 It is, however, important to proceed with caution regarding some of the media, where there is  
249 a potential release of toxins or where the pre-treatment costs may not allow for a sustainable  
250 approach to be taken. Further recommendations, following this review, are to test the media  
251 at larger scale, both individually and also in a multi-layer configuration, where it would be  
252 possible to harness the varying adsorptive qualities of different media.

### 253 **Acknowledgements**

254 The authors would like to acknowledge the financial support of the Environmental Protection  
255 Agency (EPA).

### 256 **References**

- 257 Adamczuk, A., Kołodyńska, D., 2015. Equilibrium, thermodynamic and kinetic studies on  
258 removal of chromium, copper, zinc and arsenic from aqueous solutions onto fly ash  
259 coated by chitosan. *Chem. Eng. J.* 274, 200–212. doi:10.1016/j.cej.2015.03.088
- 260 Adi, a. J., Noor, Z.M., 2009. Waste recycling: Utilization of coffee grounds and kitchen  
261 waste in vermicomposting. *Bioresour. Technol.* 100, 1027–1030.  
262 doi:10.1016/j.biortech.2008.07.024
- 263 Agrawal, S.G., King, K.W., Fischer, E.N., Woner, D.N., 2011. PO 4 3– Removal by and  
264 Permeability of Industrial Byproducts and Minerals: Granulated Blast Furnace Slag,  
265 Cement Kiln Dust, Coconut Shell Activated Carbon, Silica Sand, and Zeolite. *Water,  
266 Air, Soil Pollut.* 219, 91–101. doi:10.1007/s11270-010-0686-4
- 267 Agyei, N.M., Strydom, C. a., Potgieter, J.H., 2002. The removal of phosphate ions from  
268 aqueous solution by fly ash, slag, ordinary Portland cement and related blends. *Cem.  
269 Concr. Res.* 32, 1889–1897. doi:10.1016/S0008-8846(02)00888-8
- 270 Ahmaruzzaman, M., 2010. A review on the utilization of fly ash. *Prog. Energy Combust. Sci.*  
271 36, 327–363. doi:10.1016/j.pecs.2009.11.003
- 272 Ahmaruzzaman, M., Gupta, V.K., 2011. Rice Husk and Its Ash as Low-Cost Adsorbents in

- 273 Water and Wastewater Treatment. *Ind. Eng. Chem. Res.* 50, 13589–13613.
- 274 Ahmed, Z.T., Hand, D.W., 2014. Quantification of the adsorption capacity of fly ash. *Ind.*  
275 *Eng. Chem. Res.* 53, 6985–6989. doi:10.1021/ie500484d
- 276 Aktas, O., Cecen, F., 2007. Bioregeneration of activated carbon: A review. *Int. Biodeterior.*  
277 *Biodegrad.* 59, 257–272. doi:10.1016/j.ibiod.2007.01.003
- 278 Ali, I., Gupta, V.K., 2006. Advances in water treatment by adsorption technology. *Nat.*  
279 *Protoc.* 1, 2661–7. doi:10.1038/nprot.2006.370
- 280 Alinnor, I.J., 2007. Adsorption of heavy metal ions from aqueous solution by fly ash. *Fuel* 86,  
281 853–857. doi:10.1016/j.fuel.2006.08.019
- 282 An, C., Huang, G., 2012. Stepwise adsorption of phenanthrene at the fly ash-water interface  
283 as affected by solution chemistry: Experimental and modeling studies. *Environ. Sci.*  
284 *Technol.* 46, 12742–12750. doi:10.1021/es3035158
- 285 Andersson, K.I., Eriksson, M., Norgren, M., 2011. Removal of lignin from wastewater  
286 generated by mechanical pulping using activated charcoal and fly ash: Adsorption  
287 isotherms and thermodynamics. *Ind. Eng. Chem. Res.* 50, 7722–7732.  
288 doi:10.1021/ie200378s
- 289 Angelova, D., Uzunov, I., Uzunova, S., Gigova, a., Minchev, L., 2011. Kinetics of oil and oil  
290 products adsorption by carbonized rice husks. *Chem. Eng. J.* 172, 306–311.  
291 doi:10.1016/j.cej.2011.05.114
- 292 Aslam, Z., Shawabkeh, R.A., Hussein, I.A., Al-Baghli, N., Eic, M., 2015. Synthesis of  
293 activated carbon from oil fly ash for removal of H<sub>2</sub>S from gas stream. *Appl. Surf. Sci.*  
294 327, 107–115. doi:10.1016/j.apsusc.2014.11.152
- 295 Bagatin, R., Klemes, J.J., Reverberi, A.P., Huisingh, D., 2014. Conservation and  
296 improvements in water resource management: A global challenge. *J. Clean. Prod.* 77, 1–  
297 9. doi:10.1016/j.jclepro.2014.04.027
- 298 Berg, U., Donnert, D., Ehbrecht, a., Bumiller, W., Kusche, I., Weidler, P.G., Nüesch, R.,  
299 2005. “Active filtration” for the elimination and recovery of phosphorus from waste  
300 water. *Colloids Surfaces A Physicochem. Eng. Asp.* 265, 141–148.  
301 doi:10.1016/j.colsurfa.2004.10.135
- 302 Bhatnagar, A., Kumar, E., Sillanpää, M., 2011. Fluoride removal from water by adsorption—  
303 A review. *Chem. Eng. J.* 171, 811–840. doi:10.1016/j.cej.2011.05.028
- 304 Bhatnagar, A., Sillanpää, M., 2011. A review of emerging adsorbents for nitrate removal  
305 from water. *Chem. Eng. J.* 168, 493–504. doi:10.1016/j.cej.2011.01.103
- 306 Bhatnagar, A., Sillanpää, M., 2010. Utilization of agro-industrial and municipal waste  
307 materials as potential adsorbents for water treatment—A review. *Chem. Eng. J.* 157,  
308 277–296. doi:10.1016/j.cej.2010.01.007
- 309 Bhatnagar, A., Sillanpää, M., Witek-Krowiak, A., 2015. Agricultural “waste peels” as  
310 versatile biomass for water purification – A review. *Chem. Eng. J.* 270, 244–271.  
311 doi:10.1016/j.cej.2015.01.135
- 312 Bhatnagar, A., Vilar, V.J.P., Botelho, C.M.S., Boaventura, R. a. R., 2010. Coconut-based  
313 biosorbents for water treatment — A review of the recent literature. *Adv. Colloid*  
314 *Interface Sci.* 160, 1–15. doi:10.1016/j.cis.2010.06.011

- 315 Bibi, S., Farooqi, A., Hussain, K., Haider, N., 2015. Evaluation of industrial based adsorbents  
316 for simultaneous removal of arsenic and fluoride from drinking water. *J. Clean. Prod.*  
317 87, 882–896. doi:10.1016/j.jclepro.2014.09.030
- 318 Boopathy, R., Karthikeyan, S., Mandal, A.B., Sekaran, G., 2013. Adsorption of ammonium  
319 ion by coconut shell-activated carbon from aqueous solution: kinetic, isotherm, and  
320 thermodynamic studies. *Environ. Sci. Pollut. Res. Int.* 20, 533–42. doi:10.1007/s11356-  
321 012-0911-3
- 322 Brunori, C., Cremisini, C., Massanisso, P., Pinto, V., Torricelli, L., 2005. Reuse of a treated  
323 red mud bauxite waste: studies on environmental compatibility. *J. Hazard. Mater.* 117,  
324 55–63. doi:10.1016/j.jhazmat.2004.09.010
- 325 Caetano, N.S., Silva, V.F.M., Melo, A.C., Martins, A.A., Mata, T.M., 2014. Spent coffee  
326 grounds for biodiesel production and other applications. *Clean Technol. Environ. Policy*  
327 16, 1423–1430. doi:10.1007/s10098-014-0773-0
- 328 Carmona, M., Garcia, M.T., Carnicer, Á., Madrid, M., Rodríguez, J.F., 2014. Adsorption of  
329 phenol and chlorophenols onto granular activated carbon and their desorption by  
330 supercritical CO<sub>2</sub>. *J. Chem. Technol. Biotechnol.* 89, 1660–1667. doi:10.1002/jctb.4233
- 331 Cazetta, A.L., Vargas, A.M.M., Nogami, E.M., Kunita, M.H., Guilherme, M.R., Martins,  
332 A.C., Silva, T.L., Moraes, J.C.G., Almeida, V.C., 2011. NaOH-activated carbon of high  
333 surface area produced from coconut shell: Kinetics and equilibrium studies from the  
334 methylene blue adsorption. *Chem. Eng. J.* 174, 117–125. doi:10.1016/j.cej.2011.08.058
- 335 Cengeloglu, Y., Tor, A., Ersoz, M., Arslan, G., 2006. Removal of nitrate from aqueous  
336 solution by using red mud. *Sep. Purif. Technol.* 51, 374–378.  
337 doi:10.1016/j.seppur.2006.02.020
- 338 Chen, J., Kong, H., Wu, D., Chen, X., Zhang, D., Sun, Z., 2007. Phosphate immobilization  
339 from aqueous solution by fly ashes in relation to their composition. *J. Hazard. Mater.*  
340 139, 293–300. doi:10.1016/j.jhazmat.2006.06.034
- 341 Chen, J., Kong, H., Wu, D., Hu, Z., Wang, Z., Wang, Y., 2006. Removal of phosphate from  
342 aqueous solution by zeolite synthesized from fly ash. *J. Colloid Interface Sci.* 300, 491–  
343 497. doi:10.1016/j.jcis.2006.04.010
- 344 Chen, N., Feng, C., Zhang, Z., Liu, R., Gao, Y., Li, M., Sugiura, N., 2012. Preparation and  
345 characterization of lanthanum(III) loaded granular ceramic for phosphorus adsorption  
346 from aqueous solution. *J. Taiwan Inst. Chem. Eng.* 43, 783–789.  
347 doi:10.1016/j.jtice.2012.04.003
- 348 Chen, N., Zhang, Z., Feng, C., Li, M., Zhu, D., Sugiura, N., 2011. Studies on fluoride  
349 adsorption of iron-impregnated granular ceramics from aqueous solution. *Mater. Chem.*  
350 *Phys.* 125, 293–298. doi:10.1016/j.matchemphys.2010.09.037
- 351 Chen, S., Fang, L., Zhu, Q., Li, L., Xing, Z., 2016. Bromate removal by Fe(II)-  
352 akaganeite ( $\beta$ -FeOOH) modified red mud granule material. *RSC Adv.* 6, 28257–28262.  
353 doi:10.1039/C6RA01206J
- 354 Chintala, R., Mollinedo, J., Schumacher, T.E., Papiernik, S.K., Malo, D.D., Clay, D.E.,  
355 Kumar, S., Gulbrandson, D.W., 2013. Nitrate sorption and desorption in biochars from  
356 fast pyrolysis. *Microporous Mesoporous Mater.* 179, 250–257.  
357 doi:10.1016/j.micromeso.2013.05.023

- 358 Chou, J.-D., Wey, M.-Y., Liang, H.-H., Chang, S.-H., 2009. Biotoxicity evaluation of fly ash  
359 and bottom ash from different municipal solid waste incinerators. *J. Hazard. Mater.* 168,  
360 197–202. doi:10.1016/j.jhazmat.2009.02.023
- 361 Coleman, N., Lee, W., Slipper, I., 2005. Interactions of aqueous Cu, Zn and Pb ions with  
362 crushed concrete fines. *J. Hazard. Mater.* 121, 203–213.  
363 doi:10.1016/j.jhazmat.2005.02.009
- 364 Cooney, D.O., 1999. Adsorption design for wastewater treatment, 1st ed. CRC Lewis, Boca  
365 Raton, FL.
- 366 Dahlbo, H., Bacher, J., Lahtinen, K., Jouttijarvi, T., Suoheimo, P., Mattila, T., Sironen, S.,  
367 Myllymaa, T., Saramaki, K., 2015. Construction and demolition waste management - A  
368 holistic evaluation of environmental performance. *J. Clean. Prod.* 107, 333–341.  
369 doi:10.1016/j.jclepro.2015.02.073
- 370 Daifullah, a. a M., Girgis, B.S., Gad, H.M.H., 2004. A study of the factors affecting the  
371 removal of humic acid by activated carbon prepared from biomass material. *Colloids  
372 Surfaces A Physicochem. Eng. Asp.* 235, 1–10. doi:10.1016/j.colsurfa.2003.12.020
- 373 Daifullah, a. a M., Girgis, B.S., Gad, H.M.H., 2003. Utilization of agro-residues (rice husk)  
374 in small waste water treatment plans. *Mater. Lett.* 57, 1723–1731. doi:10.1016/S0167-  
375 577X(02)01058-3
- 376 Daud, W., 2004. Comparison on pore development of activated carbon produced from palm  
377 shell and coconut shell. *Bioresour. Technol.* 93, 63–69.  
378 doi:10.1016/j.biortech.2003.09.015
- 379 de Lima, A.C. a., Nascimento, R.F., de Sousa, F.F., Filho, J.M., Oliveira, A.C., 2012.  
380 Modified coconut shell fibers: A green and economical sorbent for the removal of  
381 anions from aqueous solutions. *Chem. Eng. J.* 185-186, 274–284.  
382 doi:10.1016/j.cej.2012.01.037
- 383 Deelwal, K., Dharavath, K., Kulshreshtha, M., 2014. Evaluation of characteristic properties  
384 of red mud for possible use as a geotechnical material in civil construction. *Int. J. Adv.  
385 Eng. Technol.* 7, 1053–1059.
- 386 del Rio Merino, M., Izquierdo Gracia, P., Weis Azevedo, I.S., 2010. Sustainable  
387 construction: construction and demolition waste reconsidered. *Waste Manag. Res.* 28,  
388 118–129. doi:10.1177/0734242X09103841
- 389 Djati Utomo, H., Hunter, K. a., 2010. Particle concentration effect: Adsorption of divalent  
390 metal ions on coffee grounds. *Bioresour. Technol.* 101, 1482–1486.  
391 doi:10.1016/j.biortech.2009.06.094
- 392 Djeribi, R., Hamdaoui, O., 2008. Sorption of copper(II) from aqueous solutions by cedar  
393 sawdust and crushed brick. *Desalination* 225, 95–112. doi:10.1016/j.desal.2007.04.091
- 394 Duan, S.M., Jia, M., Hu, J.W., Huang, X.F., Wang, Y., Fu, L.Y., Li, Z. Bin, Liu, C., Luo, J.,  
395 2013. Optimization of Ultrasonic-Assisted Regeneration Process for Coconut Shell  
396 Activated Carbon Based on Response Surface Method. *Adv. Mater. Res.* 788, 450–455.  
397 doi:10.4028/www.scientific.net/AMR.788.450
- 398 Duran, X., Lenihan, H., O'Regan, B., 2006. A model for assessing the economic viability of  
399 construction and demolition waste recycling—the case of Ireland. *Resour. Conserv.  
400 Recycl.* 46, 302–320. doi:10.1016/j.resconrec.2005.08.003

- 401 EAA, 2013. Bauxite Residue Management : Best Practice. London, UK.
- 402 Ecoba, 2015. European Coal Combusion Products Association Specification [WWW  
403 Document]. URL [www.ecoba.com/ecobaccpspec.html](http://www.ecoba.com/ecobaccpspec.html) (accessed 8.18.15).
- 404 Ecocem, 2015. Ecocem - about GGBS [WWW Document]. URL  
405 [www.ecocem.ie/technical,ggbs.htm](http://www.ecocem.ie/technical,ggbs.htm) (accessed 8.26.15).
- 406 Ecocem, 2012. GGBS Material safety data sheet [WWW Document]. URL  
407 [www.ecocem.ie/technical,safety\\_data.htm](http://www.ecocem.ie/technical,safety_data.htm) (accessed 8.26.15).
- 408 Egemose, S., Sonderup, M.J., Beinthin, M. V., Reitzel, K., Hoffmann, C.C., Flindt, M.R.,  
409 2012. Crushed Concrete as a Phosphate Binding Material: A potential new management  
410 tool. *J. Environ. Qual.* 647–653.
- 411 EPA, 2015a. Water Quality in Ireland 2010 - 2012. Johnstown Castle, Wexford, Ireland.
- 412 EPA, 2015b. Drinking Water Report 2013. Johnstown Castle, Wexford, Ireland.
- 413 EPA, 2013. The regulation and management of waste wood. Johnstown Castle, Wexford,  
414 Ireland.
- 415 EPA, 2012. Drinking Water Guidance on Disinfection By-Products Advice Note No. 4.  
416 Version 2. Disinfection By-Products in Drinking Water. Johnstown Castle, Wexford,  
417 Ireland.
- 418 EPA, 2010. National Waste Report 2010. Johnstown Castle, Wexford, Ireland.
- 419 EPA, 1995. Water Treatment Manuals: Filtration. Johnstown Castle, Wexford, Ireland.
- 420 ESB Moneypoint, 2012. Substance Information Sheet (SIS) for Ashes (residues), coal.  
421 Kilrush, Clare.
- 422 European Commission, 2015a. EU agriculture spending focused on results. Brussels,  
423 Belgium.
- 424 European Commission, 2015b. Construction and Demolition Waste [WWW Document].  
425 CDW. URL [ec.europa.eu/environment/waste/construction\\_demolition.htm](http://ec.europa.eu/environment/waste/construction_demolition.htm) (accessed  
426 10.1.15).
- 427 European Commission, 2015c. COM(2015) 614 Communication from the commission to the  
428 European Parliament, the Council, the European Economic and Social Committee and  
429 the Committee of the regions - Closing the loop - An EU action plan for the circular  
430 economy. Brussels.
- 431 European Commission, 2011. Service contract on management of construction and  
432 demolition waste - SR1. Final Report Task 2. Paris, France.  
433 doi:ENV.G.4/FRA/2008/0112
- 434 European Commission, 1999. Construction and Demolition Waste Management Practices,  
435 and Their Economic Impacts, Report to DGXI, European Commission. UK, Germany,  
436 Denmark and Netherlands.
- 437 Eurostat, 2015. Waste statistics - Statistics Explained [WWW Document]. Waste Stat. - Stat.  
438 Explain. URL [ec.europa.eu/eurostat/statistics-explained/index.php/Waste\\_statistics](http://ec.europa.eu/eurostat/statistics-explained/index.php/Waste_statistics)  
439 (accessed 11.3.15).
- 440 Eurostat, 2013. Manual on waste statistics: A handbook for data collection on waste  
441 generation and treatment. Luxemburg.

- 442 Eurostat, 2010. Manual on waste statistics. Luxemburg.
- 443 Fadhil, A.B., Dheyab, M.M., Abdul-Qader, A.Q.Y., 2012. Purification of biodiesel using  
444 activated carbons produced from spent tea waste. *J. Assoc. Arab Univ. Basic Appl. Sci.*  
445 11, 45–49. doi:10.1016/j.jaubas.2011.12.001
- 446 Fan, a M., Steinberg, V.E., 1996. Health implications of nitrate and nitrite in drinking water:  
447 an update on methemoglobinemia occurrence and reproductive and developmental  
448 toxicity. *Regul. Toxicol. Pharmacol.* 23, 35–43. doi:10.1006/rtph.1996.0006
- 449 Fang, Q.L., Chen, B.L., Lin, Y.J., Guan, Y.T., 2014. Aromatic and Hydrophobic Surfaces of  
450 Wood-derived Biochar Enhance Perchlorate Adsorption via Hydrogen Bonding to  
451 Oxygen-containing Organic Groups. *Environ. Sci. Technol.* 48, 279–288. doi:Doi  
452 10.1021/Es403711y
- 453 FAO, 2015. Aquastat [WWW Document]. Food Agric. Organ. United Nations. URL  
454 [www.fao.org/nr/water/aquastat/data/query/results.html](http://www.fao.org/nr/water/aquastat/data/query/results.html) (accessed 7.6.15).
- 455 FAO, 2011. Global food losses and food waste [WWW Document]. URL  
456 [www.fao.org/docrep/014/mb060e/mb060e.pdf](http://www.fao.org/docrep/014/mb060e/mb060e.pdf) (accessed 6.7.15).
- 457 FAOSTAT, 2015. FAOSTAT [WWW Document]. Crop Prod. URL  
458 [faostat3.fao.org/download/Q/QC/E](http://faostat3.fao.org/download/Q/QC/E) (accessed 10.12.15).
- 459 Feng, Q., Lin, Q., Gong, F., Sugita, S., Shoya, M., 2004. Adsorption of lead and mercury by  
460 rice husk ash. *J. Colloid Interface Sci.* 278, 1–8. doi:10.1016/j.jcis.2004.05.030
- 461 Feng, S., Xie, S., Zhang, X., Yang, Z., Ding, W., Liao, X., Liu, Y., Chen, C., 2012.  
462 Ammonium removal pathways and microbial community in GAC-sand dual media filter  
463 in drinking water treatment. *J. Environ. Sci.* 24, 1587–1593. doi:10.1016/S1001-  
464 0742(11)60965-0
- 465 Fischer, C., Werge, M., 2009. EU as a Recycling Society: Present Recycling Levels of  
466 Municipal Waste and Construction & Demolition Waste in the EU. Copenhagen.
- 467 Foo, K.Y., Hameed, B.H., 2010. Insights into the modeling of adsorption isotherm systems.  
468 *Chem. Eng. J.* 156, 2–10. doi:10.1016/j.cej.2009.09.013
- 469 Franca, A.S., Oliveira, L.S., Ferreira, M.E., 2009. Kinetics and equilibrium studies of  
470 methylene blue adsorption by spent coffee grounds. *Desalination* 249, 267–272.  
471 doi:10.1016/j.desal.2008.11.017
- 472 Fu, F., Wang, Q., 2011. Removal of heavy metal ions from wastewaters: a review. *J. Environ.*  
473 *Manage.* 92, 407–18. doi:10.1016/j.jenvman.2010.11.011
- 474 Grace, M.A., Healy, M.G., Clifford, E., 2015. Use of industrial by-products and natural  
475 media to adsorb nutrients, metals and organic carbon from drinking water. *Sci. Total*  
476 *Environ.* 518-519, 491–497. doi:10.1016/j.scitotenv.2015.02.075
- 477 Gunasekaran, K., Annadurai, R., Kumar, P.S., 2012. Long term study on compressive and  
478 bond strength of coconut shell aggregate concrete. *Constr. Build. Mater.* 28, 208–215.  
479 doi:10.1016/j.conbuildmat.2011.08.072
- 480 Hamdaoui, O., 2006. Batch study of liquid-phase adsorption of methylene blue using cedar  
481 sawdust and crushed brick. *J. Hazard. Mater.* 135, 264–273.  
482 doi:10.1016/j.jhazmat.2005.11.062
- 483 Han, J.G., Zhao, G., Dou, L.S., Jing, Y.J., Zhu, Y.L., 2013. Adsorption of Ammonium

- 484 Nitrogen in Water by Rice Husk Charcoal: A Simulation Study. *Adv. Mater. Res.* 781-  
485 784, 2063–2066. doi:10.4028/www.scientific.net/AMR.781-784.2063
- 486 Hanafiah, M., Ngah, W., Zolkafly, S.H., Teong, L.C., Majid, Z.A.A., 2012. Acid Blue 25  
487 adsorption on base treated *Shorea dasyphylla* sawdust: Kinetic, isotherm,  
488 thermodynamic and spectroscopic analysis. *J. Environ. Sci.* 24, 261–268.  
489 doi:10.1016/S1001-0742(11)60764-X
- 490 Harbowy, M.E., Balentine, D. a., Davies, A.P., Cai, Y., 1997. *Tea Chemistry*. CRC. Crit.  
491 *Rev. Plant Sci.* 16, 415–480. doi:10.1080/07352689709701956
- 492 Heidrich, C., Feuerborn, H., Weir, A., 2013. *Coal Combustion Products: a Global*  
493 *Perspective*, in: *World of Coal Ash*. Lexington, KY, p. 17.
- 494 Hu, Z., Srinivasan, M., 1999. Preparation of high-surface-area activated carbon from coconut  
495 shell. *Microporous Mesoporous Mater.* 27, 11–18. doi:10.1016/j.carbon.2010.03.059
- 496 Hua, T., Haynes, R.J., Zhou, Y.-F., Boulemant, a, Chandrawana, I., 2014. Potential for use  
497 of industrial waste materials as filter media for removal of Al, Mo, As, V and Ga from  
498 alkaline drainage in constructed wetlands - Adsorption studies. *Water Res.* 71C, 32–41.  
499 doi:10.1016/j.watres.2014.12.036
- 500 Huang, W., Wang, S., Zhu, Z., Li, L., Yao, X., Rudolph, V., Haghseresht, F., 2008.  
501 Phosphate removal from wastewater using red mud. *J. Hazard. Mater.* 158, 35–42.  
502 doi:10.1016/j.jhazmat.2008.01.061
- 503 Hussain, S., Aziz, H., Isa, M., Adlan, M., Asaari, F., 2007. Physico-chemical method for  
504 ammonia removal from synthetic wastewater using limestone and GAC in batch and  
505 column studies. *Bioresour. Technol.* 98, 874–880. doi:10.1016/j.biortech.2006.03.003
- 506 Hussain, S., Aziz, H.A., Isa, M.H., Ahmad, A., Van Leeuwen, J., Zou, L., Beecham, S.,  
507 Umar, M., 2011. Orthophosphate removal from domestic wastewater using limestone  
508 and granular activated carbon. *Desalination* 271, 265–272.  
509 doi:10.1016/j.desal.2010.12.046
- 510 ICO, 2015. International Coffee Organization - The Current State of the Global Coffee Trade  
511 | #CoffeeTradeStats [WWW Document]. *Curr. state Glob. coffee trade*. URL  
512 [www.ico.org/monthly\\_coffee\\_trade\\_stats.asp](http://www.ico.org/monthly_coffee_trade_stats.asp) (accessed 10.12.15).
- 513 Igunnu, E.T., Chen, G.Z., 2012. Produced water treatment technologies. *Int. J. Low-Carbon*  
514 *Technol.* 9, 157–177. doi:10.1093/ijlct/cts049
- 515 Imyim, A., Prapalimrungsi, E., 2010. Humic acids removal from water by aminopropyl  
516 functionalized rice husk ash. *J. Hazard. Mater.* 184, 775–781.  
517 doi:10.1016/j.jhazmat.2010.08.108
- 518 Itodo, A.U., Aisagbonhi, N.B., Itodo, H., 2014. Thermal regeneration of spent coconut  
519 (*Cocos Nucifera*) shells activated carbon for Pb<sup>2+</sup> adsorption. *Stud. Univ. “Vasile*  
520 *Goldis”* 24, 147–156.
- 521 Iyer, R.S., Scott, J. a., 2001. Power station fly ash - A review of value-added utilization  
522 outside of the construction industry. *Resour. Conserv. Recycl.* 31, 217–228.  
523 doi:10.1016/S0921-3449(00)00084-7
- 524 Jacukowicz-Sobala, I., Ociński, D., Kociołek-Balawejder, E., 2015. Iron and aluminium  
525 oxides containing industrial wastes as adsorbents of heavy metals: Application  
526 possibilities and limitations. *Waste Manag. Res.* 33, 612–629.

- 527 doi:10.1177/0734242X15584841
- 528 Jala, S., Goyal, D., 2006. Fly ash as a soil ameliorant for improving crop production - A  
529 review. *Bioresour. Technol.* 97, 1136–1146. doi:10.1016/j.biortech.2004.09.004
- 530 Jiang, S., Huang, L., Nguyen, T.A.H., Ok, Y.S., Rudolph, V., Yang, H., Zhang, D., 2015.  
531 Copper and zinc adsorption by softwood and hardwood biochars under elevated  
532 sulphate-induced salinity and acidic pH conditions. *Chemosphere* 142, 64–71.  
533 doi:10.1016/j.chemosphere.2015.06.079
- 534 Juckes, L., 2011. Basics of slag production - News, events & research from Global Slag  
535 [WWW Document]. *Glob. slag*. URL [www.globalslag.com/magazine/articles/604-](http://www.globalslag.com/magazine/articles/604-basics-of-slag-production)  
536 [basics-of-slag-production](http://www.globalslag.com/magazine/articles/604-basics-of-slag-production) (accessed 10.16.15).
- 537 Kalra, N., Jain, M.C., Joshi, H.C., Choudhary, R., Harit, R.C., Vatsa, B.K., Sharma, S.K.,  
538 Kumar, V., 1998. Flyash as a soil conditioner and fertilizer. *Bioresour. Technol.* 64,  
539 163–167. doi:10.1016/S0960-8524(97)00187-9
- 540 Katal, R., Baei, M.S., Rahmati, H.T., Esfandian, H., 2012. Kinetic, isotherm and  
541 thermodynamic study of nitrate adsorption from aqueous solution using modified rice  
542 husk. *J. Ind. Eng. Chem.* 18, 295–302. doi:10.1016/j.jiec.2011.11.035
- 543 Kenes, K., Yerdos, O., Zulkhair, M., Yerlan, D., 2012. Study on the effectiveness of  
544 thermally treated rice husks for petroleum adsorption. *J. Non. Cryst. Solids* 358, 2964–  
545 2969. doi:10.1016/j.jnoncrysol.2012.07.017
- 546 Kizito, S., Wu, S., Kipkemoi Kirui, W., Lei, M., Lu, Q., Bah, H., Dong, R., 2015. Evaluation  
547 of slow pyrolyzed wood and rice husks biochar for adsorption of ammonium nitrogen  
548 from piggery manure anaerobic digestate slurry. *Sci. Total Environ.* 505, 102–112.  
549 doi:10.1016/j.scitotenv.2014.09.096
- 550 Krishnani, K., Meng, X., Christodoulatos, C., Boddu, V., 2008. Biosorption mechanism of  
551 nine different heavy metals onto biomatrix from rice husk. *J. Hazard. Mater.* 153, 1222–  
552 1234. doi:10.1016/j.jhazmat.2007.09.113
- 553 Kumar, A., Mohanta, K., Kumar, D., Parkash, O., 2012. Properties and Industrial  
554 Applications of Rice husk : A review. *Int. J. Emerg. Technol. Adv. Eng.* 2, 86–90.
- 555 Kumar, A., Sengupta, B., Dasgupta, D., Mandal, T., Datta, S., 2016. Recovery of value added  
556 products from rice husk ash to explore an economic way for recycle and reuse of  
557 agricultural waste. *Rev. Environ. Sci. Biotechnol.* 15, 1–19. doi:10.1007/s11157-015-  
558 9388-0
- 559 Kumar, B., Kumar, U., Pandey, K.M., 2014. Suitability of Rice Husk as Bio Sorbent for  
560 removal of dyes from aqueous solution on the basis of chemical oxygen demand  
561 analysis. *Glob. J. reseraches Eng. Civ. Struct. Eng.* 14, 51–54.
- 562 Kyzas, G.Z., 2012. Commercial coffee wastes as materials for adsorption of heavy metals  
563 from aqueous solutions. *Materials (Basel)*. 5, 1826–1840. doi:10.3390/ma5101826
- 564 Labidi, N., 2008. Removal of Mercury from Aqueous Solutions by Waste Brick. *Int. J.*  
565 *Environ. Res.* 2, 275–278.
- 566 Lamine, S.M., Ridha, C., Mahfoud, H.M., Mouad, C., Lotfi, B., Al-Dujaili, A.H., 2014.  
567 Chemical activation of an activated carbon prepared from coffee residue. *Energy*  
568 *Procedia* 50, 393–400. doi:10.1016/j.egypro.2014.06.047

- 569 Lavat, A.E., Trezza, M. a., Poggi, M., 2009. Characterization of ceramic roof tile wastes as  
570 pozzolanic admixture. *Waste Manag.* 29, 1666–1674.  
571 doi:10.1016/j.wasman.2008.10.019
- 572 Li, C., Dong, Y., Wu, D., Peng, L., Kong, H., 2011. Surfactant modified zeolite as adsorbent  
573 for removal of humic acid from water. *Appl. Clay Sci.* 52, 353–357.  
574 doi:10.1016/j.clay.2011.03.015
- 575 Li, Y., Liu, C., Luan, Z., Peng, X., Zhu, C., Chen, Z., Zhang, Z., Fan, J., Jia, Z., 2006.  
576 Phosphate removal from aqueous solutions using raw and activated red mud and fly ash.  
577 *J. Hazard. Mater.* 137, 374–83. doi:10.1016/j.jhazmat.2006.02.011
- 578 Liang, C., Chen, Y.J., 2010. Evaluation of activated carbon for remediating benzene  
579 contamination: Adsorption and oxidative regeneration. *J. Hazard. Mater.* 182, 544–551.  
580 doi:10.1016/j.jhazmat.2010.06.066
- 581 Lippke, B., Gustafson, R., Venditti, R., Steele, P., Volk, T. a., Oneil, E., Johnson, L.,  
582 Puettmann, M.E., Skog, K., 2012. Comparing Life-Cycle Carbon and Energy Impacts  
583 for Biofuel, Wood Product, and Forest Management Alternatives\*. *For. Prod. J.* 62,  
584 247–257. doi:10.13073/FPJ-D-12-00017.1
- 585 Liu, H., Liu, R., Tian, C., Jiang, H., Liu, X., Zhang, R., Qu, J., 2012. Removal of natural  
586 organic matter for controlling disinfection by-products formation by enhanced  
587 coagulation: A case study. *Sep. Purif. Technol.* 84, 41–45.  
588 doi:10.1016/j.seppur.2011.07.009
- 589 Liu, W., Chen, X., Li, W., Yu, Y., Yan, K., 2014. Environmental assessment, management  
590 and utilization of red mud in China. *J. Clean. Prod.* 84, 606–610.  
591 doi:10.1016/j.jclepro.2014.06.080
- 592 Liu, Y., Naidu, R., 2014. Hidden values in bauxite residue (red mud): Recovery of metals.  
593 *Waste Manag.* 34, 2662–2673. doi:10.1016/j.wasman.2014.09.003
- 594 Liu, Y., Naidu, R., Ming, H., 2011. Red mud as an amendment for pollutants in solid and  
595 liquid phases. *Geoderma* 163, 1–12. doi:10.1016/j.geoderma.2011.04.002
- 596 Lo, S.F., Wang, S.Y., Tsai, M.J., Lin, L.D., 2012. Adsorption capacity and removal  
597 efficiency of heavy metal ions by Moso and Ma bamboo activated carbons. *Chem. Eng.*  
598 *Res. Des.* 90, 1397–1406. doi:10.1016/j.cherd.2011.11.020
- 599 Lopez, E., Soto, B., M, A., A, N., D, R., MT, B., 1998. Adsorbent properties of red mud and  
600 its use for wastewater treatment. *Water Res.* 32, 1314 – 1322.
- 601 Luo, S., Shen, M.-N., Wang, F., Zeng, Q.-R., Shao, J.-H., Gu, J.-D., 2016. Synthesis of  
602 Fe<sub>3</sub>O<sub>4</sub>-loaded porous carbons developed from rice husk for removal of arsenate from  
603 aqueous solution. *Int. J. Environ. Sci. Technol.* 13, 1137–1148. doi:10.1007/s13762-  
604 016-0955-x
- 605 Ma, X., Ouyang, F., 2013. Adsorption properties of biomass-based activated carbon prepared  
606 with spent coffee grounds and pomelo skin by phosphoric acid activation. *Appl. Surf.*  
607 *Sci.* 268, 566–570. doi:10.1016/j.apsusc.2013.01.009
- 608 Ma, X., Zhang, F., Zhu, J., Yu, L., Liu, X., 2014. Preparation of highly developed  
609 mesoporous activated carbon fiber from liquefied wood using wood charcoal as additive  
610 and its adsorption of methylene blue from solution. *Bioresour. Technol.* 164, 1–6.  
611 doi:10.1016/j.biortech.2014.04.050

- 612 Manique, M.C., Faccini, C.S., Onorevoli, B., Benvenuti, E.V., Caramão, E.B., 2012. Rice  
613 husk ash as an adsorbent for purifying biodiesel from waste frying oil. *Fuel* 92, 56–61.  
614 doi:10.1016/j.fuel.2011.07.024
- 615 Masoumi, A., Hemmati, K., Ghaemy, M., 2016. Chemosphere Low-cost nanoparticles  
616 sorbent from modified rice husk and a copolymer for efficient removal of Pb (II) and  
617 crystal violet from water. *Chemosphere* 146, 253–262.  
618 doi:10.1016/j.chemosphere.2015.12.017
- 619 Mehta, P.K., 2002. Greening of the Concrete Industry for Sustainable Development. *Concr.*  
620 *Int.* 23, 23–28.
- 621 Miettinen, I.T., Vartiainen, T., Martikainen, P.J., 1997. Phosphorus and Bacterial Growth in  
622 Drinking Water. *Appl. Environ. Microbiol.* 63, 3242–3245.
- 623 Mirabella, N., Castellani, V., Sala, S., 2014. Current options for the valorization of food  
624 manufacturing waste: A review. *J. Clean. Prod.* 65, 28–41.  
625 doi:10.1016/j.jclepro.2013.10.051
- 626 Mohammed, J., Nasri, N.S., Ahmad Zaini, M.A., Hamza, U.D., Ani, F.N., 2015. Adsorption  
627 of benzene and toluene onto KOH activated coconut shell based carbon treated with  
628 NH<sub>3</sub>. *Int. Biodeterior. Biodegrad.* 102, 245–255. doi:10.1016/j.ibiod.2015.02.012
- 629 Mohan, S., Sreelakshmi, G., 2008. Fixed bed column study for heavy metal removal using  
630 phosphate treated rice husk. *J. Hazard. Mater.* 153, 75–82.  
631 doi:10.1016/j.jhazmat.2007.08.021
- 632 Mohod, C. V., Dhote, J., 2013. Review of heavy metals in drinking water and their effect on  
633 human health. *Ijirset* 2, 2992–2996.
- 634 Naceri, A., Hamina, M.C., 2009. Use of waste brick as a partial replacement of cement in  
635 mortar. *Waste Manag.* 29, 2378–84. doi:10.1016/j.wasman.2009.03.026
- 636 Namasivayam, C., Sangeetha, D., 2008. Application of coconut coir pith for the removal of  
637 sulfate and other anions from water. *Desalination* 219, 1–13.  
638 doi:10.1016/j.desal.2007.03.008
- 639 Namasivayam, C., Sangeetha, D., 2004. Equilibrium and kinetic studies of adsorption of  
640 phosphate onto ZnCl<sub>2</sub> activated coir pith carbon. *J. Colloid Interface Sci.* 280, 359–365.  
641 doi:10.1016/j.jcis.2004.08.015
- 642 Nandal, M., Hood, R., Dhanial, G., 2014. Tea Wastes as a Sorbent for Removal of Heavy  
643 Metals from wastewater. *Int. J. Curr. Eng. Technol.* 4, 1–5.
- 644 Nascimento, M., Soares, P.S.M., Souza, V.P. De, 2009. Adsorption of heavy metal cations  
645 using coal fly ash modified by hydrothermal method. *Fuel* 88, 1714–1719.  
646 doi:10.1016/j.fuel.2009.01.007
- 647 Nasuha, N., Hameed, B.H., Din, A.T.M., 2010. Rejected tea as a potential low-cost adsorbent  
648 for the removal of methylene blue. *J. Hazard. Mater.* 175, 126–132.  
649 doi:10.1016/j.jhazmat.2009.09.138
- 650 Nigam, P., Armour, G., Banat, I.M., Singh, D., Marchant, R., 2000. Physical removal of  
651 textile dyes from effluents and solid-state fermentation of dye-adsorbed agricultural  
652 residues. *Bioresour. Technol.* 72, 219–226. doi:10.1016/S0960-8524(99)00123-6
- 653 Nikraz, H.R., Bodley, A.J., Cooling, D.J., Kong, P.Y.L., Soomro, M., 2007. Comparison of

- 654 Physical Properties between Treated and Untreated Bauxite Residue Mud. *J. Mater. Civ.*  
655 *Eng.* 19, 2–9.
- 656 Oguz, E., Gurses, A., Yalcin, M., 2003. Removal of phosphate from waste waters by  
657 adsorption. *Water. Air. Soil Pollut.* 148, 279–287. doi:10.1023/A:1025417901030
- 658 Ohe, K., Nagae, Y., Nakamura, S., Baba, Y., 2003. Removal of Nitrate Anion by  
659 Carbonaceous Materials Prepared from Bamboo and Coconut Shell. *J. Chem. Eng.*  
660 *JAPAN* 36, 511–515. doi:10.1252/jcej.36.511
- 661 Omorogie, M.O., Babalola, J.O., Unuabonah, E.I., 2014. Regeneration strategies for spent  
662 solid matrices used in adsorption of organic pollutants from surface water: a critical  
663 review. *Desalin. Water Treat.* 1–27. doi:10.1080/19443994.2014.967726
- 664 Orlando, U.S., Baes, a. U., Nishijima, W., Okada, M., 2002. Preparation of agricultural  
665 residue anion exchangers and its nitrate maximum adsorption capacity. *Chemosphere*  
666 48, 1041–1046. doi:10.1016/S0045-6535(02)00147-9
- 667 Orlando, U.S., Okuda, T., Baes, a. U., Nishijima, W., Okada, M., 2003. Chemical properties  
668 of anion-exchangers prepared from waste natural materials. *React. Funct. Polym.* 55,  
669 311–318. doi:10.1016/S1381-5148(03)00002-6
- 670 Pandey, V.C., Singh, N., 2010. Impact of fly ash incorporation in soil systems. *Agric.*  
671 *Ecosyst. Environ.* 136, 16–27. doi:10.1016/j.agee.2009.11.013
- 672 Parfitt, J., Barthel, M., Macnaughton, S., 2010. Food waste within food supply chains:  
673 quantification and potential for change to 2050. *Philos. Trans. R. Soc. B Biol. Sci.* 365,  
674 3065–3081. doi:10.1098/rstb.2010.0126
- 675 Plaza, M.G., González, A.S., Pevida, C., Pis, J.J., Rubiera, F., 2012. Valorisation of spent  
676 coffee grounds as CO<sub>2</sub> adsorbents for postcombustion capture applications. *Appl.*  
677 *Energy* 99, 272–279. doi:10.1016/j.apenergy.2012.05.028
- 678 Pradhan, J., Das, J., Das, S., Thakur, R.S., Mud, A.R., 1998. Adsorption of Phosphate from  
679 Aqueous Solution Using Activated Red Mud. *J. Colloid Interface Sci.* 204, 169–172.
- 680 Pujol, D., Liu, C., Gominho, J., Olivella, M.À., Fiol, N., Villaescusa, I., Pereira, H., 2013.  
681 The chemical composition of exhausted coffee waste. *Ind. Crops Prod.* 50, 423–429.  
682 doi:10.1016/j.indcrop.2013.07.056
- 683 Querol, X., Moreno, N., Umaa, J.C., Alastuey, a., Hernández, E., López-Soler, a., Plana, F.,  
684 2002. Synthesis of zeolites from coal fly ash: an overview. *Int. J. Coal Geol.* 50, 413–  
685 423. doi:10.1016/S0166-5162(02)00124-6
- 686 Quinlivan, P. a., Li, L., Knappe, D.R.U., 2005. Effects of activated carbon characteristics on  
687 the simultaneous adsorption of aqueous organic micropollutants and natural organic  
688 matter. *Water Res.* 39, 1663–1673. doi:10.1016/j.watres.2005.01.029
- 689 Qureshi, N., Schripsema, J., Lienhardt, J., Blaschek, H.P., 2000. Continuous solvent  
690 production by *Clostridium beijerinckii* BA101 immobilized by adsorption onto brick.  
691 *World J. Microbiol. Biotechnol.* 16, 377–382. doi:10.1023/A:1008984509404
- 692 Rafatullah, M., Sulaiman, O., Hashim, R., Ahmad, A., 2012. Removal of cadmium (II) from  
693 aqueous solutions by adsorption using meranti wood. *Wood Sci. Technol.* 46, 221–241.  
694 doi:10.1007/s00226-010-0374-y
- 695 Reffas, a., Bernardet, V., David, B., Reinert, L., Lehocine, M.B., Dubois, M., Batisse, N.,

- 696 Duclaux, L., 2010. Carbons prepared from coffee grounds by H<sub>3</sub>PO<sub>4</sub> activation:  
697 Characterization and adsorption of methylene blue and Nylosan Red N-2RBL. *J.*  
698 *Hazard. Mater.* 175, 779–788. doi:10.1016/j.jhazmat.2009.10.076
- 699 Reh, L., 2013. Process engineering in circular economy. *Particuology* 11, 119–133.  
700 doi:10.1016/j.partic.2012.11.001
- 701 Renman, G., Renman, A., 2012. Sustainable use of crushed autoclaved aerated concrete  
702 (CAAC) as a filter medium in wastewater purification, in: 8th International Conference  
703 on Sustainable Management of Waste and Recycled Materials in Construction,  
704 Gothenburg, Sweden, 30 May–1 June, 2012. Proceedings. pp. 1–7.
- 705 Resende, E.C. De, Gissane, C., Nicol, R., Heck, R.J., Guerreiro, M.C., Coelho, J.V., Oliveira,  
706 L.C.A. De, Palmisano, P., Berruti, F., Briens, C., Schlaf, M., 2013. Synergistic co-  
707 processing of Red Mud waste from the Bayer process and a crude untreated waste  
708 stream from bio-diesel production. *Green Chem.* 15, 496. doi:10.1039/c2gc36714a
- 709 Ricehusk.com, 2015. Rice Husk Information - riceshuk.com Pte Ltd. [WWW Document].  
710 URL [www.ricehusk.com/faq](http://www.ricehusk.com/faq) (accessed 10.13.15).
- 711 Richardson, S., 2003. Disinfection by-products and other emerging contaminants in drinking  
712 water. *TrAC Trends Anal. Chem.* 22, 666–684. doi:10.1016/S0165-9936(03)01003-3
- 713 Ruggiero, D., 2013. Waste in Europe: Production and treatment of waste in the European  
714 Union's countries. Italy.
- 715 Saakshy, Singh, K., Gupta, A.B., Sharma, A.K., 2015. Fly ash as low cost adsorbent for  
716 treatment of effluent of handmade paper industry-Kinetic and modelling studies for  
717 direct black dye. *J. Clean. Prod.* 112, 1227–1240. doi:10.1016/j.jclepro.2015.09.058
- 718 Safarik, I., Horska, K., Svobodova, B., Safarikova, M., 2012. Magnetically modified spent  
719 coffee grounds for dyes removal. *Eur. Food Res. Technol.* 234, 345–350.  
720 doi:10.1007/s00217-011-1641-3
- 721 Salim, M., Munekage, Y., 2009. Removal of Arsenic from Aqueous Solution Using Silica  
722 Ceramic: Adsorption Kinetics and Equilibrium Studies. *Int. J. Environ. Res.* 3, 13–22.
- 723 Santiagué, A.F., 2013. A second life for rice husk. *Rice Today* 12, 12–13.
- 724 Sathish, R.S., Raju, N.S.R., Raju, G.S., Nageswara Rao, G., Kumar, K.A., Janardhana, C.,  
725 2007. Equilibrium and Kinetic Studies for Fluoride Adsorption from Water on  
726 Zirconium Impregnated Coconut Shell Carbon. *Sep. Sci. Technol.* 42, 769–788.  
727 doi:10.1080/01496390601070067
- 728 Savage, a J., Tyrrel, S.F., 2005. Compost liquor bioremediation using waste materials as  
729 biofiltration media. *Bioresour. Technol.* 96, 557–64. doi:10.1016/j.biortech.2004.06.016
- 730 Selvaraju, N., Pushpavanam, S., 2009. Adsorption characteristics on sand and brick beds.  
731 *Chem. Eng. J.* 147, 130–138. doi:10.1016/j.cej.2008.06.040
- 732 Shannon, M. a, Bohn, P.W., Elimelech, M., Georgiadis, J.G., Mariñas, B.J., Mayes, A.M.,  
733 2008. Science and technology for water purification in the coming decades. *Nature* 452,  
734 301–10. doi:10.1038/nature06599
- 735 Shi, L., Yang, K., Zhao, Q., Wang, H., Cui, Q., 2015. Characterization and Mechanisms of H  
736 <sub>2</sub> S and SO <sub>2</sub> Adsorption by Activated Carbon. *Energy & Fuels* 29, 6678–6685.  
737 doi:10.1021/acs.energyfuels.5b01696

- 738 SI No 278 of 2007, 2007. European Communities (Drinking Water) (No. 2) Regulations  
739 2007. Ireland.
- 740 Siddique, R., Bennacer, R., 2012. Use of iron and steel industry by-product (GGBS) in  
741 cement paste and mortar. *Resour. Conserv. Recycl.* 69, 29–34.  
742 doi:10.1016/j.resconrec.2012.09.002
- 743 Singhania, N.P., 2004. Adding to the mix. *Inst. Civ. Eng. Surv.* 850.
- 744 Song, S., Hau, Y., Saman, N., Johari, K., Cheu, S., Kong, H., Mat, H., 2016. Journal of  
745 Environmental Chemical Engineering Process analysis of mercury adsorption onto  
746 chemically modified rice straw in a fixed-bed adsorber. *Biochem. Pharmacol.* 4, 1685–  
747 1697. doi:10.1016/j.jece.2016.02.033
- 748 Sousa, F.W., Oliveira, A.G., Ribeiro, J.P., Rosa, M.F., Keukeleire, D., Nascimento, R.F.,  
749 2010. Green coconut shells applied as adsorbent for removal of toxic metal ions using  
750 fixed-bed column technology. *J. Environ. Manage.* 91, 1634–1640.  
751 doi:10.1016/j.jenvman.2010.02.011
- 752 Srivastava, V.C., Mall, I.D., Mishra, I.M., 2007. Adsorption thermodynamics and isosteric  
753 heat of adsorption of toxic metal ions onto bagasse fly ash (BFA) and rice husk ash  
754 (RHA). *Chem. Eng. J.* 132, 267–278. doi:10.1016/j.cej.2007.01.007
- 755 Topçu, I.B., 1997. Physical and mechanical properties of concretes produced with waste  
756 concrete. *Cem. Concr. Res.* 27, 1817–1823. doi:10.1016/S0008-8846(97)00190-7
- 757 Topçu, İ.B., Şengel, S., 2004. Properties of concretes produced with waste concrete  
758 aggregate. *Cem. Concr. Res.* 34, 1307–1312. doi:10.1016/j.cemconres.2003.12.019
- 759 Tran, N.H., Ngo, H.H., Urase, T., Gin, K.Y.-H., 2015. A critical review on characterization  
760 strategies of organic matter for wastewater and water treatment processes. *Bioresour.*  
761 *Technol.* 193, 523–533. doi:10.1016/j.biortech.2015.06.091
- 762 Ugurlu, a., Salman, B., 1998. Phosphorus removal by fly ash. *Environ. Int.* 24, 911–918.  
763 doi:10.1016/S0160-4120(98)00079-8
- 764 UNCTAD, 2012. Coconut - UNCTAD.org [WWW Document]. Coconut Commod. Profile.  
765 URL [www.unctad.info/en/Infocomm/AACP-Products/COMMODITY-PROFILE---](http://www.unctad.info/en/Infocomm/AACP-Products/COMMODITY-PROFILE---Coconut2/)  
766 [Coconut2/](http://www.unctad.info/en/Infocomm/AACP-Products/COMMODITY-PROFILE---Coconut2/) (accessed 10.9.15).
- 767 United Nations, 2015. FAO Statistical Pocketbook. FAO, Rome.
- 768 USEPA, 2009. National Primary Drinking Water Regulations, The Public Health Service  
769 Act. Environmental Protection Agency, Washington DC.
- 770 Vlaev, L., Petkov, P., Dimitrov, a., Genieva, S., 2011. Cleanup of water polluted with crude  
771 oil or diesel fuel using rice husks ash. *J. Taiwan Inst. Chem. Eng.* 42, 957–964.  
772 doi:10.1016/j.jtice.2011.04.004
- 773 Vocciantè, M., Trofa, M., Rodriguez-Estupinan, P., Giraldo, L., D'Auria, T., Moreno-Pirajan,  
774 J.C., Erto, A., 2014. A rigorous procedure for the design of adsorption units for the  
775 removal of cadmium and nickel from process wastewaters. *J. Clean. Prod.* 77, 35–46.  
776 doi:10.1016/j.jclepro.2013.12.001
- 777 Wang, B., Lehmann, J., Hanley, K., Hestrin, R., Enders, A., 2015. Adsorption and desorption  
778 of ammonium by maple wood biochar as a function of oxidation and pH. *Chemosphere*  
779 138, 120–126. doi:10.1016/j.chemosphere.2015.05.062

- 780 Wang, S., Ang, H.M., Tadé, M.O., 2008a. Novel applications of red mud as coagulant,  
781 adsorbent and catalyst for environmentally benign processes. *Chemosphere* 72, 1621–  
782 1635. doi:10.1016/j.chemosphere.2008.05.013
- 783 Wang, S., Terdkiatburana, T., Tadé, M.O., 2008b. Single and co-adsorption of heavy metals  
784 and humic acid on fly ash. *Sep. Purif. Technol.* 58, 353–358.  
785 doi:10.1016/j.seppur.2007.05.009
- 786 Wang, S., Wu, H., 2006. Environmental-benign utilisation of fly ash as low-cost adsorbents.  
787 *J. Hazard. Mater.* 136, 482–501. doi:10.1016/j.jhazmat.2006.01.067
- 788 Wang, S., Zhu, Z.H., 2007. Humic acid adsorption on fly ash and its derived unburned  
789 carbon. *J. Colloid Interface Sci.* 315, 41–46. doi:10.1016/j.jcis.2007.06.034
- 790 Wang, T., Lin, J., Chen, Z., Megharaj, M., Naidu, R., 2014. Green synthesized iron  
791 nanoparticles by green tea and eucalyptus leaves extracts used for removal of nitrate in  
792 aqueous solution. *J. Clean. Prod.* 83, 413–419. doi:10.1016/j.jclepro.2014.07.006
- 793 Wang, Z., Guo, H., Shen, F., Yang, G., Zhang, Y., Zeng, Y., Wang, L., Xiao, H., Deng, S.,  
794 2015. Biochar produced from oak sawdust by Lanthanum (La)-involved pyrolysis for  
795 adsorption of ammonium (NH<sub>4</sub>(+)), nitrate (NO<sub>3</sub>(-)), and phosphate (PO<sub>4</sub>(3-)).  
796 *Chemosphere* 119, 646–53. doi:10.1016/j.chemosphere.2014.07.084
- 797 Ward, C.R., French, D., 2006. Determination of glass content and estimation of glass  
798 composition in fly ash using quantitative X-ray diffractometry. *Fuel* 85, 2268–2277.  
799 doi:10.1016/j.fuel.2005.12.026
- 800 Water\_Team, E., 2012. Secure Archive for Environmental Research Data [WWW  
801 Document]. *Drink. Water Monit. Results Water Supply Details Irel.* doi:c434eae6-697f-  
802 11e3-b233-005056ae0019
- 803 Wei, L., Wang, K., Zhao, Q., Xie, C., Qiu, W., Jia, T., 2011. Kinetics and equilibrium of  
804 adsorption of dissolved organic matter fractions from secondary effluent by fly ash. *J.*  
805 *Environ. Sci.* 23, 1057–1065. doi:10.1016/S1001-0742(10)60597-9
- 806 Weng, C.-H., Lin, Y.-T., Hsu, S.-C., 2014. Electrochemical Regeneration of Zn-Saturated  
807 Granular Activated Carbon from Electroplating Wastewater Plant. *Sep. Sci. Technol.* 49,  
808 506–512. doi:10.1080/01496395.2013.853083
- 809 WHO/UNICEF, 2015. Progresss on sanitation and drinking water - 2015 Update and MDG  
810 Assessment. Geneva, Switzerland.
- 811 Wilczak, A., Jacangelo, J.G., Marcinko, J.P., Odell, L.H., Kirmeyer, J., Wolfe, R.L.,  
812 Kirmeyer, G.J., 1996. Occurrence of nitrification in chloraminated distribution systems.  
813 *Am. Water Work. Assoc.* 88.
- 814 World Coal Association, 2015. World Coal Association [WWW Document]. URL  
815 [www.worldcoal.org/coal/uses-of-coal/coal-combustion-products/](http://www.worldcoal.org/coal/uses-of-coal/coal-combustion-products/) (accessed 4.12.16).
- 816 Wu, D., Zhang, B., Li, C., Zhang, Z., Kong, H., 2006. Simultaneous removal of ammonium  
817 and phosphate by zeolite synthesized from fly ash as influenced by salt treatment. *J.*  
818 *Colloid Interface Sci.* 304, 300–306. doi:10.1016/j.jcis.2006.09.011
- 819 Yadav, D., Kapur, M., Kumar, P., Mondal, M.K., 2015. Adsorptive removal of phosphate  
820 from aqueous solution using rice husk and fruit juice residue. *Process Saf. Environ. Prot.*  
821 94, 402–409. doi:10.1016/j.psep.2014.09.005

- 822 Yang, J., Zhao, Y., Zhang, J., Zheng, C., 2016. Removal of elemental mercury from flue gas  
823 by recyclable CuCl<sub>2</sub> modified magnetospheres catalyst from fly ash. Part 2.  
824 Identification of involved reaction mechanism. *Fuel* 167, 366–374.  
825 doi:10.1016/j.fuel.2015.11.003
- 826 Ye, H., Zhu, Q., Du, D., 2010. Adsorptive removal of Cd(II) from aqueous solution using  
827 natural and modified rice husk. *Bioresour. Technol.* 101, 5175–5179.  
828 doi:10.1016/j.biortech.2010.02.027
- 829 Yuan, H., Shen, L., 2011. Trend of the research on construction and demolition waste  
830 management. *Waste Manag.* 31, 670–9. doi:10.1016/j.wasman.2010.10.030
- 831 Zhang, B.H., Wu, D.Y., Wang, C., He, S.B., Zhang, Z.J., Kong, H.N., 2007. Simultaneous  
832 removal of ammonium and phosphate by zeolite synthesized from coal fly ash as  
833 influenced by acid treatment. *J. Environ. Sci.* 19, 540–545. doi:10.1016/S1001-  
834 0742(07)60090-4
- 835 Zhang, W., Chang, Q.-G., Liu, W.-D., Li, B.-J., Jiang, W.-X., Fu, L.-J., Ying, W.-C., 2007.  
836 Selecting activated carbon for water and wastewater treatability studies. *Environ. Prog.*  
837 28, 289–298. doi:10.1002/ep
- 838 Zhang, Y., Song, X.-L., Huang, S.-T., Geng, B.-Y., Chang, C.-H., Sung, I.-Y., 2013.  
839 Adsorption of nitrate ions onto activated carbon prepared from rice husk by NaOH  
840 activation. *Desalin. Water Treat.* 52, 4935–4941. doi:10.1080/19443994.2013.809984
- 841 Zhao, Y., Yang, Y., Yang, S., Wang, Q., Feng, C., Zhang, Z., 2013. Adsorption of high  
842 ammonium nitrogen from wastewater using a novel ceramic adsorbent and the  
843 evaluation of the ammonium-adsorbed-ceramic as fertilizer. *J. Colloid Interface Sci.*  
844 393, 264–270. doi:10.1016/j.jcis.2012.10.028
- 845 Zhu, K., Fu, H., Zhang, J., Lv, X., Tang, J., Xu, X., 2012. Studies on removal of NH<sub>4</sub><sup>+</sup>-N  
846 from aqueous solution by using the activated carbons derived from rice husk. *Biomass*  
847 and Bioenergy 43, 18–25. doi:10.1016/j.biombioe.2012.04.005
- 848 Zhu, R., Zhu, J., Ge, F., Yuan, P., 2009. Regeneration of spent organoclays after the sorption  
849 of organic pollutants: A review. *J. Environ. Manage.* 90, 3212–3216.  
850 doi:10.1016/j.jenvman.2009.06.015
- 851

**Figure and Table Captions**

**Figure 1** Disposal and utilisation of fly ash in the construction industry and underground mining in Europe (EU 15) in 2010 (Ecoba, 2015)

**Figure 2** Composition of C&D waste from EU member states excluding Estonia and Finland (Adapted from (European Commission, 2011))

**Table 1** Media Characterisation

**Table 2** Previous studies of fly ash adsorption

**Table 3** Previous studies of Bayer residue adsorption

**Table 4** Previous studies of coconut shell activated carbon adsorption


**Table 5** Previous adsorption studies using rice husk

**Table 6** Previous adsorption studies using crushed concrete

**Table 7** Previous adsorption studies with masonry waste

**Table 8** Previous studies of adsorption using wood waste

**Table 9** A brief summary of media potentials

**Figure 3**


**Figure 4**

Table 10

	Fly Ash	GGBS	Bayer Residue	Coconut Shell	Coffee Waste	Rice Husk	Crushed Concrete	Masonry Waste
SiO <sub>2</sub>	44.5-67%	35%	5-30%					66.52%
Al <sub>2</sub> O <sub>3</sub>	22.2-30.7%	10%	10-22%					14.2%
Fe <sub>2</sub> O <sub>3</sub>	1.1-14.4%		20-45%					5.45%
CaO	0.4-4.2%	40%	0-14%					6.06%
BaO	0-0.5%							
MgO	0.3-1.6%	8%						2.35%
Na <sub>2</sub> O	0.2-0.9%		2-8%					0.67%
K <sub>2</sub> O	0.5-2.9%							2.09%
TiO <sub>2</sub>	0.9-1.9%		4-20%					
P <sub>2</sub> O <sub>5</sub>	0.1-2.7%							
SO <sub>3</sub>	0.1-0.5%							0.75%
Carbon %				48.6	57-59	35		
Hydrogen %				6.5	7.1-7.6	4-5		
Oxygen %				44.6	26-23	31-37		
Nitrogen %				0.1	1.2-1.3	0.23-0.32		
Sulphur %				0.1		0.04-0.08		
Ash %						22-29		
Moisture						8-9		
Ca g kg <sup>-1</sup>							240-551	
Fe g kg <sup>-1</sup>							17-29	
Al g kg <sup>-1</sup>							18-30	
P g kg <sup>-1</sup>							1-13	
Cu mg kg <sup>-1</sup>							37-87	
Pb mg kg <sup>-1</sup>							33-87	
Cr mg kg <sup>-1</sup>							22-115	
Cd mg kg <sup>-1</sup>							1-20	
Reference	Ward & French (2006)	Ecoce m (2015)	EAA (2013)	Daud (2004)	Pujol et al. (2013)	Kumar et al. (2012)	Egemose et al. (2012)	Naceri & Hamina (2009)

Table 11

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Phosphate</b>	63.2 mg g <sup>-1</sup>	Raw	Langmuir	Li et al. (2006)
	58.9 mg g <sup>-1</sup>	Heat activated at 700°C	Langmuir	
	78.4 mg g <sup>-1</sup>	Acid activated with 0.25 M HCl	Langmuir	
	27.4 g g <sup>-1</sup>	At 40°C, with initial concentration of 100 mg/L	Langmuir	Ugurlu & Salman (1998)
	20. mg g <sup>-1</sup>	Raw fly ash	Langmuir	Wu et al. (2006)
	35.3 mg g <sup>-1</sup>	Salt treated zeolite synthesised from fly ash	Langmuir	
	42. mg g <sup>-1</sup>	Raw fly ash	Langmuir	Chen et al. (2007)
<b>Humic Acid</b>	126.6 mg g <sup>-1</sup>	zeolite synthesised from (high calcium) fly ash	Langmuir	Li et al. (2011)
	31.6 mg g <sup>-1</sup>	zeolite synthesised from (low calcium) fly ash	Langmuir	
	36.6 mg g <sup>-1</sup>	Raw, single pollutant system	Langmuir	Wang et al. (2008a)
	45.5 mg g <sup>-1</sup>	Raw, all unburned carbon present	Langmuir	Wang & Zhu (2007)
<b>DOC</b>	0.3 mg g <sup>-1</sup>	Hydrophobic acid fraction of DOC. Fly ash eluted with methanol	Langmuir	Wei et al. (2011)

Table 12

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Phosphate</b>	113.9 mg g <sup>-1</sup>	Raw Heat activated at 700°C	Langmuir	Li et al. (2006)
	345.5 mg g <sup>-1</sup>	Acid activated with 0.25 M HCl	Langmuir	
	161.6 mg g <sup>-1</sup>		Langmuir	
	K = 0.47	Acid activated with 2M HCl, experiment @ 30°C	Freundlich	Huang et al. (2008)
	K = 0.62	Acid activated with 2M HCl, experiment @ 40°C	Freundlich	
	K = 0.24	Raw, adsorption experiment @ 30°C	Freundlich	
	K = 0.33	Raw, adsorption experiment @ 40°C	Freundlich	
	75.9 mg g <sup>-1</sup>	Acid activated with 20% HCl	Langmuir	Pradhan et al. (1998)
	58.1 mg g <sup>-1</sup>	Neutralised and aggregated, 48 h study	Langmuir	Lopez et al. (1998)
<b>Nitrate</b>	365.8 mg g <sup>-1</sup>	Acid activated with 20% HCl @ 40°C	Langmuir	Cengeloglu et al. (2006)
	117.8 mg g <sup>-1</sup>	Original red mud	Langmuir	
<b>Ammonium</b>	18 % removal efficiency	Packed column	N/A	Lopez et al. (1998)

K: Freundlich adsorption capacity factor

Table 13

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Ammonium</b>	K = 44.9	Activated carbon from coconut shell, at pH 9	Freundlich	Boopathy et al. (2013)
	K = 1875	5:3 Limestone:GAC mix	Freundlich	Hussain et al. (2007)
<b>Nitrate</b>	33.7 mg g <sup>-1</sup>	NaOH modified coconut shell powder	Langmuir	de Lima et al. (2012)
	10.3 mg g <sup>-1</sup>	ZnCl <sub>2</sub> activated coir pith (from coconut husk)	Langmuir	Namasivayam & Sangeetha (2008)
	18.6 mg g <sup>-1</sup>	Activated carbon from coconut shell, at pH 2-4	Langmuir	Ohe et al. (2003)
	55.8 mg g <sup>-1</sup>	Anion exchanger produced from coconut shell	Langmuir	Orlando et al. (2002)
	6.2 mg g <sup>-1</sup>	Anion exchanger produced from coconut shell	Langmuir	Orlando et al. (2003)
<b>Phosphate</b>	3.0 mg g <sup>-1</sup>	5:3 Limestone:GAC mix	Langmuir	Hussain et al. (2011)
	200 mg g <sup>-1</sup>	NaOH modified coconut shell powder	Langmuir	de Lima et al. (2012)
	5.1 mg g <sup>-1</sup>	ZnCl <sub>2</sub> activated coir pith (from coconut husk)	Langmuir	Namasivayam & Sangeetha (2004)
	K = 0.0001 L g <sup>-1</sup>	Activated carbon from coconut shell	Frumkin	Agrawal et al. (2011)

K: Freundlich adsorption capacity factor

Table 14

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Nitrate</b>	55.6 mg g <sup>-1</sup>	Anionic sorbent prepared with rice husk	Langmuir	Katal et al. (2012)
	74.4 mg g <sup>-1</sup>	Anion exchanger produced from rice husk	Langmuir	Orlando et al. (2002)
	6.2 mg g <sup>-1</sup>	Anion exchanger produced from rice husk	Langmuir	Orlando et al. (2003)
	70.2 mg g <sup>-1</sup>	Activated carbon prepared from rice husk	Langmuir	Zhang et al. (2013)
<b>Phosphate</b>	89.6% removal	Chemically activated rice husk	Not specified	Yadav et al. (2015)
	64.3% removal	Raw rice husk	Not specified	
<b>Ammonium</b>	39.8 mg g <sup>-1</sup>	Biochar prepared from rice husk	Langmuir	Kizito et al. (2015)
	2.6 mg g <sup>-1</sup>	Rice husk charcoal	Langmuir	Han et al. (2013)
	1.4 mg g <sup>-1</sup>	Activated carbon prepared from rice husk	Pseudo-second order	Zhu et al. (2012)
<b>Humic acid</b>	45.5 mg g <sup>-1</sup>	Activated carbon prepared from rice husk	Langmuir	Daifullah et al. (2004)
	8.2 mg g <sup>-1</sup>	Modified rice husk ash	Langmuir	Imyim & Prapalimrungsi (2010)

Table 15

	<b>Adsorption Capacity</b>	<b>Comment/Conditions</b>	<b>Isotherm</b>	<b>Reference</b>
<b>Phosphate</b>	19.6 mg g <sup>-1</sup>	Initial P concentration of 1000 mg L <sup>-1</sup>	Not specified	Egemose et al. (2012)
	17.3 mg g <sup>-1</sup>	Initial P concentration of 100 mg L <sup>-1</sup>	Langmuir	Oguz et al. (2003)
	70.9 mg g <sup>-1</sup>	Initial P concentration of 10 mg L <sup>-1</sup>	Langmuir	Renman & Renman (2012)
	$\alpha$ :4.976 and $\beta$ :0.0042	Ordinary Portland cement	Frumkin	Agyei et al. (2002)

Table 16

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Nitrate</b>	14.1 mg g <sup>-1</sup>	Brick with particle size <710 μm	Langmuir	Selvaraju & Pushpavanam (2009)
<b>Phosphate</b>	18.2 mg g <sup>-1</sup>	Brick with particle size <710 μm	Langmuir	Selvaraju & Pushpavanam (2009)
	0.9 mg g <sup>-1</sup>	La(III) loaded granular ceramic	Langmuir	Chen et al. (2012)
<b>Ammonium</b>	112.4 mg g <sup>-1</sup>	Novel ceramic adsorbent	Langmuir	Zhao et al. (2013)
	35% removal	Broken brick as biofilter	Not specified	Savage & Tyrrel (2005)

Table 17

Contaminant	Adsorption Capacity	Comment/Conditions	Isotherm	Reference
<b>Ammonium</b>	5.4 mg g <sup>-1</sup>	Biochar from maple wood, pH adjusted	Langmuir	Wang et al. (2015b)
	54.8 mg g <sup>-1</sup>	Biochar from mixed wood, 1400 mg L <sup>-1</sup> initially	Langmuir	Kizito et al. (2015)
	5.3 mg g <sup>-1</sup>	Untreated biochar from oak sawdust	Langmuir	Wang et al. (2015c)
<b>Nitrate</b>	8.9 mg g <sup>-1</sup>	Untreated biochar from oak sawdust	Langmuir	Wang et al. (2015c)
	43.5 mg g <sup>-1</sup>	Activated biochar from pine wood	Langmuir	Chintala et al. (2013)
<b>Phosphate</b>	32 mg g <sup>-1</sup>	Untreated biochar from oak sawdust	Langmuir	Wang et al. (2015c)

Table 18

Media	Opportunities	Advantages	Disadvantages
<b>Fly ash</b>	17 M t	Nutrient, metal and humic acid removal Disadvantages may be mitigated by pretreatment	Potential for metal leaching
<b>GGBS</b>	<18 M t used in Europe	Limited research available	Solidification in water Potential for metal leaching
<b>Bayer residue</b>	>2700 M t	Phosphorus and metal removal	Potential for contaminant leaching
<b>Coconut shell</b>	>60 M t of coconut grown per annum	Metal, dye and anion removal	Expensive carbonization and activation processes required
<b>Tea/Coffee wastes</b>	>5 M t of tea produced per annum	Metal and cation removal Dye removal when pretreated	Expensive pre-treatments may be required
<b>Rice husk</b>	>700 M t	Metal and dye removal	Expensive pre-treatments may be required
<b>Crushed concrete</b>	25% of all C&D waste	Phosphorus and metal removal	Potential for contaminant leaching from concrete constituents
<b>Masonry</b>	30% of all C&D waste	Nutrient, metal and microbiological removal	Variation in raw material
<b>Wood waste</b>	2% of all C&D waste	Nutrient and metal removal	Variation in raw material Expensive pre-treatments may be required